## **FERROXCUBE**

# DATA SHEET

# TX58/41/18 Ferrite toroids

Supersedes data of September 2004

2008 Sep 01



Ferrite toroids TX58/41/18

#### **RING CORES (TOROIDS)**

#### Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
Σ(I/A)	core factor (C1)	1.0	mm <sup>-1</sup>
V <sub>e</sub>	effective volume	23200	mm <sup>3</sup>
l <sub>e</sub>	effective length	152	mm
A <sub>e</sub>	effective area	152	mm <sup>2</sup>
m	mass of core	≈ 110	g

#### Coating


The cores are coated with epoxy, flame retardant in accordance with "*UL 94V-0*"; UL file number E 235873. The colour is white.

Maximum operating temperature is 200  $^{\circ}$ C.

#### Isolation voltage

DC isolation voltage: 2000 V.

Contacts are applied on the edge of the ring core, which is also the critical point for the winding operation.



#### Ring core data

GRADE	A <sub>L</sub> (nH)	μί	TYPE NUMBER
3C90 des	$2890 \pm 25\%$	≈ <b>2300</b>	TX58/41/18-3C90
3C11	5400 ± 25%	≈ <b>4300</b>	TX58/41/18-3C11
3E25	6900 ± 25%	≈ 5500	TX58/41/18-3E25

#### Properties of cores under power conditions

	B (mT) at	CORE LOSS (W) at	
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C
3C90	≥320	≤ 2.6	≤2.6

2008 Sep 01 1753

Ferrite toroids TX58/41/18

#### **DATA SHEET STATUS DEFINITIONS**

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

#### **DISCLAIMER**

**Life support applications** — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

#### **PRODUCT STATUS DEFINITIONS**

STATUS	INDICATION	DEFINITION	
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.	
Design-in	des	These products are recommended for new designs.	
Preferred		These products are recommended for use in current designs and are available via our sales channels.	
Support	sup	These products are <b>not</b> recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.	

2008 Sep 01 1754

## **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Ferrite Toroids / Ferrite Rings category:

Click to view products by Ferroxcube manufacturer:

Other Similar products are found below:

5943001601 28B0200-4 28B0250-1 29D3800-000 28B0137-3 4327 018 35221 432703013571 432703033201 4327 030 37511 4327 030 37911 4327 030 57161 432703057191 B62152P0007X030 432202090241 432202101631 432202133882 432703012441 4327 030 12521 4327 030 57111 5343232001 5943000901 432703034521 5961004101 5961000621 4078034621 4077378111 28B1250-2 28B2000-3 28B1387-1 B64291A1304X000 28B2400-0 B64290A0699X010 5510-017 5961000811 CBCT-35-1 CBCT-120-1 CBCT-70-1 5977004801 5976000201 5968003801 5975011101 5977000501 5978008001 28B0355-0 7427018 M-060 CST29/19/7.5-482 T9X8X5 4077485111 TN10/6/4-3F3