
# FERROXCUBE



Supersedes data of September 2004

2008 Sep 01




# E30/15/7

#### CORE SETS

#### Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
Σ(I/A)	core factor (C1)	1.12	mm <sup>-1</sup>
Ve	effective volume	4000	mm <sup>3</sup>
l <sub>e</sub>	effective length	67.0	mm
A <sub>e</sub>	effective area	60.0	mm <sup>2</sup>
A <sub>min</sub>	minimum area	49.0	mm <sup>2</sup>
m	mass of core half	≈ 11	g



#### Core halves

 $A_L$  measured in combination with a non-gapped core half, clamping force for  $A_L$  measurements 20 ±10 N, unless stated otherwise.

GRADE	A <sub>L</sub> (nH)	μ <sub>e</sub>	TOTAL AIR GAP (μm)	TYPE NUMBER
3C81	100 ±5% <sup>(1)</sup>	≈ 89	≈ 1100	E30/15/7-3C81-E100
	160 ±5%	≈142	≈ 580	E30/15/7-3C81-A160
	250 ±5%	≈ 222	≈ 330	E30/15/7-3C81-A250
	315 ±5%	≈ 280	≈ 240	E30/15/7-3C81-A315
	400 ±8%	≈ 355	≈ 180	E30/15/7-3C81-A400
	630 ±15%	≈ 560	≈ 100	E30/15/7-3C81-A630
	2500 ±25%	≈ 2220	≈ 0	E30/15/7-3C81
3C90	100 ±5% <sup>(1)</sup>	≈ 89	≈ 1100	E30/15/7-3C90-E100
	160 ±5%	≈142	≈ 580	E30/15/7-3C90-A160
	250 ±5%	≈ 222	≈ 330	E30/15/7-3C90-A250
	315 ±5%	≈ 280	≈ 240	E30/15/7-3C90-A315
	400 ±8%	≈ 355	≈ 180	E30/15/7-3C90-A400
	630 ±15%	≈ 560	≈ 100	E30/15/7-3C90-A630
	1900 ±25%	≈ 1690	≈ 0	E30/15/7-3C90
3C91 des	2500 ±25%	≈ 2220	≈ 0	E30/15/7-3C91
3C92 des	1400 ±25%	≈ 1250	≈ 0	E30/15/7-3C92
3C94	1900 ±25%	≈ <b>1690</b>	≈ 0	E30/15/7-3C94
3C96 des	1600 ±25%	≈ <b>1</b> 420	≈ 0	E30/15/7-3C96

# E30/15/7

GRADE	A <sub>L</sub> (nH)	μ <sub>e</sub>	TOTAL AIR GAP (μm)	TYPE NUMBER
3F3	100 ±5% <sup>(1)</sup>	≈ 89	≈ 1100	E30/15/7-3F3-E100
	160 ±5%	≈142	≈ 580	E30/15/7-3F3-A160
	250 ±5%	≈ 222	≈ 330	E30/15/7-3F3-A250
	315 ±5%	≈ 280	≈ 240	E30/15/7-3F3-A315
	400 ±8%	≈ 355	≈ 180	E30/15/7-3F3-A400
	630 ±15%	≈ 560	≈ 100	E30/15/7-3F3-A630
	1600 ±25%	≈1420	≈ 0	E30/15/7-3F3
3F35 des	1250 ±25%	≈1110	≈ 0	E30/15/7-3F35

#### Note

1. Measured in combination with an equal gapped core half, clamping force for AL measurements, 20  $\pm$ 10 N.

#### Core halves of high permeability grades

Clamping force for  $A_L$  measurements 20  $\pm 10$  N.

GRADE	A <sub>L</sub> (nH)	μ <sub>e</sub>	AIR GAP (μm)	TYPE NUMBER
3C11	3300 ±25%	≈ 2930	≈ <b>0</b>	E30/15/7-3C11
3E27	4100 ±25%	≈ 3640	≈ 0	E30/15/7-3E27

#### Properties of core sets under power conditions

	B (mT) at		CORE LOSS (W) at				
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; B = 200 mT; T = 100 °C	f = 400 kHz;		
3C81	≥320	≤ 0.82	_	_	_		
3C90	≥330	≤ 0.45	≤ 0.48	_	-		
3C91	≥320	-	$\leq 0.27^{(1)}$	≤ <b>1</b> .6 <sup>(1)</sup>	-		
3C92	≥370	_	≤ 0.36	≤ 2.0	-		
3C94	≥330	-	≤ 0.36	≤ 2.0	-		
3C96	≥340	_	≤ 0.27	≤ 1.6	-		
3F3	≥320	_	≤ 0.47	-	≤ 0.80		
3F35	≥300	_	_	_	_		

#### Properties of core sets under power conditions (continued)

	B (mT) at				
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 500 kHz; B = 50 mT; T = 100 °C	f = 500 kHz; B = 100 mT; T = 100 °C	f = 1 MHz; Ĥ = 30 mT; T = 100 °C	f = 3 MHz; B = 10 mT; T = 100 °C
3C96	≥340	≤ 1.5	-	-	-
3F3	≥320	_	_	_	_
3F35	≥300	≤ 0.54	≤4.2	-	-

#### Note


1. Measured at 60  $^\circ\text{C}.$ 

2008 Sep 01

#### **COIL FORMERS**

#### **GENERAL DATA FOR E30/15/7 COIL FORMER WITHOUT PINS**

PARAMETER	SPECIFICATION
Coil former material	polyamide (PA6.6), glass reinforced, flame retardant in accordance with <i>"UL 94-HB"</i> ; UL file number E41613(M)
Maximum operating temperature	120 °C




#### WINDING DATA AND AREA PRODUCT FOR E30/15/7 COIL FORMER WITHOUT PINS (E)

NUMBER OF SECTIONS	WINDING AREA (mm²)	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm <sup>4</sup> )	TYPE NUMBER
1	80	17.0	56	4800	CP-E30/15/7-1S

### E30/15/7

#### **GENERAL DATA FOR 10-PINS E30/15/7 COIL FORMER**

PARAMETER	SPECIFICATION
Coil former material	phenolformaldehyde (PF), glass reinforced, flame retardant in accordance with <i>"UL 94V-0"</i> ; UL file number E167521(M)
Pin material	copper-tin alloy (CuSn), tin (Sn) plated
Maximum operating temperature	180 °C, <i>"IEC 60085"</i> , class H
Resistance to soldering heat	"IEC 60068-2-20", Part 2, Test Tb, method 1B: 350 °C, 3.5 s
Solderability	<i>"IEC 60068-2-20"</i> , Part 2, Test Ta, method 1: 235 °C, 2 s



#### WINDING DATA AND AREA PRODUCT FOR 10-PINS E30/15/7 COIL FORMER (E)


NUMBER OF NECTIONS	WINDING AREA (mm²)	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm <sup>4</sup> )	TYPE NUMBER
1	80	17.1	56	4800	CSH-E30/15/7-1S-10P

# E30/15/7

#### **MOUNTING PARTS**

#### General data and ordering information

ITEM	REMARKS	FIGURE	TYPE NUMBER
Clasp	CuZn alloy, Ni plated	4	CLA-E30/15/7
Spring	stainless steel (CrNi)	5	SPR-E30/15/7



#### DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

#### DISCLAIMER

**Life support applications** — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

#### **PRODUCT STATUS DEFINITIONS**

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are <b>not</b> recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Ferrite Cable Cores category:

Click to view products by Ferroxcube manufacturer:

Other Similar products are found below :

2643626102 FX28R0984-0 FX28R0984-2 AB 3X2X3SM 2643164251 2643665709 2661626402 LB 2.8X4.5U 28R1127 28R1260 28R1575 SM28R0760 SM28R1531 2631006302 2643165451 2643178351 28R0760 MS 21X14X4.5 W SM28B1101 SS7X4X3W 4327 030 16141 ASSE017-2 2643103102 2643164151 2943666671 4327 030 12611 2643163851 AB4X2X6SM 432703013631 LB4X2X8U 28B1101 28B0785 SM28R1575 SM28R1260 74270051 2643625902 74278032 2643480009 2673069901 HFB123049-300 HFB143064-100 HFB143064-300 HFB170070-000 ETD29/16/10-3C94 ETD29-3F3 ETD39-3C94 RFP1-20-10-A5 RFP1-40-28-M-A5 RFP2-10-10-A5 RFP2-25-12-A5