

INVENTEC

500 Main Street, Suite 18 PO Box 989 Deep River, CT 06417 USA

Toll Free: 800.435.0317 Phone: 860.526.8300 Fax: 860.526.8243 www.amtechsolder.com

NC-31, No-Clean Solder Paste

Product Data Sheet

Product Highlights

- ROL0 flux classification
- Designed for low temperature applications
- Exceptional print definition
- Excellent wetting on all common finishes including Ni/Au
- REACH compliant

Tost Results

Print & Dispense grade solder paste available.

Available Alloys

Alloy	Temp °C	Temp °F
42Sn/58Bi	138	280
42Sn/57Bi/1Ag	138	280
43Sn/43Pb/14Bi	144-163	291-325

Packaging

500 gram jars 500 gram cartridges 35 or 100 gram syringes ProFlow cassettes

Test Results		
Test J-STD-004 or other requirements (as stated)	Test Requirement	Result
Copper Mirror	IPC-TM-650: 2.3.32	L: No breakthrough
Corrosion	IPC-TM-650: 2.6.15	L: No corrosion
Quantitative Halides	IPC-TM-650: 2.3.28.1	L: <0.5%
Electrochemical Migration	IPC-TM-650: 2.6.14.1	L: <1 decade drop (no-clean)
Surface Insulation Resistance 85 °C, 85% RH@ 168 Hours	IPC-TM-650: 2.6.3.7	L: ≥100 MΩ (no-clean)
Tack Value	IPC-TM-650: 2.4.44	48g
Viscosity - Malcom @ 10 RPM/25 °C (x10³mPa/s)- 42Sn/58Bi T3/T4	IPC-TM-650: 2.4.34.4	Print: 125-180 Dispensing: 90-130
Visual	IPC-TM-650: 3.4.2.5	Clear and free from precipitation
Conflict Minerals Compliance	Electronic Industry Citizenship Coalition (EICC)	Compliant
REACH Compliance	Articles 33 and 67 of Regulation (EC) No 1907/2006	Contains no substance >0.1% w/w that is listed as a SVHC or restricted for use in solder materials

NC-31, No-Clean Solder Paste

Printer Operation

The following are general guidelines for stencil printer optimization with NC-31. Some adjustments may be necessary based on your process requirements.

Print Speed: 25-125 mm/sec Squeegee Pressure: 70-250g/cm of blade Under Stencil Wipe: Once every 10-25 prints, or as necessary

Stencil Life

- > 12 hours @ 30-45% RH and 20-25 °C
- ~ 4 hours @ 45-75% RH and 20-25 °C

Cleaning

NC-31 is a no-clean solder paste that does not require cleaning for most SMT assemblies. For applications requiring cleaning, NC-31 can be cleaned using flux residue removers such as Inventec Disper 607 and Disper 610.

Amtech Low Oxide Powder Distribution

Micron Size	Туре	Pitch Requirements
45-75µ	Type-2	24 mil and above
25-45µ	Туре-3	16-24 mil
20-38µ	Type-4	12-16 mil
15-25µ	Type-5	8-12 mil
5-15µ	Туре-6	5-8 mil
2-11µ	Type-7	< 5 mil


Note: Type-6 and Type-7 may not be available in certain alloys. Other powder distributions are available on request.

Storage

Solder paste should be stored between 3-8 °C (37-46 °F) to obtain the maximum refrigerated shelf life of six months. Unopened solder paste stored at room temperature, 25 °C (77 °F) will have a one month shelf life. Syringes and cartridges should be stored vertically in the refrigerator with the dispensing tip down. Allow 4-8 hours for solder paste to reach an operating temperature of 20-25 °C (68-77 °F). Keep the solder paste container sealed while warming the solder paste to operating temperature. **NEVER FREEZE SOLDER PASTE**.

Recommended Profile

This profile is designed to serve as a starting point for process optimization using NC-31. To achieve better results with voiding or to reduce tombstoning, consider using a longer soaking zone, (90-130 °C) for 60-90 seconds, with a rapid pre-heat stage. If there is evidence of solder de-wetting, consider lowering the peak reflow temperature, or reduce the time above liquidus to <60 seconds.



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Solder category:

Click to view products by Amtech manufacturer:

Other Similar products are found below :

91362-6 24-6040-0007 24-7150-8800 24-9574-7619 24-4060-2437 14-6040-0125 04-0595-0000 9SN-310G 5901004 5901006 8001111 ECC179707EU SMDLTLFP250T5 41-096-0201N 41-096-0242N ART.AGT-030 8001263 8001265 389289 54068 0008752 04-6040-0050 580140 H560103-BULK H560106-BULK TDS12AS 5601380 BON-102 BON-102F BON-102K BON-102S BR-102F 560017A 560048 560051 560069W-LF 5601034 5601053 5601056 5601058 5601157 5601161 5601170 8001092 5601213 5601243 0401-08-000179 5601247 0401-08-000183 5601277 JD927 JD927-10