

707 Full Plastic Tweezers



Fine tips

A 4 1/2" 115 mm

B 0.02" 0.5 mm

C 0.045" 1.2 mm



707.CF

Fine tips; black ESD Carbofib (CF)

General notes

- **PA66/CF30** polyamide 66 reinforced with 30 wt% carbon fibre
- heat stabilized
- very high rigidity, excellent tensile and flexural strength, fatigue and creep resistance
- low friction, self lubricating properties, excellent wear and abrasion resistance
- good heat capability
- good chemical resistance (oils, grease, fuels, non polar solvents); not resistant to strong acids,

alkalis and hot water or steam

- ESD safe material, (avoid powder attraction, sparks generation, ignition sources).
- very low coefficient of linear thermal expansion
- typical applications include handling of sensitive components and devices (electronic components, micro-mechanical parts, glass and ceramic substrates, capillary, etc.)

Mechanical properties

Flexural modulus +23°C:	17000 MPa	ASTM D 790
Flexural modulus +60°C:	12000 MPa	ASTM D 790
Flexural modulus +90°C:	9800 MPa	ASTM D 790
Flexural modulus +120°C	8000 MPa	ASTM D 790
Tensile strength +23°C	210 MPa	ISO 527
Tensile strength +60°C	159 MPa	ISO 527
Tensile strength +90°C	134 MPa	ISO 527
Tensile strength +120°C	117 MPa	ISO 527
Rockwell hardness M:	>100	ASTM D 785
Izod-Impact strength (notched) +23°C	70 J/m	ASTM D 785
Charpy-Impact strength (unnotched)	30 kJ/m ²	DIN 53453

Thermal properties

Temp. of defl. under load (1.80 MPa):	256°C	ASTM D648
Temp. of defl. under load (0.45 MPa):	260°C	ASTM D648
Vicat softening temperature (50°C/h 50N)	254°C	ISO 306
Coef. of lin.therm expansion, normal:	2.80 E-5/°C	ASTM D 696
Continuous Use Temperature	130°C	20'000 h
Short Time Temperature	190°C	

Electrical properties

Surface resistivity	10 ² Ohm	100V
Comparative tracking index:	<100 Volts	IEC 112
Decay time:	< 0.1 sec	1000-10 V

Other properties

Density	1.28 g/ccm	ISO 1183
Water absorption in water 23°C (24h)	0.60%	ISO 62

© IDEAL-TEK SA

Credits

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [AntiStatic Control Products](#) category:

Click to view products by [Ideal-Tek](#) manufacturer:

Other Similar products are found below :

[13505](#) [13870](#) [14404](#) [20-053-0017](#) [2229](#) [2231](#) [3039](#) [37061](#) [39792](#) [42470](#) [XON-ASB4X30](#) [XON-ASB4X6](#) [XON-ASB6X30](#) [09813](#) [09857](#)
[XON-ASB8X10](#) [XON-ASB6X10](#) [19695](#) [09037](#) [68101](#) [68103](#) [73741](#) [13515](#) [13869](#) [13868](#) [13485](#) [13457](#) [13245](#) [13332](#) [13205](#) [13135](#) [91070](#)
[8031](#) [8523](#) [13080](#) [13215](#) [157](#) [ROLL BEIGE 1.0](#) [VERAX1R-300R](#) [17260](#) [66051](#) [12550](#) [19863](#) [09121](#) [73831](#) [13340](#) [13338](#) [04541](#) [19696](#)
[16104](#) [SPI-20686](#)