



## **SPECIFICATION**

- Supplier : Samsung electro-mechanics
- Product : Multi-layer Ceramic Capacitor

- Samsung P/N : CL21C471JBANNND
- Description : CAP, 470pF, 50V, ±5%, C0G, 0805

A. Samsung Part Number

			<u>CL</u> ①	<mark>21</mark> ②	<u>C</u> 3	<u>471</u> ④	<u>J</u> 5	<u>B</u> 6	<u>А</u> ⑦	<u>N</u> 8	<u>N</u> 9	<u>N</u> 10	<u>D</u> 11			
1	Series	Samsung I	Multi-la	yer Ce	erami	c Capa	citor									٦
2	Size	0805 (	(inch co	de)		L: :	2.0	± 0.1		mm		W:	1.25	± 0.1	mm	
3	Dielectric	C0G					8	Inne	r ele	ctrod	le		Ni			
4	Capacitance	470 g	ъF					Term	ninat	tion			Cu			
5	Capacitance	±5 9	%					Plati	ng				Sn 100	)%	(Pb Free)	
	tolerance						9	Prod	luct				Norma	l		
6	Rated Voltage	50 \	V				10	Spec	cial				Reserv	ved for	future use	
$\bigcirc$	Thickness	0.65 ±	± 0.1	mm			1	Pack	cagir	ng			Cardbo	bard Ty	/pe, 13" reel	

## B. Samsung Reliablility Test and Judgement condition

	Performance	Test condition						
Capacitance	Within specified tolerance	1Mt±10% 0.5~5Vrms						
Q	1000 min							
Insulation	10,000Mohm or 500Mohm · <i>μ</i> F	Rated Voltage 60~120 sec.						
Resistance	Whichever is Smaller							
Appearance	No abnormal exterior appearance	Microscope (×10)						
Withstanding	No dielectric breakdown or	300% of the rated voltage						
Voltage	mechanical breakdown							
Temperature	COG							
Characterisitcs	(From -55 ℃ to 125 ℃, Capacitance change shoud be within ±30PPM/℃)							
Adhesive Strength	No peeling shall be occur on the	500g·F, for 10±1 sec.						
of Termination	terminal electrode							
Bending Strength	Capacitance change :	Bending to the limit (1mm)						
	within $\pm 5\%$ or $\pm 0.5$ pF whichever is larger	with 1.0mm/sec.						
Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder						
	is to be soldered newly	245±5℃, 3±0.3sec.						
		(preheating : 80~120℃ for 10~30sec.)						
Resistance to	Capacitance change :	Solder pot : 270±5°C, 10±1sec.						
Soldering heat	within $\pm 2.5\%$ or $\pm 0.25$ pF whichever is larger							
	Tan δ, IR : initial spec.							

	Performance	Test condition					
Vibration Test	Capacitance change :	Amplitude : 1.5mm					
	within ±2.5% or ±0.25pF whichever is larger	From 10Hz to 55Hz (return : 1min.)					
	Tan δ, IR : initial spec.	2hours $\times$ 3 direction (x, y, z)					
Moisture	Capacitance change :	With rated voltage					
Resistance	within $\pm 7.5\%$ or $\pm 0.75$ pF whichever is larger	40±2℃, 90~95%RH, 500+12/-0hrs					
	Q : 200 min						
	IR : 500Mohm or 25Mohm $\cdot \mu F$						
	Whichever is Smaller						
High Temperature	Capacitance change :	With 200% of the rated voltage					
Resistance	within $\pm 3\%$ or $\pm 0.3$ pF whichever is larger	Max. operating temperature					
	Q : 350 min	1000+48/-0hrs					
	IR : 1000Mohm or 50Mohm · μF						
	Whichever is Smaller						
Temperature	Capacitance change :	1 cycle condition					
Cycling	within $\pm 2.5\%$ or $\pm 0.25$ pF whichever is larger	Min. operating temperature $\rightarrow$ 25 °C					
	Tan δ, IR : initial spec.	$\rightarrow$ Max. operating temperature $\rightarrow$ 25 °C					
		5 cycle test					

## C. Recommended Soldering method :

Reflow ( Reflow Peak Temperature : 260+0/-5 °C, 10sec. Max )

\* For the more detail Specification, Please refer to the Samsung MLCC catalogue.

## **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Multilayer Ceramic Capacitors MLCC - Leaded category:

Click to view products by Samsung manufacturer:

Other Similar products are found below :

010-007220-002REV A M39014/01-1210V M39014/01-1281V M39014/01-1335V M39014/01-1571V M39014/01-1578V M39014/01-1593 M39014/02-1265V M39014/02-1347 M39014/02-1350 M39014/02-1356VTR1 M39014/22-0167 M39014/22-0734 87043-49 Q52-DK AR215F103K4RTR2-3323 C0603C309C5GACTU-CUT-TAPE C410C221K1G5TATR C420C102J1G5TATR C430C104M1U5TATR SL155C222MAB FK26X7R2E104KN006 CCR06CG183GRV CFB1/2C101J CFB1/2C102J CN20C102K M39014/01-1317 M39014/01-1572V M39014/01-1594V M39014/02-1236 M39014/02-1321V M39014/02-1345V M39014/22-0351 M39014/22-0695 M39014/220767 M39014/220788 M39014/22-1005 MA405E334MAA MD015A103KAB SL301E105MAB CCR05CG242FRV KTD101B684M32A0B00 CCR07CG473KR CCR05CG820JP TKC-TMC1206-05-1501-J?? TKC-TMC1206-05-1801-J TKC-TMC1206-05-20R0-F TKC-TMC1206-05-3901-J TKC-TMC1206-05-44R2-F TKC-TMC1206-05-4703-J??