
X8R/X8L Dielectric








AVX has developed a range of multilayer ceramic capacitors designed for use in applications up to 150°C. These capacitors are manufactured with an X8R and an X8L dielectric material. X8R material has capacitance variation of $\pm 15\%$ between -55°C and +150°C. The X8L material has capacitance variation of $\pm 15\%$ between -55°C to 125°C and +15/-40% from +125°C to +150°C.

The need for X8R and X8L performance has been driven by customer requirements for parts that operate at elevated temperatures. They provide a highly reliable capacitor with low loss and stable capacitance over temperature.

They are ideal for automotive under the hood sensors, and various industrial applications. Typical industrial application would be drilling monitoring system. They can also be used as bulk capacitors for high temperature camera modules.

Both X8R and X8L dielectric capacitors are automotive AEC-Q200 qualified. Optional termination systems, tin, FLEXITERM® and conductive epoxy for hybrid applications are available. Providing this series with our FLEXITERM® termination system provides further advantage to customers by way of enhanced resistance to both, temperature cycling and mechanical damage.

PART NUMBER (see page 2 for complete part number explanation)



NOTE: Contact factory for availability of Termination and Tolerance Options for Specific Part Numbers.

X8R X8L

	SIZE		0603		0805		1206		SIZE		0603		0805		1206				
	WVDC	25V	50V	25V	50V	25V	50V		WVDC	25V	50V	100V	25V	50V	100V	16V	25V	50V	100
331	Cap 330	G	G	J	J			331	Cap 330		G	G		J	J				
471	(pF) 470	G	G	J	J			471	(pF) 470		G	G		J	J				
681	680	G	G	J	J			681	680		G	G		J	J				
102	1000	G	G	J	J	J	J	102	1000		G	G		J	J				
152	1500	G	G	J	J	J	J	152	1500		G	G		J	J			J	J
222	2200	G	G	J	J	J	J	222	2200		G	G		J	J			J	J
332	3300	G	G	J	J	J	J	332	3300		G	G		J	J			J	J
472	4700	G	G	J	J	J	J	472	4700		G	G		J	J			J	J
682	6800	G	G	J	J	J	J	682	6800		G	G		J	J			J	J
103	Cap 0.01	G	G	J	J	J	J	103	Cap 0.01		G	G		J	J			J	J
153	(μF) 0.015	G	G	J	J	J	J	153	(μF) 0.015	G	G		J	J	J			J	J
223	0.022	G	G	J	J	J	J	223	0.022	G	G		J	J	J			J	J
333	0.033	G	G	J	J	J	J	333	0.033	G	G		J	J	N			J	J
473	0.047	G	G	J	J	J	J	473	0.047	G	G		J	J	N			J	J
683	0.068	G		N	N	M	M	683	0.068	G	G		J	J				J	J
104	0.1			N	N	M	M	104	0.1	G	G		J	J				J	M
154	0.15			N	N	М	M	154	0.15				J	N		J	J	J	Q
224	0.22			N		M	M	224	0.22				N	N		J	J	J	Q
334	0.33					M	M	334	0.33				N			J	М	Р	Q
474	0.47					M		474	0.47				N			М	M	Р	
684	0.68							684	0.68							M			
105	1							105	1							М			
	WVDC	25V	50V	25V	50V	25V	50V		WVDC	25V	50V	100V	25V	50V	100V	16V	25V	50V	100
	SIZE	06	603	08	805	1206		SIZE		0603		0805		1206					

Letter	Α	С	Е	G	J	K	М	N	Р	Q	Х	Υ	Z
Max.	0.33	0.56	0.71	0.90	0.94	1.02	1.27	1.40	1.52	1.78	2.29	2.54	2.79
Thickness	(0.013)	(0.022)	(0.028)	(0.035)	(0.037)	(0.040)	(0.050)	(0.055)	(0.060)	(0.070)	(0.090)	(0.100)	(0.110)
	PAPER					EMBOSSED							

= AEC-Q200 Qualified



X8R/X8L Dielectric


General Specifications



APPLICATIONS FOR X8R AND X8L CAPACITORS

- All market sectors with a 150°C requirement
- Automotive on engine applications
- Oil exploration applications
- Hybrid automotive applications
 - Battery control
 - Inverter / converter circuits
 - Motor control applications
 - Water pump
- Hybrid commercial applications
 - Emergency circuits
 - Sensors
 - Temperature regulation






ADVANTAGES OF X8R AND X8L MLC CAPACITORS

- Both ranges are qualified to the highest automotive AEC-Q200 standards
- Excellent reliability compared to other capacitor technologies
- RoHS compliant
- Low ESR / ESL compared to other technologies
- Tin solder finish
- FLEXITERM® available
- Epoxy termination for hybrid available
- 100V range available

ENGINEERING TOOLS FOR HIGH VOLTAGE MLC CAPACITORS

- Samples
- Technical Articles
- Application Engineering
- Application Support





X8R/X8L Dielectric



Specifications and Test Methods

Parame		X8R/X8L Specification Limits	Measuring Conditions				
Operating Temp		-55°C to +150°C	Temperature Cycle Chamber				
Capac	itance	Within specified tolerance	Freq.: 1.0 kHz ± 10%				
Dissipation	on Factor	≤ 2.5% for ≥ 50V DC rating ≤ 3.5% for 25V DC and 16V DC rating	Vrms ± .2V				
Insulation I	Resistance	100,000ΜΩ or 1000ΜΩ - μ F, whichever is less	Charge device with rated voltage for 120 ± 5 secs @ room temp/humidity				
Dielectric	Strength	No breakdown or visual defects	Charge device with 300% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max) Note: Charge device with 150% of rated voltage for 500V devices.				
	Appearance	No defects	Deflection: 2mm				
Resistance to	Capacitance Variation	≤ ±12%	Test Time: 30 seconds				
Flexure Stresses	Dissipation Factor	Meets Initial Values (As Above)	V 1mm/sec				
Ollesses	Insulation Resistance	≥ Initial Value x 0.3	90 mm				
Solder	rability	≥ 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 ± 5°C for 5.0 ± 0.5 seconds				
	Appearance	No defects, <25% leaching of either end terminal					
	Capacitance Variation	≤ ±7.5%					
Resistance to	Dissipation Factor	Meets Initial Values (As Above)	Dip device in eutectic seconds. Store at room	temperature for 24 ± 2			
Solder Heat	Insulation Resistance	Meets Initial Values (As Above)	hours before measuring electrical				
	Dielectric	Meets Initial Values (As Above)					
	Strength Appearance	No visual defects	Step 1: -55°C ± 2°	30 ± 3 minutes			
	Capacitance	≤ ±7.5%	Step 2: Room Temp	≤ 3 minutes			
		S ±1.570	Step 2. Noom lemp 5 3 minutes				
Thermal Shock	Dissipation Factor	Meets Initial Values (As Above)	Step 3: +125°C ± 2°	30 ± 3 minutes			
Gilook	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	≤ 3 minutes			
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 ± 2 hours at room temperature				
	Appearance	No visual defects					
	Capacitance Variation	≤ ±12.5%	Charge device with 1.5 rated voltage (≤ 10V) in test chamber set at 150°C ± 2°C				
Load Life	Dissipation Factor	≤ Initial Value x 2.0 (See Above)	for 1000 hou	urs (+48, -0)			
	Insulation Resistance	≥ Initial Value x 0.3 (See Above)	Remove from test ch at room temperatu				
	Dielectric Strength	Meets Initial Values (As Above)	before measuring.				
	Appearance	No visual defects	Ctoro in a test share-	or oot at 0E00 : 000/			
	Capacitance Variation	≤ ±12.5%	85% ± 5% relative hu	Store in a test chamber set at $85^{\circ}\text{C} \pm 2^{\circ}\text{C}/85\% \pm 5\%$ relative humidity for 1000 hours			
Load Humidity	Dissipation Factor	≤ Initial Value x 2.0 (See Above)	(+48, -0) with rate				
	Insulation Resistance	≥ Initial Value x 0.3 (See Above)	Remove from chamber and stabilize at room temperature and humidity for				
	Dielectric Strength	Meets Initial Values (As Above)	24 ± 2 hours be	Tore measuring.			



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for avx manufacturer:

Other Similar products are found below:

MD015A222JAB M39014/220755 VE17M02750K-- SM037C305KAN360 SV097C105MAA CH541C156KA80A0

CX2016DB16000D0GPSC1 AOL-1502-02 LIFE_SAMP-1A139-159V001 88011-154 RF CWR09HC106KBA 00-8129-015-610-108

SK071E276ZAA PBRC7.37MR50X000 M39014/22-1137-TUBE 3640CC224KAT6A M39014/220194 MD015C273KAB M39014/220458

105061100000861+ CDR12BP102AKUM CDR12BP330AJUR\M500 18123A104FAT2A CDR12BP221AJUR\M500 00 6224020001800

LD12CC104KAB1A L08052R2DEWTR CR21-10R0F-T 009286001203906 M39014/22-1181 F931A227KNC F931C227MNC

FFLI6B3007KJE 12102U101JAT2A KIT5000UZ KITTYPE1400 LF LD065A332FAB2A SA205C393JAA 308016056000413

SK052C105KAA SR211A151FAA F931A226MBA FFB24I0755K-- CK06BX472K M39014/05-2731 M39014/220476

CWR29JC476KCHC TAJB225M035R TAJC107K006RNJ TAJD226K035RNJV