

ANSI/ESD S20.20 requires that all nonessential insulators, such as those made of plastics and paper, must be removed from the workstation. Substituting ESD tape for regular tape (a very high tribocharging insulator) protects your ESD susceptible products.

# **Use and Storage:**

Users shall determine the suitability of the product for its intended use. For best results, tape inventory should be continually replenished. It is recommended that rolls of tape be stored flat and rotated (flipped over to the other side) periodically. Tapes should be stored in a dry, well ventilated room with a reasonably consistent temperature of 68°F (20°C) and be protected from exposure to direct sunlight. Tape should not be stored in ultraviolet sunlight, moisture, or heat. Tape over one year old should be evaluated by the user to determine acceptability for the user's application. Desco Industries, Inc. recommends those tracking useful life of product to use shipping/invoice date as Desco Industries, Inc. expressly warrants that for a period of one (1) year from the date of purchase, our Wescorp Brand ESD Tape will be free of defects in material (parts) and workmanship (labor). See details of Limited Warranty online at Desco.com/Warranty.aspx

If not otherwise noted tolerance +/- 10%.
\*Wescorp is a Desco Industries brand.
Note: Tape rolls may vary slightly in color

### **Electrical Properties:**

- Both surfaces low-tribocharging at 50% RH
- Conductive grid layer 1 x 10<sup>4</sup> to < 1 x 10<sup>6</sup> ohms at 50% RH
- Adhesive copolymer resistivity 1 x 10<sup>9</sup> ohms (nominal) acrylic based adhesive
- Copolymer layer 8 x 10<sup>12</sup> ohms (nominal)

# **Physical Properties:**

- 1.9 mil (0.0019"), (0.049 mm) total thickness
- No silicone (adhesive, film backing, release material)
- Max Temperature 60°C (140°F)
- Non-corrosive

Property	Test Method	Value	
Tensile Strength - Longitudinal	ASTM D 882	160 N/mm sq.	
Tensile Strength - Transverse	ASTM D 882	270 N/mm sq.	
Elongation - Longitudinal	ASTM D 882	160%	
Elongation - Transverse	ASTM D 882	50%	
Static Decay Time	FTMS 101B, M4046	0.5 sec.	
Base Film Thickness		30 micron	
Peeling Force		12 N	
Cohesion Force	LCTS-T2-4	12 hrs	
Adhesion to Steel	LCTS-T3-4	0.300 kg/25mm min.	

#### Width - See Metric Note

Tape	0.5"	.75"	1"	2"	Core	Length
Conductive Shielding Grid	<u>81250</u>	<u>81251</u>	<u>81252</u>	<u>81253</u>	3"	118 ft.

Tape widths are nominal metric  $\pm 0.8$  mm ( $\pm 1/32$ ").

1/2" is 12 mm nominal or 0.472" 3/4" is 18 mm nominal or 0.709" 1" is 24 mm nominal or 0.945"

2" is 48 mm nominal or 1.890"

RoHS 2, REACH and Conflict Mineral Statement None of the RoHS 2 restricted materials or REACH substances of very high concern as of 2014/06/16, or Conflict Minerals are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See Desco Limited Warranty at Desco.com.

Specifications and procedures subject to change without notice.

Made in Malaysia



# WESCORP\* ESD CONDUCTIVE SHIELDING GRID TAPE, PAPER CORE

**DESCO WEST:** 3651 WALNUT AVE., CHINO, CA 91710 **PHONE**: (909) 627-8178 **WEB SITE**: <u>Desco.com</u>

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407

PHONE: (781) 821-8370 WEB SITE: Desco.com

DRAWING NUMBER: 81250 **DATE:** February 2015

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Adhesive Tapes category:

Click to view products by Desco manufacturer:

Other Similar products are found below:

PF24.0W 4718 4516-1/4x36 56-YELLOW-34"X72YD 00-021200-13972-7 021200-64630 60 TAPE (1") 62-GRAY-12"X36YD 62-GRAY-12"X36YD 69-1"X36YD 764-1"x36yd-Red 764-1"x36yd-White PG ASSY 926-1/4X18YD 967454-1 1194-14"X36YD 1181 19MM X 16,5 METERS 1182-7.7X10 1245-34"X18YD 1267 130C-1X15FT 130-1x10FT 1345-3/8x18yrd 1380-2"X8" E39-RS1-CA 1900-48mm 22-1/2X36YD 2229-P-2-1/2x3-3/4 88-SUPER-34X44FT 890103N001 2670 SJ3527N-Black-1.5"x50yd EVK-TA-TM047NBH01 AD-UCUSB-DCAUD-SPL 20-1"X60YDS 2020-18mmx55m H150 3900-Blue 3939-24mmx55m 396-1"x36yd 4016-34"x36yd 4462W-12"x72yd 44-TAN-14"X90YD 4504-34x18 471-Trans-1"x36yd-Bulk 5414 34X36 C-22 35-Gray-1/2 371-Tan-48mmx50m 4008-12"X36YD