Encapsulation Resins

Technical Data Sheet



Page 1

ER2218 Epoxy Resin

ER2218 is a low viscosity, flame retardant, two part potting and encapsulating compound. The product has been specifically designed for compatibility with reflow applications, therefore remaining stable for short term, high temperature excursions.

- Exceptionally low viscosity; ideal for applications with complex geometries or limited spacing
- Combines flame retardancy with ease of application; efficient potting processes
- Excellent thermal stability; can withstand short term excursions at high temperatures
- Does not contain abrasive fillers; low wear on dispensing machinery

Approvals	RoHS-2 Compliant (2011/65/EU):	Yes
	UL Approval:	Meets UL94 V-0

Typical Properties		
Liquid Properties:	Base Material Density Part A - Resin (g/ml) Density Part B - Hardener (g/ml) Part A Viscosity (mPa s @ 20-23°C) Part B Viscosity (mPa s @ 20-23°C) Mixed System Viscosity (mPa s @ 20-23°C) Mix Ratio (Weight) Mix Ratio (Volume) Usable Life (20°C) Gel Time (23°C)	Epoxy 1.22 0.96 800 400 500 3.58:1 2.82:1 40 minutes 50 minutes
	Cure Time (23°C) Cure Time (60 °C) Cure Time (100 °C) Colour Part A – Resin Colour Part B – Hardener Storage Conditions Shelf Life Exotherm (Measured on 100ml sample; cylinder of diameter 49.4mm @ 23°C) Shrinkage	24 hours 4 hours 30 minutes Black Amber Dry Conditions: Above 15°C, Below 30°C 24 Months (bulk) 18 months (resin pack) < 90°C < 1%

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way, Ashby de la Zouch, Leicestershire LE65 1JR T+44 (0)1530 419 600 F+44 (0)1530 416 640 BS EN ISO 9001:2008 Certificate No. FM 32082



Page 2

Cured System: Thermal conductivity (W/m.K) 0.28

Cured Density (g/ml) 1.16

Temperature Range (°C) -50 to +150

Max Temperature Range (Short Term (°C)/5 Mins)
(Application and Geometry Dependent)
Dielectric Strength (kV/mm)
Volume Resistivity (ohm-cm)
Shore Hardness
Colour (Mixed System)

+ 245
10
10
10
10
14
Black

Flame Retardancy Yes
Coefficient of thermal expansion (ppm/°C) 80-100


Water Absorption (9.7mm thick disk, 51mm diameter) < 1.5% / < 0.5%

10 days @ 20°C / 1 hour @ 100°C

Mixing Procedures


Resin Packs

When in Resin pack form, the resin and hardener are mixed by removing the clip and moving the contents around inside the pack until thoroughly mixed. To remove the clip, remove both end caps, grip each end of the pack and pull apart gently. By using the removed clip, take special care to push unmixed material from the corners of the pack. Mixing normally takes from two to four minutes depending on the skill of the operator and the size of the pack. Both the resin and hardener are evacuated prior to packing so the system is ready for use immediately after mixing. The corner may be cut from the pack so that it may be used as a simple dispenser.














Bulk Mixing

When mixing, care must be taken to avoid the introduction of excessive amounts of air. Automatic mixing equipment is available which will not only mix both the resin and hardener accurately in the correct ratio but do this without introducing air. Containers of Part A (Resin) and Part B (Hardener) should be kept sealed at all times when not in use to prevent the ingress of moisture. Bulk material must be thoroughly mixed before use. Incomplete mixing will result in erratic or partial curing.

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way, Ashby de la Zouch, Leicestershire LE65 1JR T +44 (0)1530 419 600 F +44 (0)1530 416 640 BS EN ISO 9001:2008 Certificate No. FM 32082





Page 3

General

Sedimentation of the resin has been minimised by careful attention to the formulation. However, any sediment which may have occurred over long periods of time must be dispersed before removing any material from the container. This dispersion can be carried out (if necessary) by stirring with a broad bladed spatula or gently rolling the can. Take care not to introduce excessive amounts of air during this operation or it may be necessary to re-evacuate the resin. Sedimentation will be accelerated by storage at high temperatures. Sedimentation found in resin packs forms no problem since the sediment is re-mixed when the pack is used.

Additional Information

Cleaning: It is far easier for machines & containers to be cleaned before the resin has been allowed

to cure. Electrolube's RRS is suitable for cleaning machines and containers and cured

resin may be slowly softened and removed by soaking in our RRS.

Curing: Do not heat cure large volumes immediately. Allow these to gel at room temperature and

post-cure at high temperature if required (refer to liquid properties for details). Small

volumes (250ml) may be heat cured immediately.

Storage: When storing under very cold conditions, the hardener may crystallise. If this occurs,

simply warm (40°C) the container gently until all crystals have re-melted.

Health & Safety: Always refer to the Health & Safety data sheet before use. These can be downloaded

from www.electrolube.com

Revision 2: Jan 2014

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for electrolube manufacturer:

Other Similar products are found below:

TCRGUNB ER2220RP250G GP300S GP500S HTCX35SL EAD200D PRS400D TPM350 SCP26G 2K300KIT DCT01L SWAJ05L

ARW300 DCE0.75L GP300SL SSS500ML SYR20ML GP500SL ER2218RP250G ER2224 UR5638 CCRG01L SPG900G DEI05L

ER221935SL HTS100T ASA250ML HTC700G ULL200D EADI200D AFAG35SL ECW025 EADPI200 HTSP100T CMO200D FSC05L

HTC100T OSL400 SYR02ML URC200D ER2223 RST250 SOB200D UR5118RP250G UR5528RP250G DDF400 ML NSCP400H

AFC400D/12 SYR10ML DCA01L