

Tgard™ 3000 Series Thermally Conductive Insulators



HIGH PERFORMANCE THERMAL INTERFACE PRODUCTS

Tgard™ 3000 is specifically designed to solve overheating issues such as lower component efficiency, premature component failures, size limitations and other performance problems for today's power component assemblies. The need to remove unwanted heat to ambient temperatures becomes more important as electronic systems pack more power into smaller spaces.

Tgard 3000 is a film-based product that is designed to resist cut through in screw mounting applications while providing a more consistent breakdown voltage over other insulator constructions. The soft conformal coating on the film core provides an excellent mating surface for low pressure clip mounting applications.

PERFORMANCE CAPABILITIES

- High dielectric breakdown of 6,000 volts
- · Film base resistant to cut through
- Thermal resistance of 0.55°C-in2/watt @ 50 psi pressure
- Thermal resistance of 0.37°C-in2/watt @ 400 psi pressure

FEATURES AND BENEFITS

- Designed for switch mode power supply applications
- · Reinforced with high temperature resistant film
- High voltage resistant film

APPLICATIONS

- Switching mode power supplies for:
 - Communications
 - Consumer electronics
 - Industrial
 - Instrumentation
 - Medical
- Electrial power generators
- UPS units

Americas: +1.847 839.6907 IAS-AmericasEastSales@lairdtech.com

Europe: +44.1628.858941
IAS-EUSales@lairdtech.com
Asia: ++86.21.5855.0827.127
IAS-AsiaSales@lairdtech.com
CLV-customerservice@lairdtech.com
www.lairdtech.com/thermal

Tgard™ 3000 Series Thermally Conductive Insulators

PROPERTIES	TEST M	TEST METHOD		METRIC VALUES		IMPERIAL VALUES		
ELECTRICAL PROPERTIES								
Dielectric withstand voltage 50mm probe for 30 sec	ASTM D149		4,500 volts DC		С	4,500 volts DC		
Dielectric breakdown voltage 50mm probe	ASTM D149		Avg >6,000 volts AC			Avg >6,000 volts AC		
Volume resistivity	ASTN	ASTN D257		² ohm-cr	n	10 ¹² ohm-in		
Dielectric constant @1Mhz	ASTN D257		3.3			3.3		
MECHANICAL PROPERTIES								
Thickness			0.13 mm			5 mils		
Hardness	ASTM D2240		80 Shore A			80 Shore A		
Tensile strength	ASTM	ASTM D412		3.4 Mpa		6.3 Kpsi		
Elongation along width or le	gth ASTM D412		35%			35%		
Operating temperature rang	nge		-60º to 180ºC			-76º to 356ºF		
Color			Brown			Brown		
UL flammability rating	UL	UL 94		V-0			V-0	
PRESSURE	UNITS	10 (69)	25 (172)	50 (345)	100 (689)	200 (1379)	400 (2758)	
TOTAL THERMAL RESISTANCE	E							
Modified ASTM D5470	ºC-in²/watt	0.86	0.68	0.55	0.44	0.40	0.37	
Modified ASTM D5470	ºC-cm²/watt	5.55	4.39	3.55	2.83	2.58	2.39	
T0-220	ºC/watt	1.36	1.08	0.91	0.83	0.78	0.74	
 Sheet form, roll form and die-cut parts Single-side, pressure-sensitive adhesive on request Without adhesive (A0): 12 x 18" sheets, 12" x 65M, 12" x 30M roll or custom configuration With adhesive (A1): 11.75 x 18" sheets, 11.75" x 30M roll or custom configuration 								
Standard die cut parts: Custom die cut parts:	Standard part sizes for TO-220, TO-247, TO-3P, TO-3PL and TO-264 Custom configurations available with standard tolerance of 0.5mm (0.020"). Ability to handle drawings in multiple file formats. (.DXF and .DWG preferred)							

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for laird connectivity manufacturer:

Other Similar products are found below:

29D3800-000 63202-501 8860-0062-324-72 A10095-02 A10237-21 A14564-01 A15344-01 A15372-01 DA-033-12-02-00-00 DVK-PRM120 ODH24-9-WB 9360002-301 A10093-37 A10874-01 A11809-02 A15796-26 A16367-04 CMQ69273-30NF 430701-501 430744-513 430848-509 DA-075-12-02-00-00 4106-.25 430140-502 430745-505 43280-503 DVK-RM191-SM-01 0650-00005 56460-501 POE-24IR 8861-0175-93 DVK-BL600-SC TPCM FSF-52 CRX150 CRX150B DVK-BT900-SA-03 B3003 PA24-19 POE-HP-24i PLC1666 Y80612 A17690-10 Y4065 387000840 A17653-12 YS1505 387000866 OD9-8 A17775-05 CW42S