# **DWFR TUBING**

Dual Wall, Heat Shrink Tubing Highly flame-retardant, UL VW-1 rated



DWFR tubing from TE Connectivity (TE) is a highly flame-retardant, high-shrink ratio, adhesive-lined tubing made from a polyolefin jacket with a thermoplastic adhesive inner wall. It insulates and environmentally seals and protects components and other electrical connections and terminations. DWFR's medium wall thickness provides increased mechanical protection. Its high shrink ratio allows DWFR to cover a variety of substrates with a limited number of tubing sizes. It is suitable for sealing and protection of connector-to-cable transitions and repairing damaged cable jackets. It can also be used to create and seal breakouts in harnesses.

### **KEY FEATURES**

- Highly flame-retardant with UL VW-1 flammability rating
- 3:1 and 4:1 shrink ratios provide design versatility
- Moisture-resistant seal
- Withstands mechanical stress for increased product reliability

### **APPLICATIONS**

- Household appliances
- Automotive
- Commercial electronics and communications
- Consumer products
- Industrial equipment

### MATERIALS

- Irradiated polyolefin jacket
- Thermoplastic adhesive inner wall

### ELECTRICAL

• Provides excellent electrical insulation

### MECHANICAL

- Medium wall jacket provides mechanical protection from abrasion and bending
- Adhesive liner bonds to a variety of substrate materials, providing protection from moisture ingress

### **TEMPERATURE RATING**

- Minimum shrink temperature: 60°C [140°F]
- Full recovery temperature: 110°C [256°F]
- Operating temperature: -40°C to 110°C [-40°F to 230°F]

### STANDARDS AND SPECIFICATIONS

- Customer drawing: DWFR
- UL 224 VW-1
- UL file E35586
- Submitted for CSA Certification

### ORDERING INFORMATION

- Color: Black (-0)
- Standard packaging (-STK): Cut pieces that are 1.2m [4ft] long Optional special order packaging (-SP): Spool, varying lengths (consult TE for details)
- Ordering description: Specify product name, size, color and packaging. For example, DWFR-3/1-0-STK



## **DWFR TUBING** Dual Wall, Highly Flame-Retardant Heat Shrink Tubing

### DIMENSIONS



| Shrink<br>Ratio | Size  | Minimum<br>Expanded I.D. (D) | Maximum<br>Recovered I.D. (d) | Total Recovered Wall<br>Thickness (W) | Minimum Recovered Inner<br>Meltable Wall Thickness (W1) |
|-----------------|-------|------------------------------|-------------------------------|---------------------------------------|---|
| 3:1             | 3/1   | 3.0 [0.118]                  | 1.0 [0.039]                   | 1.12 ± 0.25 [0.044 ± 0.010]           | 0.25 [0.010]  |
|                 | 6/2   | 6.0 [0.236]                  | 2.0 [0.079]                   | 1.14 ± 0.25 [0.045 ± 0.010]           | 0.25 [0.010]  |
|                 | 9/3   | 9.0 [0.354]                  | 3.0 [0.118]                   | 1.40 ± 0.25 [0.055 ± 0.010]           | 0.56 [0.022]  |
|                 | 12/4  | 12.0 [0.472]                 | 4.0 [0.157]                   | 1.78 ± 0.36 [0.070 ± 0.014]           | 0.58 [0.023]  |
|                 | 19/6  | 19.0 [0.748]                 | 6.0 [0.236]                   | 2.25 ± 0.50 [0.088 ± 0.020]           | 0.58 [0.023]  |
|                 | 24/8  | 24.0 [0.945]                 | 8.0 [0.315]                   | 2.54 ± 0.50 [0.100 ± 0.020]           | 0.79 [0.031]  |
|                 | 40/13 | 40.0 [1.575]                 | 13.0 [0.512]                  | 2.54 ± 0.50 [0.100 ± 0.020]           | 0.86 [0.034]  |
| 4:1             | 4/1   | 4.0 [0.157]                  | 1.0 [0.039]                   | 1.12 ± 0.25 [0.044 ± 0.010]           | 0.25 [0.010]  |
|                 | 8/2   | 8.0 [0.315]                  | 2.0 [0.079]                   | 1.14 ± 0.25 [0.045 ± 0.010]           | 0.25 [0.010]  |
|                 | 12/3  | 12.0 [0.472]                 | 3.0 [0.118]                   | 1.40 ± 0.25 [0.055 ± 0.010]           | 0.56 [0.022]  |
|                 | 16/4  | 16.0 [0.630]                 | 4.0 [0.157]                   | 1.78 ± 0.36 [0.070 ± 0.014]           | 0.58 [0.023]  |
|                 | 24/6  | 24.0 [0.945]                 | 6.0 [0.236]                   | 2.25 ± 0.50 [0.088 ± 0.020]           | 0.58 [0.023]  |
|                 | 32/8  | 32.0 [1.260]                 | 8.0 [0.315]                   | 2.54 ± 0.50 [0.100 ± 0.020]           | 0.79 [0.031]  |
|                 | 52/13 | 52.0 [2.047]                 | 13.0 [0.512]                  | 2.54 ± 0.50 [0.100 ± 0.020]           | 0.86 [0.034]  |

### PRODUCT DESCRIPTION AND ORDERING INFORMATION

| Shrink Ratio | Material Description | Material Number | Shrink Ratio | Material Description | Material Number |
|--------------|----------------------|-----------------|--------------|----------------------|-----------------|
| 3:1          | DWFR-3/1-0-STK       | EH2288-000      | 4:1          | DWFR-4/1-0-STK       | EH2295-000      |
|              | DWFR-6/2-0-STK       | EH2289-000      |              | DWFR-8/2-0-STK       | EH2296-000      |
|              | DWFR-9/3-0-STK       | EH2290-000      |              | DWFR-12/3-0-STK      | EH2297-000      |
|              | DWFR-12/4-0-STK      | EH2291-000      |              | DWFR-16/4-0-STK      | EH2298-000      |
|              | DWFR-19/6-0-STK      | EH2292-000      |              | DWFR-24/6-0-STK      | EH2299-000      |
|              | DWFR-24/8-0-STK      | EH2293-000      |              | DWFR-32/8-0-STK      | EH2300-000      |
|              | DWFR-40/13-0-STK     | EH2294-000      |              | DWFR-52/13-0-STK     | EH2301-000      |

### <u>DWFR-3/1-0-STK</u>



### PROPERTY REQUIREMENTS

| Property  | Unit                 | Requirement                                    | Test Method              |
|---|----------------------|--|--------------------------|
| Physical  | ·                    |  |                          |
| Dimensions*   | mm [in]              | As shown in DIMENSIONS table                   | ASTM D 2671              |
| Longitudinal Change   | Percent              | O, -15%  | ASTM D 2671              |
| Tensile Strength*   | psi (MPa)            | 1500 (10.3) minimum                            | ASTM D 2671              |
| Ultimate Elongation*  | Percent              | 200 minimum                                    | ASTM D 2671              |
| Secant Modulus (Expanded)   | psi (MPa)            | 2.5 x 104 (172) maximum                        | ASTM D 882, 2% strain    |
| Cold Bend Test<br>at -30 ± 1°C (-22 ± 1.8°F) for 1 hour   | -                    | No cracking                                    | UL 224, section 5.9      |
| Heat Shock*<br>4 hours at 250 ± 1°C (482 ± 1.8°F)   | -                    | No dripping. flowing or cracking of outer wall | UL 224, section 5.8      |
| Heat Resistance<br>168 hours at 158 ± 2°C (347 ± 4°F)<br>followed by test for<br>Tensile strength<br>Elongation | psi (MPa)<br>Percent | 70% of original minimum<br>100% minimum        | UL 224                   |
| Sealing Efficiency  | -                    | No openings on reheat                          | AMS-DTL 23053/4          |
| Electrical  | ·                    | ·  |                          |
| Dielectric Strength   | Volts/mil (V/mm)     | 300 (11,811) minimum on dual wall specimen     | ASTM D 2671              |
| Volume Resistivity  | ohm/cm               | 10 <sup>14</sup> minimum on dual wall specimen | ASTM D 2671              |
| Chemical  |                      |  |                          |
| Copper Mirror Corrosion<br>16 hours at 121 ± 2°C (250 ± 4°F)  | -                    | No removal of copper                           | ASTM D 2671, Procedure A |
| Copper Contact Corrosion<br>16 hours at 121 ± 2°C (250 ± 4°F)   | -                    | No pitting or blackening of copper             | ASTM D 2671, Procedure B |
| Flammability  | -                    | Pass   | UL 224, VW-1             |
| Water Absorption<br>24 hours at 23°C (73°F)   | Percent              | 0.5 maximum                                    | ASTM D 2671              |

\* Denotes Lot Acceptance Test

### For More Information

VIsit www.te.com and enter search term "DWFR" or visit www.te.com/DWFRtubing

### **TE Technical Support Center**

| USA:  | +1 (800) 522-6752      |  |  |  |
|---|------------------------|--|--|--|
| Canada:   | +1 (905) 475-6222      |  |  |  |
| Mexico:   | +52 (0) 55-1106-0800   |  |  |  |
| Latin/S. America  | :+54 (0) 11-4733-2200  |  |  |  |
| China:  | +86 (0) 400-820-6015   |  |  |  |
| Germany:  | +49 (0) 6251-1333-1999 |  |  |  |
| UK:   | +44 (0) 800-267666     |  |  |  |
| France:   | +33 (0) 1-3420-8686    |  |  |  |
| Netherlands:  | +31 (0) 73-6246-999    |  |  |  |
| For phone numbers in other countries, go to te.com/support-center |                        |  |  |  |

TE Connectivity, TE, and TE connectivity (logo) are trademarks of the TE Connectivity Ltd. family of companies. Other products, logos and company names mentioned herein may be trademarks of their respective owners. While TE has made every reasonable effort to ensure the accuracy of the information in this document, TE does not guarantee that it is error-free, nor does TE make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. TE reserves the right to make any adjustments to the information contained herein at any time without notice. TE EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES REGARDING THE INFORMATION CONTAINED HEREIN, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. In no event will TE be liable for any direct, incidental, special or consequential damages arising from or related to recipient's use of the information. It is the sole responsibility of recipient of this information to verify the results of this information using their engineering and product environment. Recipient assumes any and all risks associated with the use of the information.

#### www.te.com

© 2015 TE Connectivity Ltd. family of companies. All Rights Reserved.

1-1773862-9 APP CS 11/2015



### **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Heat Shrink Tubing and Sleeves category:

Click to view products by TE Connectivity manufacturer:

Other Similar products are found below :

 770-006S102
 5685710001
 CR8248-000
 CR9960-000
 603312-4
 607381P039
 617867N001
 6500750004
 D-306-38
 770-003S106W2
 770 

 005S105W1
 770-005S106W1
 770-007A303
 770-010Y106W1
 770-010Y706W1
 7771210001
 MFP-1/4"-Clear
 MFP-3/64"-Clear
 790-3012

 MFT-MT2000-NO.14-0-SP
 MHHT-4-15K2-G-104
 MIL-LT-1-1/2-4-SP
 MIL-LT-1-1/2-9-STK
 MIL-LT-1/2-2-STK
 MIL-LT-3-0-SP
 MIL-LT-3/32-6-SP

 3/32-0-SP
 MIL-LT-3/32-6-SP
 MIL-LT-3/4-6-SP
 MIL-LT-3/8-0-SP
 8159270001
 839602-000
 8423-6
 FP301-116-6"-Black
 FP301-1/2-48" 

 Black
 FP301-12-48"-Black-Hdr
 FP301-1/4-48"-Black
 FP301-1/4-48"-White-Hdr
 FP301-1-6"-Clear
 FP301-18-48"-Black-Hdr
 FP301-1/8-6"- 

 Black
 FP301-18-6"-Black-Bulk
 FP301-316-48"-Blue-Hdr
 FP301-316-6"-Clear
 FP301-332-6"-Black
 912229N002
 120-126-16BL
 121-001-09

 121-018-32
 121-018-40
 121-123-1-1-32BTC
 S20-126-16BL
 121-001-09
 S20-126-16BL
 121-001-09