FERROXCUBE

DATA SHEET

TN29/19/15 Ferrite toroids

Supersedes data of September 2004

2008 Sep 01



Ferrite toroids TN29/19/15

RING CORES (TOROIDS)

Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
Σ(I/A)	core factor (C1)	0.98	mm ⁻¹
V _e	effective volume	5410	mm ³
l _e	effective length	73.2	mm
A _e	effective area	73.9	mm ²
m	mass of core	≈ 28	g

Coating

The cores are coated with polyamide 11 (PA11), flame retardant in accordance with "UL 94V-2"; UL file number E 45228 (M).


The colour is white.

Maximum operating temperature is 160 °C.

Isolation voltage

DC isolation voltage: 2000 V.

Contacts are applied on the edge of the ring core, which is also the critical point for the winding operation.



Ring core data

GRADE	A _L (nH)	μί	TYPE NUMBER
3C90	2960 ± 20%	≈ 2300	TN29/19/15-3C90
3E25	7000 ± 25%	≈ 5500	TN29/19/15-3E25

Properties of cores under power conditions

	B (mT) at	CORE LOSS (W) at		
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	
3C90	≥320	≤ 0.61	≤ 0.61	

2008 Sep 01 1710

Ferrite toroids TN29/19/15

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

2008 Sep 01 1711

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for ferroxcube manufacturer:

Other Similar products are found below:

014660H P66/56-3F3 EFD30/15/9-3C94 CPV-RM12/I-1S-12PD-TZ RM10/I-3C90 TX102/66/25-3C11 CPHS-EFD20/7-1S-10P
EFD30/15/9-3C90 TX63/38/25-3E25 EFD15/8/5-3F3-A63-S T102/66/25-3C90 ETD49-3C94 ETD59/31/22-3C90 ER11-3F3-S 4312-02037500 RM10/I-3C90-A250 E25/13/7-3F3 CPH-U15/11/6-1S-4P 4322-021-35150 RM6S-3H3 E55/28/21-3F3 CON-P30/19 U15/11/6-3C94
CLI-EFD15 EFD30/15/9-3F3 058374D EFD15/8/5-3F3-S 058351G TN32/19/13-3F3 U93/76/16-3C90 RM10/I3C90-A400 CSHS-EFD151S-8P-Z RM14/I-3F3 EFD20/10/7-3F3 CSH-EFDD20-1S-8P E42/21/15-3C94 E65/32/27-3F3 TX10/6/4-3E5 EFD20-3C90/K ETD54-3C94
CLI-EFD30 TX102/66/15-3C11 TX58/41/18-3C11 CLI-EP13 009968H 4322-020-97010 TX58/41/18-3E25 TN13/7.5/5-3F3 EFD10-3F3-S
CLI-EF7