

非准定性 医排泄性

DuraType® TM650

The TM650 tube and tape supplies are unique to the DuraType 240ST, Tubemarker 600 and TM650 printers and are not suitable for use in other Kroy DuraType printers.



Available in white or yellow heat shrinkable tubing: $3.2\text{mm}(^{1}/_{8}")$, $4.8\text{mm}(^{3}/_{16}")$, $6.2\text{mm}(^{1}/_{4}")$ with black printing.

Heat shrinkable tubing type: Irradiated polyolefinMIL-LT Shrink temperature: 90°C Operating temperature: -55°C to 135°C Shrink ratio: 3 to 1 Flammability: UL224, VW-1 UL specification: Meets UL-224 Military specification: Meets MIL-I-32053/5, class 1 & 3




- 204mm wide x 242mm deep x 73mm high $(8" \times 9^{1}/_{2}" \times 2^{7}/_{8}")$
- 1.68 kg (3lbs. 7 oz.) without batteries
- 4 D-Cell alkaline batteries (not included)
- Low battery LCD indicator
- AC power adaptor (included)
- FCC Part 15 class A computer devices
- Resident font: Helvetica Regular 8,10,12 and 16pt
- Printer only part number 2559200
- Includes printer and power adaptor

Supplies ordering information

Tube supplies

3.2mm (1/8")	2404201	2404202	
4.8mm (3/ ₁₆ ")	2404210	2404211	
5.2mm (1/4")	2404220	2404221	
Tape supplies	Polyester	Vinyl	
12.7mm	part no	part no	
Black on clear:	2464401	2559401	
Black on white:	2464416	2559416	

Black on white:



TM650 Industrial tape supplies

Available in clear, white, red and yellow tape with black printing.



Permanent adhesion to variety of substrates

(ASTM D3330 on 1/2" strip. Peel strength greater than 600 gram)

- Stainless Steel ■ Aluminum
- Glass ■ Ероху
- ABS ■ Acrylic
- Polycarbonate
- - Painted Metal ■ Rigid PVC



Temperature resistance

Continuous operating temperature range from -40°F to 200°F (-40°C to 93°C).It will withstand a minimum of 200 cycles between -40°F (-40°C) and 200°F (93°C) on the substrate list above.



UV fade resistance

UV fade resistance greater than 2000 hours in QUV Chamber (Estimated 3-5 year exterior durability)



Chemical resistance test

The supply will still be legible after 24 hour immersion in the following chemicals:

- 150° F Water Alcohol Mixture* ASTM #3 Oil
- Hydraulic Fluid Motor Oil ■ Jet Fuel
 - Sea Water
- Alphaflux 200L
- Airplane De-icer (Ethylene Glycol)
- Skydrol (Airplane Hydraulic Fluid)

*50% Ethanol, 30% Methanol, 20% Water

One hour immersion in the following chemicals

■ JP-4 Fuel

■ ASTM Reference Fuel B

■ Trichoroethylene

■ Gasoline

■ MEK

■ Alphaflux

For best results, adhere labels to clean, dry surface. If surface requires cleaning, use a solvent to disslove the residue. The data indicated above was gathered after tests results were received from outside test laboratory. To the best of our knowledge, the above is accurate and true.



Kroy (Europe) Limited Worton Grange, Reading, Berkshire RG2 0LZ England Tel +44 (0)118 9865 200 Fax +44 (0)118 9865 205


www.kroyeurope.com e-mail info@kroyeurope.com

France Service Commercial Tel +33 1 48 69 58 18 Germany Kundendienst Tel +49 2464 907142

Black on vellow:







X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for kroy manufacturer:

Other Similar products are found below:

 $\underline{2470031}\ \underline{2438616}\ \underline{2470032}\ \underline{2487943}\ \underline{2438643}$