

10G High Precision Tweezers



4 1/4" 110 mm Fine, serrated tips and grips

10G.SA Anti-Magnetic Anti-Acid Stainless Steel

General Notes

- low carbon austenitic steel (Material number 1.4435, DIN X2CrNiMo18-14-3, AISI number 316L)
- contains from 16.5 to 18.5 wt% chromium and has important quantities of nickel and molybdenum as additional alloying elements
- non-magnetizable
- good corrosion resistance to most chemicals, salts and acids
- generally used where corrosion resistance and toughness are primary requirements
- typical applications include tweezers for the electronic industry, watch-makers, jewelers and laboratory and medical applications in moderately aggressive chemical environments

Composition

Component	Wt.%	Component	Wt.%	Component	Wt.%
С	≤0.03	Si	≤1.0	Mn	≤2.0
Р	≤0.045	S	≤0.03	Cr	17.0-19.0
Мо	2.5-3.0	Ni	12.5-15.0		

Mechanical properties:

State	annealed
Density	8.0 g/cm ³
hardness HB30	≤215
Hardness Rockwell B	79
Tensile strength, ultimate	500-700 MPa
Tensile strength, yield	290
0.2% Yield stress	≤200 MPa
Elongation, break	40%
Modulus of elasticity	200 GPa

Thermal properties

Coef. of lin. therm expansion	16.0 E-6/°C	20°C-100°C
Coef. of lin. therm expansion	17.0 E-6/°C	20°C-300°C
Specific heat capacity:	0.50 J/(g·K)	
Thermal conductivity:	15W/(m·K)	
Continuos use temperature:	350°C	
Max service temperature, ait	925°C	

Electrical properties

Resistivity	0.75 E-4 Ohm.cm
J	

© IDEAL-TEK SA Credits

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for ideal-tek manufacturer:

Other Similar products are found below :

 56A.SA
 65A.SA
 ALCRON
 BON-102A
 2WF.SA
 4313 SM
 5340
 K5HP.SA
 E6024
 5CF.SA
 MPT123.CP
 3C.TA
 PCSA-4.2
 UV00000300

 AM4023X
 EX2175
 3C.SA.DR.1
 14A.C.DR
 2A.NC
 3.NC
 3XCF.SA
 4.SA.DR
 5.SA.T
 51S.SA
 72MZ.SA
 8507
 2AMZ.SA.0
 3C.SA.NE.6

 3CPR.SA.1
 AA.SA.DN.6
 KCFR
 00D.SA.0
 812.01
 K5SMD.SA
 M12102
 BON-102
 NLP-1
 PEN-TEK
 35A SA
 BS-PCSS2/4

 818.01
 8X
 A242CP
 E5140
 E5350
 AA.SA.DR.6
 7.SA.DR.1
 E5160L
 E5162
 242SVR.SA
 2ABCPR.SA