

LOCTITE[®] 5926™

November 2004

PRODUCT DESCRIPTION

LOCTITE[®] 5926™ provides the following product characteristics:

Technology	Silicone
Chemical Type	Acetoxy silicone
Appearance (uncured)	Blue paste
Components	One component - requires no mixing
Cure	Room temperature vulcanizing (RTV)
Application	Gasketing
Flexibility	Enhances load bearing & shock absorbing characteristics of the bond area.
Specific Application	Gasket replacement or Gasket dressing

LOCTITE[®] 5926™ cures on exposure to moisture in the air to form a tough, flexible, silicone rubber gasket. This product resists aging, weathering and thermal cycling without hardening, shrinking or cracking. Typical applications include valve covers, timing gear covers, differential covers, oil pans, transmission pans, water pumps, and thermostat housings. This product is typically used in applications with an operating range of -54 °C to 204 °C.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Extrusion Rate, g/min:

Pressure 0.62 MPa, temperature 25 °C:

1/8" Nozzle ≥550
Specific Gravity @ 25 °C 1.04
Odor Acetic Acid
Flash Point - See MSDS

TYPICAL CURING PERFORMANCE

Surface Cure

Tack Free Time is the time required to achieve a tack free surface.

Tack Free Time, minutes: Cured @ 25 °C / 50±5% RH

≤60

TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 7 days @ 25 °C / 50% RH:

Physical Properties:

Shore Hardness, ISO 868, Durometer A >25

TYPICAL ENVIRONMENTAL RESISTANCE

The product retains effective properties in contact with automotive fluids, such as motor oil, transmission fluids, alcohol and antifreeze solutions.

NOTE: Not recommended for parts in contact with gasoline.

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

NOTE: The curing process can cause corrosion to some surfaces.

Directions for use

- For best performance bond surfaces should be clean and free from grease.
- Moisture curing begins immediately after the product is exposed to the atmosphere, therefore parts to be assembled should be mated within a few minutes after the product is dispensed.
- 3. The bond should be allowed to cure (e.g. seven days), before subjecting to heavy service loads.
- Excess material can be easily wiped away with non-polar solvents.

NOTE: LOCTITE[®] 5926^{TM} is not recommended for use as a cylinder head gasket or head gasket sealant.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F kV/mm x 25.4 = V/mil mm / 25.4 = inches N x 0.225 = lb N/mm x 5.71 = lb/in N/mm² x 145 = psi MPa x 145 = psi N·m x 8.851 = lb·in N·m x 0.738 = lb·ft N·mm x 0.142 = oz·in mPa·s = cP



Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. [®] denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for loctite manufacturer:

Other Similar products are found below:

37684 MM01939 2257357 2139180 LOC-MIKSER2 406 603, 10ML 403, 50G 2701, 50ML 542, 250ML 572, 50ML 3526 8106, 1L 2700, 50ML 5800, 50ML MM01057 1188112 386862 LOC-5615/400ML 97262 983438 5990, 40ML 648, 50ML 40945 MM01056 98472 984569 5400, 50ML SUPERLUBE OIL, 375ML 290 GC 10 TYPE 3 (JAR) 660, 50ML SUPER GLUE GLASS, 3G LOC-MIKSER 6300, 50ML 2023641 LT 5075 GC 10 TYPE 4 (JAR) 495, 50G 243, 250ML LOC-638-10 98455 496, 50G 2472659 5660, 40ML 4080, 50G 55, 160M 5145 5368, 310ML 518, 65ML