

Water Soluble Flux Pen 837-P Technical Data Sheet

Description

The 837-P *Water Soluble Flux Pen* is a neutral, water-removable soldering flux. The organic activating system in 837-P has a neutral pH at room temperature and becomes activated at soldering temperature. The 837-P flux is formulated to be effective over a broad preheat range and may be used for both leaded and lead-free applications. It cleans easily with hot or cold water. A chiseled tip provides exact delivery of the flux to the surface.

Application & Usages

The 837-P pen is designed to dispense flux in a precisely. It is excellent for prototyping and rework/repair of printed circuit boards. It works well on chip carriers, heat sinks, surface mounted device pads, switches and sockets.

Features and Benefits

- Good soldering properties
- Yields bright, shiny joints
- Excellent wettability
- Cleans with water
- Neutral ρH
- RoHS compliant

Flux Paste Properties

Flux Properties	Method	Value
Flux Classification	J-STD-004	ORH1
Flux type		Organic
Flux Activity		High
Halides %(wt)		2.2% ±0.3%
Copper Mirror	IPC-TM-650 2.3.32	Complete removal of copper film
Corrosion Test	IPC-TM-650 2.6.15	Pass (Cleaned)
Surface insulation resistance (SIR)	IPC-TM-650 2.6.3.3	$1.8 \times 10^{10} \Omega$
Physical Properties	Method	Value
Color		Colorless
pH		7.3 ±0.5
Solids%	IPC-TM-650 2.3.34	17.5% ±1%
Density	ASTM D 4212	0.85
Flash Point	Closed cup	12 °C [54 °F]



Storage and Shelf Life

Store at around room temperature and protect from direct heat or sunlight.

Properties	Value
Shelf Life after DOM	2 y
Storage Temperature	18 to 27 °C [65 to 80 °F]

DOM = date of manufacture

Health and Safety

Please see the 837-P **Safety Data Sheet** (SDS) for more details on transportation, storage, handling and other security guidelines.

Application Instructions

Apply flux directly with the pen on the joint to be soldered.

Cleaning

Use hot or cold water to remove flux residues. A water spray pressure of 20 to 30 lb/in² (psi) is recommended. Use deionized water as a final rinse to meet MIL-28809A cleaning requirements.

Packaging and Supporting Products

Cat. No.	Form	Net Volume		Net Weight	
837-Р	Pen	10 mL	0.33 fl oz	8.4 g	0.27 oz
837LFWS-1L	Liquid	1 L	33 fl oz	846 g	1.87 lb

Suitable Flux Cleaners

- Heavy Duty Flux Remover: Cat. No. 413B-1L, 413B-4L, 413B-20L, 413B-425G
- Flux Remover for PC Boards: Cat. No. 4140-P, 4140-400G, 4140-1L, 4140-4L, 4140-20L



Water Soluble Flux Pen 837-P Technical Data Sheet

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at <u>www.mgchemicals.com</u>.

Email: support@mgchemicals.com

Phone: 1-800-340-0772 (Canada, Mexico & USA) 1-905-331-1396 (International) Fax: 1-905-331-2862 or 1-800-340-0773

Mailing address: Manufacturing & Support 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6

Head Office 9347–193rd Street Surrey, British Columbia, Canada V4N 4E7

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Soldering Flux category:

Click to view products by Metz manufacturer:

Other Similar products are found below :

24-6337-9727 8351-1L 051-0002 051-0007 051-0008 053-1000 053-1001 053-1002 053-1003 CW8700 CW8300 SMD4300TF10 SMD291/30CC CQ2LF CQ4LF 8342-50G 270WR ART.AGT-094 CW8100 CW8400 CW8500 CQ4LF-0.5 CQ4LF-1.0 SMD291 SMD291150G SMD29175G SMD291AX SMD291AX10 SMD291AX250T3 SMD291AX250T5 SMD291ST2CC6 SMD291ST8CC SMD4300TF CW8100 CW8200 CW8500 63-0000-0951 63-0000-0977 63-0000-1544 83-1000-0186 83-1097-2331 NF372-TB 760089 8341-10ML 8341-10ML 835-100ML 837-P SF-01 SF-02 2506-N