

Electronics

ES2000

Raychem

Flame-retardant, adhesive-lined heat-shrinkable tubing (extended temperature range)

Adhesive-lined ES2000 heatshrinkable tubing is specifically designed to meet automotive industry requirements for environmental sealing and electrical insulation of automotive wire splices, terminations, and components.

ES2000 tubing has an outer jacket of radiation-crosslinked, semirigid polyolefin. Flame-retardant and mechanically tough, the jacket provides strain relief and abrasion protection of wire splices and mechanically sensitive components. The inner layer of the tubing is a unique hot-melt adhesive, specially formulated to adhere to all major types of automotive wire insulation and to perform well at an extended temperature range. The adhesive forms an effective barrier against automotive fluids and moisture, helping to protect the harness from the effects of corrosion and water wicking.

Because ES2000 tubing has a high shrink ratio, only a few sizes are needed to cover a wide range of splice and component diameters. ES2000 tubing dimensions have been engineered to provide low-cost sealing solutions on multiple-wire splices (up to seven wires per side), using standard Tyco Electronics application equipment.

Temperature rating

| Full recovery temperature: | 135°C |
|-----------------------------------|----------------|
| Continuous operating temperature: | -40°C to 130°C |


Specifications*

| . | | | |
|-----------|---------|--------|--|
| Туре | Raychem | UL | |
| ES2000 | RT-1112 | E85381 | |

*When ordering, always specify latest issue.

Dimensions (millimeters/inches)





Inside diameter (including core)

Recovered wall thickness**

| | D (min.) | d (max.) | W | W1 | W2 |
|-------------|--------------------|-------------------|-------------------|-------------------|-------------------|
| | Expanded | Recovered after | Minimum | Minimum | Minimum |
| Part number | as supplied | heating | total wall | jacket wall | adhesive wall |
| ES2000-No.1 | 5.72 <i>0.225</i> | 1.27 0.050 | 1.20 0.047 | 0.64 0.025 | 0.56 0.022 |
| ES2000-No.2 | 7.44 0.293 | 1.65 <i>0.065</i> | 1.52 0.060 | 0.76 0.030 | 0.76 0.030 |
| ES2000-No.3 | 10.85 <i>0.427</i> | 2.41 0.095 | 1.91 <i>0.075</i> | 0.89 <i>0.035</i> | 1.02 <i>0.040</i> |
| ES2000-No.4 | 17.78 <i>0.700</i> | 4.45 <i>0.175</i> | 2.41 0.095 | 1.04 0.041 | 1.37 0.054 |

^{**}Wall thickness will be less if tubing recovery is restricted during shrinkage.

Ordering information

| Color | Black |
|----------------------|---|
| Size selection | Consult manufacturer's recommended size selection guidelines. |
| Standard packaging | Cut pieces. See reverse for information on standard cut lengths. |
| Marking | Tubing will be marked with the number size (for example, ES-1, ES-2, ES-3, or ES-4). |
| Ordering description | Specify product name, size, color, and cut length; for example, ES2000-No.2-0-50MM (0=Black). |

Specification values

| | Property | Unit | Requirement | Method of test |
|--------------------|---|------------------|--|----------------|
| Material | Dimensions | mm (inches) | See reverse | ASTM D 2671 |
| | Longitudinal change | percent | 0 to -10 | ASTM D 2671 |
| | Tensile strength | psi <i>(MPa)</i> | 1500 <i>(10.3)</i> minimum | ASTM D 2671 |
| | Ultimate elongation | percent | 250 minimum | ASTM D 2671 |
| | Secant modulus at 2% (expanded)* | psi <i>(MPa)</i> | 20,000 <i>(137)</i> minimum | ASTM D 2671 |
| | Heat shock (4 hours at 225°C/437°F) | | No dripping, flowing or cracking of outer jacket | ASTM D 2671 |
| | Dynamic cut through | pounds (kg) | 30 <i>(13.6)</i> minimum | ASTM D3032 |
| | Volume resistivity | ohm-cm | 1.0 X 10 ¹² minimum | ASTM D 2671 |
| | Flammability | | Self-extinguishing | See note below |
| | | | within 30 seconds | |
| Splice performance | Current leakage | microamps | 0.25 maximum | See note below |
| | Room temperature flex test Current leakage | microamps | 0.25 maximum | See note below |
| | Thermal shock | · | | See note below |
| | Current leakage | microamps | 0.25 maximum | |
| | Low-temperature flexibility Dielectric withstand 1 minute at 1000 V | | No breakdown | See note below |
| | Heat aging | | | See note below |
| | Current leakage | microamps | 0.25 maximum | |
| | Fluid immersion | | | See note below |
| | Current leakage | microamps | 0.25 maximum | |
| | Swell | percent | 50 maximum | |

Note: Consult Raychem RT-1112 for specific details about test procedures.

Standard cut lengths

| Part number | Standard cut length | Cut length tolerance | |
|--------------|---------------------|----------------------|--|
| ES2000-No. 1 | 27 mm, 50 mm, 65 mm | ± 1.5 mm | |
| | 1220 mm | ± 25.4 mm | |
| ES2000-No. 2 | 27 mm, 50 mm, 65 mm | ± 1.5 mm | |
| | 1220 mm | ± 25.4 mm | |
| ES2000-No. 3 | 27 mm, 65 mm, 75 mm | ± 1.5 mm | |
| | 1220 mm | ± 25.4 mm | |
| ES2000-No. 4 | 27 mm, 75 mm, 90 mm | ± 1.5 mm | |
| | 1220 mm | ± 25.4 mm | |

Raychem is a trademark of Tyco Electronics Corporation.

Users should independently evaluate the suitability of the product for their application.

Tyco Electronics Corporation 300 Constitution Drive

Menlo Park, CA 94025-1164

Tel: (800) 926-2425 (US & Canada)

Tel: +1 (650) 361-3860 (All other countries)

Faraday Road Dorcan, Swindon, SN3 5HH United Kingdom Tel: +44 1793 528171

3816 Noborito, Tama-ku Kawasaki, Kanagawa 214-8533 Japan

Tel: +81 44 900 5102

Asia Pacific Headquarters 26 Ang Mo Kio, Industrial Park 2 Singapore 569507

Tel: +65 4866 151

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

^{*}Calculate based on wall thickness of jacket only.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Heat Shrink Tubing and Sleeves category:

Click to view products by TE Connectivity manufacturer:

Other Similar products are found below:

770-006S102 5685710001 CR6145-000 CR8248-000 CR9960-000 603312-4 607381P039 611112-000 617867N001 6500750004 CZ1420-000 D-306-38 770-003S106W2 770-005S105W1 770-005S106W1 770-007A303 770-010Y106W1 770-010Y706W1 7771210001 MFP-1/4"-Clear MFP-3/64"-Clear 790-3012 MFT-MT2000-NO.14-0-SP MHHT-4-15K2-G-104 MIL-LT-1-1/2-4-SP MIL-LT-1-1/2-9-STK MIL-LT-1/2-2-STK MIL-LT-3/0-SP MIL-LT-3/32-0-SP MIL-LT-3/32-6-SP MIL-LT-3/4-6-SP MIL-LT-3/8-0-SP 8159270001 839602-000 8423-6 FP301-116-6"-Black FP301-1/2-48"-Black FP301-12-48"-Black-Hdr FP301-1/4-48"-Black FP301-1/4-48"-White-Hdr FP301-18-48"-Black-Hdr FP301-1/8-6"-Black FP301-18-6"-Black FP301-316-48"-Blue-Hdr FP301-316-6"-Clear FP301-332-6"-Black 912229N002 120-126-16BL 121-001-09 121-018-32