FERROXCUBE

DATA SHEET

EFD12/6/3.5 EFD cores and accessories

Supersedes data of February 2002

2004 Sep 01




EFD12/6/3.5

CORES

Effective core parameters

SYMBOL	PARAMETER VALUE		UNIT
Σ(I/A)	core factor (C1) 2.50		mm ⁻¹
V _e	effective volume 325		mm ³
l _e	effective length 28.5 m		mm
A _e	effective area 11.4 mm		mm ²
A _{min}	minimum area 10.7		mm ²
m	mass of core half ≈ 0.9 g		g



Core sets

Clamping force for A_L measurements, 15 ± 5 N.

GRADE	A _L (nH)	$\mu_{\mathbf{e}}$	AIR GAP (μm)	TYPE NUMBER
3C90	40 ±5%	≈ 80	≈ 540	EFD12/6/3.5-3C90-A40-S
	63 ±8%	≈ 125	≈ 290	EFD12/6/3.5-3C90-A63-S
	100 ±10%	≈ 200	≈ 160	EFD12/6/3.5-3C90-A100-S
	825 ±25%	≈ 1610	≈ 0	EFD12/6/3.5-3C90-S
3C94	40 ±5%	≈ 80	≈ 540	EFD12/6/3.5-3C94-A40-S
	63 ±8%	≈ 125	≈ 290	EFD12/6/3.5-3C94-A63-S
	100 ±10%	≈ 200	≈ 160	EFD12/6/3.5-3C94-A100-S
	825 ±25%	≈ 1610	≈ 0	EFD12/6/3.5-3C94-S
3C96 des	750 ±25%	≈ 1460	≈ 0	EFD12/6/3.5-3C96-S
3F3	40 ±5%	≈ 80	≈ 540	EFD12/6/3.5-3F3-A40-S
	63 ±8%	≈ 125	≈ 290	EFD12/6/3.5-3F3-A63-S
	100 ±10%	≈ 200	≈ 160	EFD12/6/3.5-3F3-A100-S
	700 ±25%	≈ 1370	≈ 0	EFD12/6/3.5-3F3-S
3F35 pro	550 ±25%	≈ 1070	≈ 0	EFD12/6/3.5-3F35-S
3F4 des	40 ±5%	≈ 80	≈ 500	EFD12/6/3.5-3F4-A40-S
	63 ±8%	≈ 125	≈ 260	EFD12/6/3.5-3F4-A63-S
	100 ±10%	≈ 200	≈ 130	EFD12/6/3.5-3F4-A100-S
	380 ±25%	≈ 730	≈ 0	EFD12/6/3.5-3F4-S
3F45 pro	380 ±25%	≈ 730	≈ 0	EFD12/6/3.5-3F45-S

EFD12/6/3.5

Properties of core sets under power conditions

	B (mT) at		CORE LO	SS (W) at	
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; B = 200 mT; T = 100 °C	f = 400 kHz; B = 50 mT; T = 100 °C	f = 500 kHz; B = 50 mT; T = 100 °C
3C90	≥320	≤ 0.036	-	-	-
3C94	≥320	≤ 0.029	≤ 0.2	_	-
3C96	≥340	≤ 0.022	≤ 0.15	≤ 0.06	≤ 0.12
3F35	≥300	_	_	≤ 0.03	≤ 0.045
3F3	≥315	≤ 0.04	_	≤ 0.065	-
3F4	≥250		_	_	_

Properties of core sets under power conditions (continued)


B (mT) at		CORE LOSS (W) at				
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 500 kHz; B = 100 mT; T = 100 °C	f = 1 MHz; B = 30 mT; T = 100 °C	f = 1 MHz; B = 50 mT; T = 100 °C	f = 3 MHz; B = 10 mT; T = 100 °C	
3C90	≥320	_	_	_	_	
3C94	≥320	_	_	_	_	
3C96	≥340	_	_	_	_	
3F35	≥300	≤ 0.35	_	_	_	
3F3	≥315	_	_	_	_	
3F4	≥250	_	≤ 0.09	_	≤ 0.15	
3F45	≥250	_	≤ 0.065	≤ 0.16	≤ 0.11	

EFD12/6/3.5

COIL FORMERS

General data

ITEM	SPECIFICATION
Coil former material	liquid crystal polymer (LCP), glass reinforced, flame retardant in accordance with "UL 94V-0"; UL file number E83005(M)
Solder pad material	copper-tin alloy (CuSn), tin (Sn) plated
Maximum operating temperature	155 °C, <i>"IEC 60085"</i> , class F
Resistance to soldering heat	"IEC 60068-2-20", Part 2, Test Tb, method 1B, 350 °C, 3.5 s
Solderability	"IEC 60068-2-20", Part 2, Test Ta, method 1: 235 °C, 2 s



Winding data for EFD12/6/3.5 coil former (SMD) with 8-solder pads


NUMBER OF SECTIONS	NUMBER OF SOLDER PADS	MINIMUM WINDING AREA (mm²)	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	TYPE NUMBER
1	8	6.5	7.65	18.6	CPHS-EFD12-1S-8P-Z

EFD12/6/3.5

MOUNTING PARTS

General data

ITEM	REMARKS	FIGURE	TYPE NUMBER
Clamp	stainless steel (CrNi); clamping force ≈20 N		CLM-EFD12



EFD12/6/3.5

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for ferroxcube manufacturer:

Other Similar products are found below:

014660H P66/56-3F3 EFD30/15/9-3C94 CPV-RM12/I-1S-12PD-TZ RM10/I-3C90 TX102/66/25-3C11 CPHS-EFD20/7-1S-10P EFD30/15/9-3C90 ETD49-3C94 TN29/19/7.5-3E25 EFD15/8/5-3F3-A63-S T102/66/25-3C90 CPH-ETD59-1S-24P ETD39-3C94 ETD59/31/22-3C90 ER11-3F3-S TX10/6/4-3E5 4312-020-37500 RM10/I-3C90-A250 CPH-U15/11/6-1S-4P 4322-021-35150 RM6S-3H3 E55/28/21-3F3 EFD10-3F3-S CON-P30/19 U15/11/6-3C94 CLI-EFD15 U93/76/30-3C94 EFD30/15/9-3F3 058374D EFD15/8/5-3F3-S 058351G RM14/I-3F3 EFD25/13/9-3F3 TN32/19/13-3F3 U93/76/16-3C90 RM10/I3C90-A400 EFD20/10/7-3F3 CSH-EFDD20-1S-8P E42/21/15-3C94 E65/32/27-3F3 EFD20-3C90/K CLI-EFD30 TX58/41/18-3E25 E13/7/4-3C94 TX102/66/15-3C11 TX58/41/18-3C11 CLI-EP13 009968H 4322-020-97010