

BONDERITE 1455-W Wipes

November 2012

PRODUCT DESCRIPTION

BONDERITE 1455-W Wipes provides the following product characteristics:

Technology	Surface treatment
	Surface conversion with corrosion
	protection and enhanced adhesion.

BONDERITE 1455-W Wipes is a chromium free and water-based corrosion protecting surface treatment for metals like aluminum, zinc, zinc alloy, cold- and hot rolled steel, stainless steel, galvanized, sand basted and armor plate surfaces. BONDERITE 1455-W Wipes produce a conversion which forms from a reaction with the above mentioned metal surfaces to form true chemical bonds. The converted surface provides an excellent base for organic finishes, paint, sealers and most adhesives. This reaction greatly enhances adhesion and corrosion resistance of subsequently applied paints (including primer when multiple coat systems are used), sealers and adhesives. BONDERITE 1455-W Wipes conversion coating process is a dry-in-place application and does not require subsequent cleaning.

TECHNICAL DATA

Concentration	Ready to use wipes
Application	Wet the surface by wipe
	on
Evaporation time	min. 1 minute
Open time	max. 15 minutes
Ph-value	2.6
Application temperature	20 to 40 °C

DIRECTION OF USE

Preliminary Statement

Prior to application it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Application

Treating metal surfaces with BONDERITE 1455-W Wipes is the last step before starting with sealing, bonding or paint process.

The complete process sequence consists of the following steps:

- 1. All bare metal surfaces to be converted with BONDERITE 1455-W Wipes must be dry and free from grease, oil and other foreign matter before pre-treatment. Abrasive cleaning is acceptable method of surface preparation where scale or corrosion particles exist. Afterward thoroughly clean and prepare the metal surface using Teroson FI / FL+ or cleaners used in the paint shop (e.g. SiliconeEx).
- 2. Wipe the clean and dry surface with BONDERITE 1455-W Wipes. Use slightly over lapping vertical and horizontal, even with slightly application pressure. Make sure the entire bare metal surface is

wetted with fluid. The surface should remain wet for one minute for the chmical reaction to be bonded. If handling of the dried, treated work is necessary, operators should wear clean, lint free paint gloves so that the treated surface is not contaminated. If the treated surface becomes damaged or re-contaminated, go back to the first step above.

To use only on bare metal surfaces.

Not to use on paint primers 1K, 2K, Polyester fillers, residual paint coatings and plastic parts.

- **3.** Allow the wetted surface to dry at ambient temperature or speed drying with low velocity (do not disturb film) forced warm air up to 100 °C max. We recommend a temperature arround 60 °C (standard paint conditions)
- **4.** Within 15 minutes apply paint, sealer or adhesive over the dry and converted surface. It is necessary to complete the painting, sealing or adhesive bonding operation. Make sure that all treated surface is covered

Storage

Temperature, °C	+10 to +25
Frost-Sensitive	yes
Shelf-life	12 months

Storage requirements:

Store product in the unopened container in a dry location. Always reseal the wipe package immediately after removing BONDERITE 1455-W Wipes. BONDERITE 1455-W Wipes should be protected from freezing. If the chmemical is frozen, it will be irreversibly damaged and should not be used. When BONDERITE 1455-W Wipes get in contact with the pre-treated surface it could be polluted with surface contamination. To ensure an optimal corrosion protection, the Wipes should be used only once. Wipe that are accidentally allowed to dry out completely should not be remoistured by adding water to the package; dried out wipe should be discarded. To keep wipes moist, reseal any opened package of BONDERITE 1455-W Wipes using the zip lock closure feature on the package. If free fluid accumulates in the bottom of the wipe package, vertically rotate the package 90° and roll the pack a few times around its own axle, the free fluid is re-absorbed by the less moist portion of the unused wines

ADDITIONAL INFORMATION

Disclaimer:

The Information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

This datasheet replaces all former versions.



Henkel AG & Co. KGaA

D-40191 Düsseldorf. Germany Phone: +49-211-797-0 www.henkel.com

Henkel Central Eastern Europ GmbH A-1030 Wien. Austria Phone: +43-1711-040 www.henkel.com

Henkel & Cie AG

CH-4133 Pratteln. Switzerland Phone: +41-61-825-7000 www.henkel.com



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Loctite manufacturer:

Other Similar products are found below:

2003721 2701 5080,GREY 50M X 50MM 37684 GC 10 TYPE 4 (JAR) 97262 406 577, 250ML 603, 10ML 542, 250ML 330, 50ML & 7388, 40ML GLUE REMOVER, 5G 270, 50ML 262, 50ML 40945 98454 3526 SUPER GLUE GLASS, 3G 4080, 50G 460, 50G 641, 50ML 495, 50G 55, 160M 7360 LT 5075 242, 50ML 98472 GC 10 TYPE 3 (JAR) 660, 50ML 3463, 114G 595, 100ML 603, 50ML 2400, 50ML 270 983438 7386, 500ML 572, 50ML 8106, 1L 96001 496, 50G 243, 250ML 5400, 50ML 403, 50G 420, 20G 9464, 50ML 638, 50ML 496, 20G 1487439 3455, 24ML 4062, 20G