### **Encapsulation Resins**

# **Technical Data Sheet**



Page 1

## ER2221 Epoxy Resin

ER2221 is a high temperature resistant, thermally conductive, two-part encapsulation compound based on epoxy technology. Designed to meet increasing demands for efficient thermal dissipation, ER2221 combines ease of processing with an enhanced thermal conductivity when compared to traditional thermally conductive encapsulants. It also offers enhanced performance in high temperature applications as well as those subject to thermal cycling.

- Excellent high temperature resistance; suitable for operating environments up to 150°C
- Enhanced thermal conductivity; ideal for heat dissipation within a variety of applications
- Moderate viscosity for a filled system; provides thermal dissipation for units with limited spacing
- Does not contain abrasive fillers; low wear on dispensing machinery

Approvals RoHS-2 Compliant (2011/65/EU): Yes UL Approval: UL94 V-0

#### **Typical Properties**

Liquid Properties: Base Material Epoxy

Density Part A - Resin (g/ml) 2.00 Density Part B - Hardener (g/ml) 1.01 Part A Viscosity (mPa s 23°C) 8000 Part B Viscosity (mPa s 23°C) 250 Mixed System Viscosity (mPa s 23°C) 6000 Mix Ratio (Weight) 13.91:1 Mix Ratio (Volume) 7:1 Usable Life (23°C) 60 mins Gel Time (23°C) 6 hours Cure Time (23 °C) 24 hours Cure Time (60 °C) 2 hours Cure Time (100 °C) 1 hour Colour Part A - Resin Black Colour Part B - Hardener Brown

Storage Conditions Dry Conditions: Above 15°C, Below 30°C Shelf Life 24 Months (bulk) 12 months (resin pack)

Shrinkage < 1%

#### Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way, Ashby de la Zouch, Leicestershire LE65 1JR T +44 (0)1530 419 600 F +44 (0)1530 416 640 BS EN ISO 9001:2008 Certificate No. FM 32082






Page 2

Cured System:	Thermal Conductivity (W/m.K)	1.20
	Cured Density (g/ml)	1.88
	Temperature Range (°C)	-40 to +150
	Max Temperature Range (Short Term (°C)/30 Mins) (Application and Geometry Dependent)	+170
	Relative Thermal Index (°C)	+130
	Dielectric Strength (kV/mm)	10
	Volume Resistivity (ohm-cm)	10 <sup>10</sup>
	Shore Hardness	D90
	Colour (Mixed System)	Black
	Flame Retardancy	Meets UL94 V-0
	Tensile Strength (MPa)	50
	Compressive Strength (MPa)	120
	Coefficient of Expansion (ppm/°C)	30
	Loss Tangent @ 50 Hz	0.05
	Permittivity @ 50 Hz	6.00
	Comparative Tracking Index	>850 Volts
	Water Absorption (9.7mm thick disk, 51mm diameter) 10 days @ 20°C / 1 hour @ 100°C	< 0.5% / < 1%
	Elongation At Break	6.5%

### **Mixing Procedures**

#### **Resin Packs**

When in Resin pack form, the resin and hardener are mixed by removing the clip and moving the contents around inside the pack until thoroughly mixed. To remove the clip, remove both end caps, grip each end of the pack and pull apart gently. By using the removed clip, take special care to push unmixed material from the corners of the pack. Mixing normally takes from two to four minutes depending on the skill of the operator and the size of the pack. Both the resin and hardener are evacuated prior to packing so the system is ready for use immediately after mixing. The corner may be cut from the pack so that it may be used as a simple dispenser.



#### Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way, Ashby de la Zouch, Leicestershire LE65 1JR T +44 (0)1530 419 600 F +44 (0)1530 416 640 BS EN ISO 9001:2008 Certificate No. FM 32082





Page 3

#### **Bulk Mixing**

When mixing, care must be taken to avoid the introduction of excessive amounts of air. Automatic mixing equipment is available which will not only mix both the resin and hardener accurately in the correct ratio but do this without introducing air. Containers of Part A (Resin) and Part B (Hardener) should be kept sealed at all times when not in use to prevent the ingress of moisture. Bulk material must be thoroughly mixed before use. Incomplete mixing will result in erratic or partial curing.

#### General

Sedimentation of the resin has been minimised by careful attention to the formulation. However, any sediment which may have occurred over long periods of time must be dispersed before removing any material from the container. This dispersion can be carried out (if necessary) by stirring with a broad bladed spatula or gently rolling the can. Take care not to introduce excessive amounts of air during this operation or it may be necessary to re-evacuate the resin. Sedimentation will be accelerated by storage at high temperatures. Sedimentation found in resin packs forms no problem since the sediment is re-mixed when the pack is used.

#### **Additional Information**

**Cleaning:** It is far easier for machines & containers to be cleaned before the resin has been allowed

to cure. Electrolube's RRS is suitable for cleaning machines and containers and cured

resin may be slowly softened and removed by soaking in our RRS.

**Curing:** Do not heat cure large volumes immediately. Allow these to gel at room temperature and

post-cure at high temperature if required (refer to liquid properties for details). Small

volumes (250ml) may be heat cured immediately.

Storage: When storing under very cold conditions, the hardener may crystallise. If this occurs,

simply warm (40°C) the container gently until all crystals have re-melted.

Health & Safety: Always refer to the Health & Safety data sheet before use. These can be downloaded

from www.electrolube.com

Revision 5: Nov 2016

### **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Electrolube manufacturer:

Other Similar products are found below:

EADI200D BLR-15ML UR5545RP250G FLU(5L) URC200D ASA250ML ER2220RP250G ARW300 ER221935SL DCE0.75L TPM350

RRS05L CG-53A HTS100T UR5597RP500G ROC500ML ER2224 EHFAC200H HTSX35SL GP500SL 2K300KIT RCS UR5638

230B1E156K CCRG01L ULL200D SOB200D TCRGUNB UR5637RP250G EADPI200 HTC700G CTG35SL AFAG35SL ECSP200DB

RST250 DCT01L ER2223 SCP26G SSS500ML OSL400 FSC05L SPG900G ER2218RP250G MR8008B SMFL200D EML200F

ULS200D SCP03B AFC400D/12 SCO200D