

TFE and TFER

High-Temperature, Chemically Inert, Modified Tubing made of PTFE

Product Facts

- Shrink ratio: 1.8:1 (TFE) 3.2:1 (TFER)
- High flame-resistance
- Excellent chemical resistance
- RoHS compliant



Applications

Designed to provide insulation and mechanical protection in severe chemical and thermal environments. Used to cover hydraulic hose and couplings to prevent contamination and corrosion. The high mechanical strength and extremely low coefficient of friction make it good for reducing damage to bearing shafts and similar applications.

Installation

Minimum shrink temperature: 330°C [625°F] Minimum full recovery temperature: 340°C [644°F]

Operating Temperature Range

-67°C to 250°C [-88.6°F to 482°F]

Specifications/Approvals

Series	Military	Raychem
TFE, TFER	AMS-DTL-23053/12*, Classes 3 and 5 Def. Stan. 59-97 Type 5A (TFE) Def. Stan. 59-97 Type 5B (TFER)	RW-2055 (TFE) RW-2054 (TFER)

^{*}Formerly MIL-I-23053/12 and MIL-DTL-23053/12.

Available in:	Americas	Europe	Asia Pacific	
			•	



TFE and TFER (Continued)

Product Dimensions TFE

	Inside Diameter		Wall Thickness**	
Size	Minimum Expanded as Supplied	Maximum Recovered After Heating	Nominal Recovered After Heating	
30	0.8 [0.032]	0.38 [0.015]	0.23 [0.009]	
28	0.9 [0.035]	0.46 [0.018]	0.23 [0.009]	
26	1.1 [0.043]	0.56 [0.022]	0.25 [0.010]	
24	1.2 [0.047]	0.68 [0.027]	0.25 [0.010]	
22	1.4 [0.055]	0.81 [0.032]	0.30 [0.012]	
20	1.5 [0.059]	0.99 [0.039]	0.30 [0.012]	
18	1.9 [0.075]	1.24 [0.049]	0.30 [0.012]	
16	2.3 [0.091]	1.55 [0.061]	0.30 [0.012]	
14	3.0 [0.118]	1.83 [0.072]	0.30 [0.012]	
12	3.8 [0.150]	2.26 [0.089]	0.30 [0.012]	
10	4.8 [0.189]	2.84 [0.112]	0.30 [0.012]	
8	6.1 [0.240]	3.58 [0.141]	0.38 [0.015]	
6	7.6 [0.299]	4.52 [0.178]	0.38 [0.015]	
4	9.4 [0.370]	5.69 [0.224]	0.38 [0.015]	
2	10.9 [0.429]	7.06 [0.278]	0.38 [0.015]	
0	11.9 [0.469]	8.81 [0.347]	0.38 [0.015]	

^{**}Wall thickness will be less if tubing recovery is restricted during shrinkage.

TFER

Size	Inside Diameter		Wall Thickness**	
	Minimum Expanded as Supplied	Maximum Recovered After Heating	Nominal Recovered After Heating	
5/64	2.0 [0.079]	0.6 [0.024]	0.23 [0.009]	
1/8	3.2 [0.126]	1.0 [0.039]	0.25 [0.010]	
1/4	6.4 [0.252]	1.6 [0.063]	0.30 [0.012]	
3/8	9.5 [0.374]	2.4 [0.095]	0.30 [0.012]	
1/2	12.7 [0.500]	3.7 [0.146]	0.38 [0.015]	
5/8	15.9 [0.626]	4.5 [0.177]	0.38 [0.015]	
3/4	19.0 [0.748]	5.7 [0.224]	0.38 [0.015]	
1	25.4 [1.000]	7.1 [0.230]	0.38 [0.015]	
1-1/4	32.0 [1.260]	8.8 [0.347]	0.38 [0.015]	

^{**}Wall thickness will be less if tubing recovery is restricted during shrinkage.

Ordering Information

Color	Standard Clear (-X)	
Size selection	Always order the largest size that will shrink snugly over the component to be covered. Special order sizes are available upon request.	
Standard packaging	In 1.2-meter [4-foot] lengths.	
Ordering description***	Specify product name, size and color (for example,TFE 22-X).	

^{***}Europe only. For supply to MIL spec., Def Stan and BS add -MS, -DS or -BS to ordering description.

Germany: 49-6251-133-1999 China: 86-400-820-6015 Japan: 81-44-844-8013 UK: 44-800-267-666

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for TE Connectivity manufacturer:

Other Similar products are found below:

D38999/24FJ4AN 1-2000677-8 SMD100-2 D38999/20WJ43BD 4-176756-8 983-6SE22-12S7-L D38999/24ZE35PN CUA-41-70003

DJT10F17-26HN 5-1437490-9 7022X3H 983-6SE18-14P9-L AFD50-16-23SN-6116-LC 603995-1 D38999/24WF32JE D38999/24WF32SE-LC DTS24W19-32HE D38999/20WD19SB-LC 842723N001 213904-1 C1177A AFD51-18-32PW-6116-LC D38999/24FD19PD

D38999/24FD19PD-LC D38999/24FF32BA D38999/26WH21PB-LC D38999/20FH21PE D38999/20FH21PE-LC D38999/24FD1PN

DTS20F23-21PE D38999/20FH21PB-LC D38999/26FJ35PE D38999/32Z15N DTS26W9-35JB-LC D38999/26JJ29JN 102976-7

D38999/20FJ4SB-LC 1-2322421-6 D38999/20FJ24SB-LC MS3474L12-10P-LC MS3474L12-10PW-LC MS27467T21F16P-LC D50184-000

WINTOTAL-6-END-USER-LICENCE 164-8033-08 DTS26W17-99HA MS27468T17F26H DJT14F17-26HN DJT14F17-26HB

AFD58-24-61PY-1A