

8616

Description

The 8616 Super Thermal Grease II is a low thermal resistance grease with a synthetic oil base that is electrically insulating and non-corrosive. It is used to improve the thermal interface contact conductivity between heat sinks, LEDs, motors, and heat-generating electronic components such as CPUs, GPU chipsets, and power components. It improves the thermal interface between irregular and pitted surfaces.

Benefits & Features

- · High thermal conductivity
- Silicone free and non-bleeding
- Excellent corrosion resistance—Passed ASTM B 117 1 000 hours
- Lowers the contact resistance between irregular surfaces
- Extends the life of electronic components
- · Electrically insulating
- Safe on plastics

Usage Parameters

Properties	Value		
Shelf Life Theoretical Coverage for 3 mL syringe ^{a)}	5 y <1 180 cm ² <0.64 ft ²		

a) Idealized estimate based on $25 \mu m$ [1.0 mil] thickness and 100% transfer efficiency.

Temperature Ranges

Properties	Value
Constant Service Temperature Storage Temperature Limits	-68 to 165 °C [-90 to 329 °F] -10 to 40 °C [14 to 104 °F]

Principal Components

Name
Aluminum oxide
Zinc oxide (thermally conductive filler)

CAS Number
1344-28-1
1314-13-2

Properties

Thermal Properties	Method	Value
Thermal Conductivity @25 °C [77 °F]	ASTM E 1461	1.78 W/(m·K)
Contact Thermal Resistance a)	ASTM E 1225	$0.24 \times 10^{-3} (m^2 \text{K})/\text{W}$

a) Tested with stainless steel plates

Rev. Date: 20 June 2017 / Ver. 1.05



8616

Electrical Properties	Method	Value
Volume Resistivity (ρ _ν)	ASTM D 257	1.8 x 10 ¹¹ Ω·cm
Volume Conductivity (σ _v)	"	5.6 x 10 ⁻¹² S/cm
Dielectric Strength @50 mil gap	ASTM D 149	330 V/mil [13 kV/mm]
Breakdown Voltage	п	16 600 V [16.6 kV]
Dielectric Constant @1 000 cps	ASTM D 150	6.77
@10 000 cps	"	6.69
Dissipation Factor @1 000 cps	"	0.01
@10 000 cps	"	0.01
·		

TBD=To be determined

Grease Properties	Method	Value
Evaporation Loss, 22 h @165 °C [329 °F]	ASTM D 2595	1.2%
Oil Separation, 30 h @165 °C [329 °F]	ASTM D 6184	0.02%
Dropping Point	ASTM D 2265	>300 °C [>572 °F]
Water Washout @38 °C [100 °F]	ASTM D 1264	0.9%
Worked Penetration, unworked	ASTM D 217	284
60 strokes	"	287
10 000 Strokes	"	313
Salt Spray Corrosion Resistance a)	ASTM B 117	Pass
, ,		
Physical Properties	Method	Value
Physical Properties Color	Method	Value White silvery
Color	Method	White, silvery
Color Odor		White, silvery Odorless
Color Odor Density @25 °C [77 °F]	Method ASTM D 1475	White, silvery Odorless 2.69 g/mL
Color Odor Density @25 °C [77 °F] Viscosity		White, silvery Odorless 2.69 g/mL Thixotropic paste
Color Odor Density @25 °C [77 °F] Viscosity Lubricant		White, silvery Odorless 2.69 g/mL Thixotropic paste No
Color Odor Density @25 °C [77 °F] Viscosity Lubricant Bleed		White, silvery Odorless 2.69 g/mL Thixotropic paste No Yes
Color Odor Density @25 °C [77 °F] Viscosity Lubricant Bleed Corrosion Resistant		White, silvery Odorless 2.69 g/mL Thixotropic paste No Yes Yes
Color Odor Density @25 °C [77 °F] Viscosity Lubricant Bleed		White, silvery Odorless 2.69 g/mL Thixotropic paste No Yes

a) Aluminum 2024 coupons with 254 $\,\mu m$ [10 mil] film thickness and 1 000 hours exposure to 5% salt spray

Synthetic Oil Properties	Method	Value
Oil Viscosity Index c)	ASTM D 2270	>110
Fire Point d)	ASTM D 92	321 °C [609.8 °F]
Flash Point	ASTM D 92	>290 °C [>554 °F]

Note: Values based on synthetic oil component only.

- c) High oil viscosity index of more than a 100 indicate small oil viscosity change with temperature.
- d) Temperature at which oil will continue to burn for at least 5 s after ignition with an open flame.



8616

Storage

Store between -10 and 40 °C [14 and 104 °F] in dry area.

Health, Safety, and Environmental Awareness

Please see the 8616 **Safety Data Sheet** (SDS) for greater details on transportation, storage, handling and other security guidelines.

Environmental Impact: The VOC (volatile organic compound) content is 18% by WHMIS and European standards. Not regulated as a dangerous good for transport.

Health and Safety: Wear safety glasses and disposable gloves to avoid exposures.

HMIS® RATING

HEALTH:	1
FLAMMABILITY:	1
PHYSICAL HAZARD:	0
PERSONAL PROTECTION:	





Approximate HMIS and NFPA Risk Ratings Legend:

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

Application Instructions

The conductive grease performance depends on mainly on surface preparation. Improperly prepared contact surfaces can degrade the paste's stability, conductivity, and lubrication characteristics. While the thickness and coverage are also important, the application method itself can easily be adjusted according to performance and application needs.

Prerequisites

- Wear gloves and protective clothing.
- Clean and dry the surface of the substrate to remove other oils and greases, as well as dust, water, solvents, or any other contaminants.
- Recommendations: Use MG 824 Isopropyl Alcohol or MG 4351 Thinner

Equipment

- Lint free cloth (for cleaning contact and for wiping excess residue)
- Spatula or stick application tools (sized appropriately for your application)
- Isopropyl alcohol or other residue-free organic solvents

To apply the grease

- 1. Wipe the contact with a lint-free cloth.
- 2. Clean the contacts with isopropyl alcohol or other non-oil based cleaner.
- 3. Once dry, spread grease in a thin layer onto the surface.

Page 3 of 4

Rev. Date: 20 June 2017 / Ver. 1.05



8616

Packaging and Supporting Products

Cat. No.	Packaging	Net Volume		Net Weight		Packaging Weights	
8616-3ML	Syringe	3 mL	0.1 fl oz	8.07 g	0.28 oz	0.02 kg	0.04 lb
8616-25ML	Jar	25 mL	0.84 fl oz	67.2 g	2.37 oz	0.63 kg ^{a)}	1.4 lb ^{a)}
8616-85ML	Tube	86 mL	2.93 fl oz	228 g	8.21 oz	TBD	TBD
8616-1P	Jar	483 mL	1.0 pint	1.3 kg	2.86 lb	1.34 kg	2.95 lb
8616-1G	Pail	3.78 L	1.0 gal	10.1 kg	22.4 lb	10.6 kg	23.3 lb
Contact MG Chemicals if custom packaging or sizes are required							

TBD=To be determined

a) Case pack of five

Supporting Products

• Thinner: Cat. No. 4351-1L

• Isopropyl Alcohol: Cat. No. 824-1L

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAOs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+(1) 905-331-1396 (International) +(44) 1663 362888 (UK & Europe)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: Manufacturing & Support Head Office

1210 Corporate Drive 9347–193rd Street

Burlington, Ontario, Canada Surrey, British Columbia, Canada

L7L 5R6 V4N 4E7

Warranty

M.G. Chemicals Ltd. warranties this product for 12 months from the date of purchase by the end user.

M.G. Chemicals Ltd. makes no claims as to shelf life of this product for the warranty. The liability of

M.G. Chemicals Ltd. whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

Rev. Date: 20 June 2017 / Ver. 1.05

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for MG ELECTRONICS manufacturer:

Other Similar products are found below:

<u>M-50H FMS-100</u> <u>8616-25ML AVC-25</u> <u>8616-3ML T-65BT MGT-1220 MGT 1640 MGT2412DV BT-2 MGT 2420 ST-122A ST-241A MGT 2440 M132</u>