## **MUREX** Welding Consumables

Table 1 Fume analysis for MMA Electrodes where control of total welding fume to 5mg/m<sup>a</sup> will ensure that no constituent of the fume will exceed its own recommended limit.

Fume Analysis (wt %)											
Electrode	Fe	Mn	Nī Nī	Çr	Cu	Pb	F				
Castcraft*	2	0.2	2.5	0.1	0.1	0.1	5				
Celtian	40	3.5	0.1	<0.1	0.2	0.1	•	٠,			
Cinex	2	0.2	2.5	0.1	<0.1	0.1	5				
Fastex 5	30	5	0.1	<0.1	0.1	0.1	u				
Ferex Super	19	<b>3</b> .5	<0:1	<0.1	<0.1	0.1	18				
Ferex Universal	21	7	<0.1	<0.1	0.1	0.3	10				
Ferex 7016	12	5	<0.1	0.1	<0.1	0.1	13				
Ferex 7016-1Ni	7	4	0.2	<0.1	<0.1	0.2	12				
Ferex 7018LT	20	5	0.1	<0.1	<0.1	0.4	18				
Ferroloid 1	2	0.4	1	0.1	2	0.1	5				
Ferroloid 3	3	0.4	1.5	0.1	<0.1	0.1	5				
Ferromax	28	5	0.1	0.1	<0.1	0.2	4				
Fortrex NQ1	8	· 5	0.1	<0.1	<0.1	0.1	9				
Fortrex NQ2	7	6	0.1	<0.1	<0.1	0.1	8				
Fortex 7018	13	6	0.2	<0.1	0.1	0.4	16				
Fortex 8018-C1	15	3.5	0.1	<0.1	. <0.1	0.1	14	•			
Gravitex	27	7	<0.1	<0.1	<0.1	0.1	-				
Groovex	31	16	<0.1	<0.1	<0.1	<0,1	-				
Hi-Trex 7016-C1L	8	3	0.1	<0.1	<0.1	0.6	14				
Hi-Trex 8016G	17	9	0.1	<0.1	<0.1	0.2	5				
Mirrospeed	30	7	0.1	<0.1	0.1	0.1	· -				
Murex Ferrospeed*	32	6	<0.1	<0.1	< 0.1	<0.1	_				
Murex 6010*	54	6	<0.1	<0.1	<0.1	0.3	-				
Murex 6013*	35	5	<0.1	<0.1	<0.1	<0,1	-				
Murex 7010 A1*	57	5	<0.1	<0.1	0.2	<0.1	-				
Murex 7010 G*	40	6	0.1	<0.1	< 0.1	<0.1	•				
Murex 8010"	42	8	0,2	<0.1	<0.1	<0.1	-				
Satinex	27	7	<0.1	<0.1	0.1	<0.1	-				
Super Fastex	21	5	<0.1	<0.1	<0.1	<0.1	<del></del>				
Vodex	35	5	<0.1	<0.1	0.1	0.1	₩.				
Vortic Marine	40	5	0.1	0.1	0.1	0.1	*				
Zodian Super	30	6	0.1	<0.1	0.1	<0.1					
Zodian Universal	30	7	0.1	<0.1	0.1	0.1	-				

<sup>\*</sup> Denotes information has changed since last issued.

## **ESAB** Welding Consumables

Table 1 Fume analysis for MMA Electrodes where control of total welding tume to 5mg/m³ will ensure that no constituent of the fume will exceed its own recommended limit.

Fume Analysis (wt %)									
Electrode	Fe	Mn	Ni	Cr	Cu	Pb	F	Al	
OK 21.03 Cutmat	31	16	<0.1	<0.1	< 0.1	<0.1	_	7	
OK 33.80 Femax	30	7	<0.1	<0.1	<0.1	<0.1	4	•	
OK 43,23 Smoothtrode	20	9	0.1	0.1	0.1	<0.1		-	
OK 43.24 Silkmat	24	7 ,	<0.1	<0.1	<0.1	<0.1	•	-	
OK 46.00 Mildtrode	35	5	<0.1	<0.1	< 0.1	<0.1	-	-	
OK 46.68 Versimat	27	7	<0.1	<0.1	0.1	0.1	~	-	
OK 48.00 Unitrode	19	4	< 0.1	<0.1	<0.1	<0.1	18	-	
OK 48.04 Unitrode	23	5	<0.1	<0.1	<0.1	<0.1	18		
OK 53.08 Hytuf 1Ni	9	5	0.1	<0.1	<0.1	0.2	7	·	
OK 49.20 Losilmat	22	12	<0.1	<0.1	0.1	0.2		<del></del>	
OK 53.88 Hytrode	7	4	<0.1	< 0.1	< 0.1	0.3	15	•	
OK 55.00 Tensitrode	17	5	<0.1	< 0.1	<0.1	< 0.1	20	-	
OK 73.08	22	5	<0.1	<0.1	0.6	<0.1	18	-	
OK 73.69 8018-C1	18	3	0.3	< 0.1	<0.1	<0.1	17	-	
OK 74.56 Molytrode	20	4	<0.1	<0.1	<0.1	< 0.1	18	~	
OK 74.78 Tensitrode	13	6	<0.1	<0.1	<0.1	<0.1	20	-	
OK 74.86 Tensitrode	18	7	0.1	0.1	<0.1	<0.1	20	-	
OK 75.65	19	4	0.2	<0.1	<0.1	<0.1	19	-	
OK 75.75	16	6	0,2	0.1	<0.1	<0.1	21	-	
OK 75.76 Tensitrode	13	5	0.2	0.3	<0.1	0.2	14	-	
OK 76.19 Chromotrode	19	6	0.1	0.3	<0.1	0.4	7	<u>-</u> .	
OK 76.28 Chromotrode	18	4	<0.1	0.6	<0.1	<0.1	20	-	
OK 78.12	17	7	0.4	<0.1	<0.1	< 0.1	13	-	
OK 92.18 Castmat Ni	2	0.2	2.5	0.1	0.1	0.1	5	•	
OK 92.58 Castmat NiFe	3	0.4	1.5	0.1	2	0.1	5	₩	
OK 92.78 Castmat NiCu	2	1.4	1	0.1	2	0.1	5	•	
OK 96.50 Almintrode	0.1	0.1	<0.1	<0.1	<0.1	<0.1	20	21	

## **MUREX**

Table 3 Fume analysis for MMA Electrodes where the fume contains hexavalent chromium compounds for which a long term exposure limit of 0.05mg/m³ is included in Guidance Note EH40.

Fume Analysis (wt %)										
Electrode	Fe	Mn	Ni	Çr	Cu	Pb	F	<i>:</i>		
Armex 2	18	9	2	8	0.2	0.2	6 6	#**\*; **** * *		
Armex 2PR	5	2	0.5	5	<0.1	<0.1	3	:		
Armoid 1	12	6	1	4	0.1	0.1	11	:		
Cobalarc 1A*	12	2	0.1	2	<0.1	0.1	11			
Hardcraft*	30	6	<0.1	1.8	<0.1	<0.1	· <b>-</b>			
Hardex 350	38	8	0.1	2	<0.1	<0.1		•		
Hardex 650	39	9	0.1	2.5	<0.1	<0.1	_			
Hardex 650B	25	4	0.1	2	<0.1	0.1	14			
Hardex 800	27	2.5	0.1	3	<0.1	0.1	9			
Hardex MnP	8	11	0.5	8	0.1	0.3	8			
Nicrex E308L	6	3	0.4	5	<0.1	0.1	4			
Nicrex E309L*	3	3	0.5	6	<0.1	<0.1	14	•		
Nicrex E309MoL	5	4	1	7	0.1	0.1	16			
Nicrex E312	12	12	1,5	12.5	<0.1	0.1	10	ļ		
Nicrex E316L	6	3	0.6	4	、<0.1	0.1	7	1		
Nicrex E347	6	2	0.4	5	<0.1	0.1	5			
Nicrex UE1*	8	13	0.5	3,5	0.1	0.3	_			
Nicrex 1	12	8	2	7	0.1	0.3	20			
Weldall*	4	3	0.3	5	0.1	0.3				

<sup>\*</sup> Denotes information has changed since last issued.

## **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for murex manufacturer:

Other Similar products are found below:

**MUREX**