SPECIFICATION CONTROL DRAWING		44A7422
WIRE, RADIATION-CROSSLINKED, POLYALKENE-INSULATED, MEDIUM WEIGHT, 600 VOLT	7-28-11	Т

This specification sheet forms a part of the latest issue of Raychem Specification 44.

CONDUCTOR - E.C. ALUMINUM

JACKET - RADIATION-CROSSLINKED, MODIFIED PVDF
Thickness: .006 + .002 in.
- .001 in.

BRAIDS - 1st, GLASS BRAID
2nd, PET, TREATED TO
PREVENT FRAYING

	TABLE I. CONSTRUCTION DETAILS					
	SIZE STRAND		DIAMETER OF	FINISHED WIRE		
PART NUMBER 1/		CONDUCTOR STRANDING (number x AWG)	STRANDED CONDUCTOR (in.)	MAXIMUM RESISTANCE AT 20°C (ohms/1000 ft)	DIAMETER (in.)	MAXIMUM WEIGHT (lbs/1000 ft.)
44A7422-8-**	8	41 x 24	.155 ± .005	1.09	.217 ± .010	28.0
44A7422-6-**	6	70 x 24	.206 ± .005	.641	.275 ± .012	44.9
44A7422-4-**	4	107 x 24	.255 ± .007	.427	.327 ± .012	63.9
44A7422-2-**	2	168 x 24	.320 ± .010	.268	.400 ± .015	94.6
44A7422-1-**	1	219 x 24	.358 ± .010	.214	.440 ± .015	120.
44A7422-0-**	0	259 x 24	.408 ± .012	.169	.490 ± .015	142.
44A7422-00-**	00	334 x 24	.466 ± .012	.133	.560 ± .018	183.
44A7422-000-**	000	427 x 24	.523 ± .012	.109	.620 ± .020	223.
44A7422-0000-**	0000	523 x 24	.575 ± .012	.085	.680 ± .022	269.

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER. AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER

Page 1 of 2

Raychem, TE Connectivity, TE connectivity (logo) and TE (logo) are trademarks.

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.



Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297



SPECIFICATION CONTROL DRAWING

Page 2 of 2

Revision SCD Number

Т

44A7422

TABLE II. PERFORMANCE DETAILS						
	BEND TESTING					
PART NUMBER	MANDREL DIAMETER (inch) (± 3%)			WEIGHT (lb) (± 3%)		
1/	IMMERSION LIFE CYCLE AND ACCELERATED AGING	COLD BEND	WRAP	IMMERSION LIFE CYCLE AND ACCELERATED AGING	COLD BEND	
44A7422-8-**	3.00	6.00	.750	3.00	6.00	
44A7422-6-**	4.00	8.00	1.00	3.00	10.0	
44A7422-4-**	5.00	10.0	1.25	3.00	10.0	
44A7422-2-**	6.00	12.0	3.00	4.00	15.0	
44A7422-1-**	7.00	13.0	4.00	4.00	15.0	
44A7422-0-**	8.00	14.0	4.00	4.00	15.0	
44A7422-00-**	9.00	16.0	5.00	4.00	15.0	
44A7422-000-**	10.0	18.0	6.00	4.00	15.0	
44A7422-0000-**	12.0	18.0	6.00	4.00	15.0	

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C

Maximum continuous conductor temperature VOLTAGE RATING: 600 volts (rms) at sea level *ACCELERATED AGING: 300 \pm 2°C for 7 hours

Identification legibility, 225 ± 2°C *BLOCKING: 150 ± 2°C for 6 hours

BRAID (PET) COLOR: For tan only, Munsell Color Limits are per Table III. (Note: Due to the braid treatment, braids may include intermitten color variations such as smudges, spots or marks.) FLAMMABILITY: 30 seconds (maximum); 3 in. (maximum); no flaming of facial tissue

*HUMIDITY RESISTANCE: Insulation Resistance, 5000 megohms for 1000 ft. (minimum)

IMMERSION: Diameter increase 5% (maximum); no cracking, no dielectric breakdown.

INSULATION ELONGATION AND TENSILE STRENGTH:

Primary Insulation,

Elongation, 150% (minimum)

Tensile Strength, 2000 lbf/in2 (minimum)

INSULATION FLAWS:

Primary Insulation,

Spark Test, 3.0 kV (rms)

Impulse Dielectric Test, 6.0 kV (peak)

Finished Wire,

Spark Test, 5.0 kV (rms) at 3 kHz Impulse Dielectric Test, 8.0 kV (peak) INSULATION RESISTANCE: 5000 megohms for 1000 ft. (minimum)

JACKET COLOR: White

LIFE CYCLE: 200 ± 2°C for 168 hours

LOW TEMPERATURE-COLD BEND: -65 \pm 2°C for 4 hours SHRINKAGE: 300 \pm 2°C, 0.125 in. (maximum) in 12 in.

SMOKE: 200 ± 2°C. No visible smoke.

*SURFACE RESISTANCE: 500 megohms-in. (minimum), both readings

THERMAL SHOCK RESISTANCE: 150 ± 2°C, 0.060 in. (maximum)

VOLTAGE WITHSTAND (Post Environmental):

2500 volts (rms), 60 Hz, 5 minutes

PART NUMBER: The "**" in the part numbers on pages 1 and 2 shall be replaced by color code designators.

1/ Example: AWG 8, tan; 44A7422-8-1L AWG 8, white; 44A7422-8-9

TABLE III. MUNSELL COLOR LIMITS (For Tan)		
HUE	5R - 5YR	
VALUE	3.0 - 5.0	
CHROMA	4.0 - 6.0	

^{*} NOTE: These tests to be conducted prior to the application of the braids.

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Multi-Conductor Cables category:

Click to view products by TE Connectivity manufacturer:

Other Similar products are found below:

89182-010-1000 89705-008-500 89842-002-1000 6000FE-877-1000 6120UL-002-1000 CS2885-000 M27500-20SP2S23 6300FE-877-U1000 6309UE-877-1000 M3905-BK005 6502FE 8771000 6541PA-008-U1000 CV6807-000 CW9530-000 CX6543-000 CXA-0066-20-4-9CS2973 CXA-0078-16-1-9CS2405 CXA-0078-22-4-9CS2405 CXA-0078-24-4-9CS2405 CXA-0140-16-6/9-9CS2405 CY0660-000 720451-000 752687-000 768146-000 773159-000 82841-877-5000 83318E-009-500 8348-060-500 83559-002-1000 83653-002-5000 83659-002-1000 83709-002-1000 8404-060-500 8469 060100 858171-000 8628-060-500 868361-001 8730-060-1000 8737-060-U1000 8747-060-100 8747-060-1000 8769-060-1000 8775-060-500 8780-060-1000 8782-001-U1000 88444-002-1000 9159-060-500 9318-060-1000 939870-000 9423 060U500