

3M

VHB™ Tapes

Technical Data

October 2018

Product Description:

3M™ VHB™ Tapes provide the convenience and simplicity of a tape fastener and are ideal for use in many interior and exterior bonding applications. In many situations, they can replace rivets, spot welds, liquid adhesives and other permanent fasteners.

These 3M™ VHB™ Tapes are made with acrylic foam which is viscoelastic in nature. This gives the foam energy absorbing and stress relaxing properties which provides these tapes with their unique characteristics. The acrylic chemistry provides outstanding durability performance.

These tapes utilize a variety of specific foam, adhesive, color and release liner types to provide each product/family with specific features. These features can include adhesion to specific or a broad range of materials, conformability, high tensile strength, high shear and peel adhesion, resistance to plasticizer migration, and UL746C recognition. All 3M™ VHB™ Tapes have excellent durability and excellent solvent and moisture resistance.

The tapes included in this data page represent products most commonly used by customers. Please refer to “3M™ VHB™ Tape Specialty Tapes” technical data sheet for additional 3M™ VHB™ Tapes that may be required in special circumstances.

3M™ VHB™ Tape Products

4941 Family

This family utilizes multi-purpose acrylic adhesive on both sides of a conformable adhesive foam core. The adhesive provides excellent adhesion to a broad range of high and medium surface energy substrates including metals, glass, and a wide variety of plastics, as well as plasticized vinyl. The conformable adhesive foam core provides good contact, even with mismatched substrates. The combination of foam strength, conformability, and adhesion makes this family one of the most capable all-around 3M™ VHB™ tapes.

| Tape Number | Color | Thickness in (mm) |
|-------------|-------|-------------------|
| 4919F | Black | 0.025 (0.6) |
| 4926 | Gray | 0.015 (0.4) |
| 4936(F) | Gray | 0.025 (0.6) |
| 4941(F) | Gray | 0.045 (1.1) |
| 4947F | Black | 0.045 (1.1) |
| 4956(F) | Gray | 0.062 (1.6) |
| 4979F | Black | 0.062 (1.6) |
| 4991 | Gray | 0.090 (2.3) |
| 4991B | Black | 0.090 (2.3) |

5952 Family

This family utilizes modified acrylic adhesive on both sides of a very conformable adhesive foam core, providing adhesion the broadest range of substrates, including most powder coated paints.

| Tape Number | Color | Thickness in (mm) |
|-------------|-------|-------------------|
| 5906 | Black | 0.006 (0.15) |
| 5907 | Black | 0.008 (0.20) |
| 5908 | Black | 0.010 (0.25) |
| 5909 | Black | 0.012 (0.30) |
| 5915(P) | Black | 0.016 (0.4) |
| 5915WF | White | 0.016 (0.4) |
| 5925(P) | Black | 0.025 (0.6) |
| 5925WF | White | 0.025 (0.6) |
| 5930(P) | Black | 0.032 (0.8) |
| 5930WF | White | 0.032 (0.8) |
| 5952(P) | Black | 0.045 (1.1) |
| 5952WF | White | 0.045 (1.1) |
| 5958FR | Black | 0.040 (1.0) |
| 5962(P) | Black | 0.062 (1.6) |
| 5962WF | White | 0.062 (1.6) |

RP Family

This family utilizes multi-purpose acrylic adhesive on both sides of a conformable adhesive foam core. The adhesive provides good adhesion to a broad range of high and medium surface energy substrates including metals, glass, and a wide variety of plastics. The conformable adhesive foam core provides good contact, even with mismatched substrates

| Tape Number | Color | Thickness in (mm) |
|-------------|-------|-------------------|
| RP16(F) | Gray | 0.016 (0.4) |
| RP25(F) | Gray | 0.025 (0.6) |
| RP32(F) | Gray | 0.032 (0.8) |
| RP45(F) | Gray | 0.045 (1.1) |
| RP62(F) | Gray | 0.062 (1.6) |

(P) or (F) after the product number designates that both a paper and film liner product version are available. [e.g. 4941 (paper liner) and 4941F (film liner), 5915 (film liner) and 5915P (paper liner)]. See page 2 for specific details.

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

| 3M™ VHB™ Tapes | | | | Adhesive and Foam | | | Release Liner | | | |
|----------------|--------|-------------------|---|--------------------|-----------|---------------------------|---------------|--------------------------|-----------------|-------|
| Family | Number | Color | Tape Thickness Inches (mm) Tolerance | Adhesive Type | Foam Type | Density lb/ft³ (kg/m³) | Type | Thickness Inches (mm) | Color | |
| 4941 | 4919F | Black | 0.025 (0.6) ± 15% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | 4926 | Gray | 0.015 (0.4) ± 15% | Multi-Purp | Conform | 45 (720) | Dk Paper | 0.003 (0.08) | White (printed) | |
| | 4936 | Gray | 0.025 (0.6) ± 15% | Multi-Purp | Conform | 45 (720) | Dk Paper | 0.003 (0.08) | White (printed) | |
| | 4936F | Gray | 0.025 (0.6) ± 15% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | 4941 | Gray | 0.045 (1.1) ± 10% | Multi-Purp | Conform | 45 (720) | Dk Paper | 0.003 (0.08) | White (printed) | |
| | 4941F | Gray | 0.045 (1.1) ± 10% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red | |
| | 4947F | Black | 0.045 (1.1) ± 10% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | 4956 | Gray | 0.062 (1.6) ± 10% | Multi-Purp | Conform | 45 (720) | Dk Paper | 0.003 (0.08) | White (printed) | |
| | 4956F | Gray | 0.062 (1.6) ± 10% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | 4979F | Black | 0.062 (1.6) ± 10% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | 4991 | Gray | 0.090 (2.3) ± 10% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | 4991B | Black | 0.090 (2.3) ± 10% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | 5952 | 5906 | Black | 0.006 (0.15) ± 15% | Modified | Very Conf | 45 (720) | PET | 0.003 (0.08) | Clear |
| | | 5907 | Black | 0.008 (0.20) ± 15% | Modified | Very Conf | 45 (720) | PET | 0.003 (0.08) | Clear |
| 5908 | | Black | 0.010 (0.25) ± 15% | Modified | Very Conf | 45 (720) | PET | 0.003 (0.08) | Clear | |
| 5909 | | Black | 0.012 (0.30) ± 15% | Modified | Very Conf | 45 (720) | PET | 0.003 (0.08) | Clear | |
| 5915 | | Black | 0.016 (0.4) ± 15% | Modified | Very Conf | 43 (690) | PE Film | 0.005 (0.13) | Red (printed) | |
| 5915P | | Black | 0.016 (0.4) ± 15% | Modified | Very Conf | 43 (690) | PCK Paper | 0.004 (0.10) | White (printed) | |
| 5915WF | | White | 0.016 (0.4) ± 15% | Modified | Very Conf | 43 (690) | PE Film | 0.005 (0.13) | Red (printed) | |
| 5925 | | Black | 0.025 (0.6) ± 15% | Modified | Very Conf | 37 (590) | PE Film | 0.005 (0.13) | Red (printed) | |
| 5925P | | Black | 0.025 (0.6) ± 15% | Modified | Very Conf | 37 (590) | PCK Paper | 0.004 (0.10) | White (printed) | |
| 5925WF | | White | 0.025 (0.6) ± 15% | Modified | Very Conf | 37 (590) | PE Film | 0.005 (0.13) | Red (printed) | |
| 5930 | | Black | 0.032 (0.8) ± 15% | Modified | Very Conf | 37 (590) | PE Film | 0.005 (0.13) | Red (printed) | |
| 5930P | | Black | 0.032 (0.8) ± 15% | Modified | Very Conf | 37 (590) | PCK Paper | 0.004 (0.10) | White (printed) | |
| 5930WF | | White | 0.032 (0.8) ± 15% | Modified | Very Conf | 37 (590) | PE Film | 0.005 (0.13) | Red (printed) | |
| 5952 | | Black | 0.045 (1.1) ± 10% | Modified | Very Conf | 37 (590) | PE Film | 0.005 (0.13) | Red (printed) | |
| 5952P | | Black | 0.045 (1.1) ± 10% | Modified | Very Conf | 37 (590) | PCK Paper | 0.004 (0.10) | White (printed) | |
| 5952WF | | White | 0.045 (1.1) ± 10% | Modified | Very Conf | 37 (590) | PE Film | 0.005 (0.13) | Red (printed) | |
| 5958FR | | Black | 0.040 (1.0) ± 10% | Modified | Very Conf | 50 (800) | PE Film | 0.005 (0.13) | Red (printed) | |
| 5962 | | Black | 0.062 (1.6) ± 10% | Modified | Very Conf | 37 (590) | PE Film | 0.005 (0.13) | Red (printed) | |
| 5962P | Black | 0.062 (1.6) ± 10% | Modified | Very Conf | 37 (590) | PCK Paper | 0.004 (0.10) | White (printed) | | |
| 5962WF | White | 0.062 (1.6) ± 10% | Modified | Very Conf | 37 (590) | PE Film | 0.005 (0.13) | Red (printed) | | |
| RP | RP16 | Gray | 0.016 (0.4) ± 15% | Multi-Purp | Conform | 45 (720) | Dk Paper | 0.003 (0.08) | White (printed) | |
| | RP16F | Gray | 0.016 (0.4) ± 15% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | RP25 | Gray | 0.025 (0.6) ± 15% | Multi-Purp | Conform | 45 (720) | Dk Paper | 0.003 (0.08) | White (printed) | |
| | RP25F | Gray | 0.025 (0.6) ± 15% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | RP32 | Gray | 0.032 (0.8) ± 15% | Multi-Purp | Conform | 45 (720) | Dk Paper | 0.003 (0.08) | White (printed) | |
| | RP32F | Gray | 0.032 (0.8) ± 15% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | RP45 | Gray | 0.045 (1.1) ± 10% | Multi-Purp | Conform | 45 (720) | Dk Paper | 0.003 (0.08) | White (printed) | |
| | RP45F | Gray | 0.045 (1.1) ± 10% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |
| | RP62 | Gray | 0.062 (1.6) ± 10% | Multi-Purp | Conform | 45 (720) | Dk Paper | 0.003 (0.08) | White (printed) | |
| | RP62F | Gray | 0.062 (1.6) ± 10% | Multi-Purp | Conform | 45 (720) | PE Film | 0.005 (0.13) | Red (printed) | |

Available Sizes

| Tape Thickness inches (mm) | Standard Length yards (meters) | Minimum Width inches (mm) | Maximum Width inches (mm) | Maximum Roll Length | | |
|-------------------------------|-----------------------------------|------------------------------|------------------------------|--|---|--|
| | | | | Width 1/4" up to 3/8" (6.4mm up to 9.5mm) yards (meters) | Width >3/8" up to 1/2" (>9.5mm up to 12.7mm) yards (meters) | Width 1/2" and wider (12.7mm and wider) yards (meters) |
| < 0.015 (0.4) | 72 (65.8) | 0.5 (13) | 46 (1168) | N/A N/A | N/A N/A | See Note Below |
| 0.015/0.016 (0.4) | 72 (65.8) | 0.25 (6) | 48* (1219) | 144 (131.7) | 175 (160.0) | 360 (329.2) |
| 0.025 (0.6) | 72 (65.8) | 0.25 (6) | 48* (1219) | 72 (65.8) | 108 (98.8) | 175 (160.0) |
| 0.032 (0.8) | 72 (65.8) | 0.25 (6) | 48 (1219) | 72 (65.8) | 108 (98.8) | 175 (160.0) |
| 0.040 (1.0) | 36 (32.9) | 0.25 (6) | 48 (1219) | 72 (65.8) | 108 (98.8) | 144 (131.7) |
| 0.045 (1.1) | 36 (32.9) | 0.25 (6) | 48 (1219) | 72 (65.8) | 108 (98.8) | 144 (131.7) |
| 0.062 (1.6) | 36 (32.9) | 0.25 (6) | 46 (1168) | 72 (65.8) | 72 (65.8) | 108 (98.8) |
| 0.090 (2.3) | 36 (32.9) | 0.25 (6) | 46 (1168) | 36 (32.9) | 36 (32.9) | 72 (65.8) |

*Exception – 5915 (P) max. width 46 inches (1168 mm); 5925 (P) max. width 47 inches (1194 mm).

Note: 5952 family tapes thinner than 0.015 in (0.4 mm) have max. length 360 yd (329.2 m) for widths 1 in (25 mm) to 8 in (203 mm) and 180 yd (164.6 m) for all other widths.

Slitting Tolerance

Standard slitting tolerance ± 1/32 inch (± 0.031 inch, ± 0.79 mm).

Precision slitting with slitting tolerance of ± 1/64 inch (± 0.016 in., ± 0.41 mm) is available on select products with minimum order of full web increments.

Core Size

All products are provided on a 3 inch ID Core (76.2 mm)

Converted Parts

In addition to standard and custom roll sizes available from 3M through the distribution network, 3M™ VHB™ Tapes are also available in limitless shapes and sizes through the 3M Converter network. For additional information, contact 3M Converter Markets at 1-800-223-7427 or on the web at www.3M.com/converter.

Shelf Life

All 3M™ VHB™ Tapes have a shelf life of 24 months from date of manufacture when stored at 40°F to 100°F (4°C to 38°C) and 0-95% relative humidity. The optimum storage conditions are 72°F (22°C) and 50% relative humidity.

Performance of tapes is not projected to change even after shelf life expires; however, 3M does suggest that 3M™ VHB™ Tapes are used prior to the shelf life date whenever possible.

The manufacturing date is available on all 3M™ VHB™ Tape cores as the lot number. The lot number, typically a 4 digit code, is a Julian date (Y D D D). The first digit refers to the year of manufacture, the last 3 digits refer to the days after January 1. Example: A lot number of 9266 would translate to a date of manufacture of Sept. 22 (266th day of year) in 2009. On most products this is found as the 4 digits after the “9” following the product number. For tapes printed continuously around the core (e.g. 3M™ VHB™ Tape 5952 family) the lot number typically will be the string of 4 digits preceding the product number.

Special Cases:

Plasticized Vinyl – Plasticizers compounded in soft vinyl can migrate into adhesives and significantly change their performance characteristics. 3M™ VHB™ Tapes 4941 family has very good plasticizer resistance and adhesion to many vinyl formulations. Because of the wide variation in vinyl formulations, however, evaluation by the user must be conducted with the specific vinyl used to ensure that performance will be satisfactory over time. Problems related to plasticizer migration can often be predicted by accelerated aging of assembled parts at 150°F (66°C) for one week).

Typical Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

| 3M™ VHB™ Tapes | | | | Dynamic Adhesion Performance | | |
|----------------|----------------|-------|------------------|---------------------------------|--|---|
| Family | Product Number | Color | Thickness Inches | 90° Peel Adhesion lb/in N/cm | Normal Tensile lb/in ² kPa | Dynamic Overlap Shear lb/in ² kPa |
| 4941 | 4919F | Black | 0.025 | 17 (30) | 90 (620) | 80 (550) |
| | 4926 | Gray | 0.015 | 14 (25) | 95 (660) | 90 (620) |
| | 4936(F) | Gray | 0.025 | 17 (30) | 90 (620) | 80 (550) |
| | 4941(F) | Gray | 0.045 | 22 (39) | 85 (590) | 70 (480) |
| | 4947F | Black | 0.045 | 22 (39) | 85 (590) | 70 (480) |
| | 4956(F) | Gray | 0.062 | 22 (39) | 80 (550) | 70 (480) |
| | 4979F | Black | 0.062 | 22 (39) | 80 (550) | 70 (480) |
| | 4991 | Gray | 0.090 | 22 (39) | 70 (480) | 65 (450) |
| | 4991B | Black | 0.090 | 22 (39) | 70 (480) | 65 (450) |
| 5952 | 5906 | Black | 0.006 | 9 (16) | 100 (690) | 100 (690) |
| | 5907 | Black | 0.008 | 10 (18) | 100 (690) | 100 (690) |
| | 5908 | Black | 0.010 | 12 (21) | 100 (690) | 100 (690) |
| | 5909 | Black | 0.012 | 12 (21) | 100 (690) | 100 (690) |
| | 5915(P) | Black | 0.016 | 14 (25) | 90 (620) | 90 (620) |
| | 5915WF | White | 0.016 | 14 (25) | 90 (620) | 90 (620) |
| | 5925(P) | Black | 0.025 | 17 (30) | 90 (620) | 90 (620) |
| | 5925WF | White | 0.025 | 17 (30) | 90 (620) | 90 (620) |
| | 5930(P) | White | 0.032 | 19 (33) | 90 (620) | 85 (590) |
| | 5930WF | Black | 0.032 | 19 (33) | 90 (620) | 85 (590) |
| | 5952(P) | Black | 0.045 | 22 (39) | 90 (620) | 80 (550) |
| | 5952WF | White | 0.045 | 22 (39) | 90 (620) | 80 (550) |
| | 5958FR | Black | 0.040 | 20 (35) | 100 (690) | 100 (690) |
| | 5962(P) | Black | 0.062 | 22 (39) | 90 (620) | 80 (550) |
| | 5962WF | White | 0.062 | 22 (39) | 90 (620) | 80 (550) |
| RP | RP16(F) | Gray | 0.016 | 12 (21) | 95 (660) | 90 (620) |
| | RP25(F) | Gray | 0.025 | 17 (30) | 90 (620) | 80 (550) |
| | RP32(F) | Gray | 0.032 | 18 (32) | 85 (590) | 75 (520) |
| | RP45(F) | Gray | 0.045 | 20 (35) | 85 (590) | 70 (480) |
| | RP62(F) | Gray | 0.062 | 20 (35) | 80 (550) | 70 (480) |



90° Peel Adhesion - Based on ASTM D3330 - To stainless steel, room temperature, jaw speed 12 in/min (304.8 mm/min). Average force to remove is measured. 72 hour dwell.



Normal Tensile (T-Block Tensile) - ASTM D-897 - To aluminum, room temperature, 1 in² (6.45 cm²), jaw speed 2 in/min (50.8 mm/min) Peak force to separate is measured. 72 hour dwell.



Dynamic Overlap Shear - ASTM D-1002 - To stainless steel, room temperature, 1 in² (6.45 cm²), jaw speed 0.5 in/min (12.7 mm/min) Peak force to separate is measured. 72 hour dwell.

Typical Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

| 3M™ VHB™ Tapes | | | | Static Shear | | | | Temperature Tolerance | |
|----------------|----------------|-------|------------------|--------------|--------------|--------------|---------------|-------------------------------------|---------------------------------|
| Family | Product Number | Color | Thickness Inches | 72°F (22°C) | 150°F (66°C) | 200°F (93°C) | 250°F (121°C) | Short Term (Minutes, Hours) °F (°C) | Long Term (Days, Weeks) °F (°C) |
| 4941 | 4919F | Black | 0.025 | 1000 | 500 | 500 | | 300 (149) | 200 (93) |
| | 4926 | Gray | 0.015 | 1000 | 500 | 500 | | 300 (149) | 200 (93) |
| | 4936(F) | Gray | 0.025 | 1000 | 500 | 500 | | 300 (149) | 200 (93) |
| | 4941(F) | Gray | 0.045 | 1000 | 500 | 500 | | 300 (149) | 200 (93) |
| | 4947F | Black | 0.045 | 1000 | 500 | 500 | | 300 (149) | 200 (93) |
| | 4956(F) | Gray | 0.062 | 1000 | 500 | 500 | | 300 (149) | 200 (93) |
| | 4979F | Black | 0.062 | 1000 | 500 | 500 | | 300 (149) | 200 (93) |
| | 4991 | Gray | 0.090 | 1000 | 500 | 500 | | 250 (121) | 200 (93) |
| | 4991B | Black | 0.090 | 1000 | 500 | 500 | | 250 (121) | 200 (93) |
| 5952 | 5906 | Black | 0.006 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5907 | Black | 0.008 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5908 | Black | 0.010 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5909 | Black | 0.012 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5915(P) | Black | 0.016 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5915WF | White | 0.016 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5925(P) | Black | 0.025 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5925WF | Black | 0.032 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5930(P) | Black | 0.032 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5930WF | White | 0.032 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5952(P) | Black | 0.045 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5952WF | White | 0.045 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5958FR | Black | 0.040 | 1000 | 350 | 250 | | 300 (149) | 200 (93) |
| | 5962(P) | Black | 0.062 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| | 5962WF | White | 0.062 | 1000 | 500 | 500 | 250 | 300 (149) | 250 (121) |
| RP | RP16(F) | Gray | 0.016 | 1000 | 500 | 500 | | 250 (121) | 200 (93) |
| | RP25(F) | Gray | 0.025 | 1000 | 500 | 500 | | 250 (121) | 200 (93) |
| | RP32(F) | Gray | 0.032 | 1000 | 500 | 500 | | 250 (121) | 200 (93) |
| | RP45(F) | Gray | 0.045 | 1000 | 500 | 500 | | 250 (121) | 200 (93) |
| | RP62(F) | Gray | 0.062 | 1000 | 500 | 500 | | 250 (121) | 200 (93) |

Static Shear - ASTM D3654 - To stainless steel, tested at various temperatures and gram loadings. 0.5 in² (3.23 cm²). Will hold listed weight for 10,000 minutes (approximately 7 days). Conversion: 1500 g/0.5 in² equals 6.6 lb/in²; 500 g/0.5 in² = 2.2 lb/in².

Short Term Temperature Tolerance - No change in room temperature dynamic shear properties following 4 hours conditioning at indicated temperature with 100 g/static load. (Represents minutes, hours in a process type temperature exposure).

Long Term Temperature Tolerance - Maximum temperature where tape supports at least 250 g load per 0.5 in² in static shear for 10,000 minutes. (Represents continuous exposure for days or weeks).

Additional Typical Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.


| | 3M™ VHB™ Tape | | Units | Test Standard |
|---------------------------------------|------------------------|------------------------|---|----------------------------|
| | 4941 | 5952 | | |
| Dielectric Constant | 2.29 | 2.14 | at 1 kHz | ASTM D150 |
| | 1.99 | 1.95 | at 1MHz | ASTM D150 |
| Dissipation Factor | 0.0245 | 0.0065 | at 1 kHz | ASTM D150 |
| | 0.0374 | 0.0506 | at 1MHz | ASTM D150 |
| Dielectric Breakdown Strength | 14 (360) | 18 (455) | V/μm (V/mil) | ASTM D140 |
| Thermal Conductivity (k value) | 0.08 (0.5) | 0.05 (0.4) | W/mK (BTU•in/hr•ft²•°F) | |
| Volume Resisitivity | 2.1 x 10 ¹⁴ | 2.5 x 10 ¹⁴ | Ω-cm | ASTM D257 |
| Surface Resisitivity | 2.7 x 10 ¹⁴ | >10 ¹⁶ | Ω/sq | ASTM D257 |
| Water Vapor Transmission Rate | 25.6 | 37.1 | g/m²•day | ASTM F1249 at 38°C/100% RH |
| Thermal Properties of Modeling | | | | |
| Thermal Coefficient of Expansion | 180 (100) | | 10 ⁻⁶ m/m/°C (10 ⁻⁶ in/in/°F) | |
| Shear Modulus (at 25°C, 1 Hz) | 3 x 10 ⁵ | | Pa | |

**3M™ VHB™ Tapes
UL746C Listings - File MH 17478**
Category Q0QW2 Component - Polymeric Adhesive Systems, Electrical Equipment

| 3M™ VHB™ Tapes/ Product Families | Substrates | Temperature Rating | |
|---|--|--------------------|---------|
| | | Minimum | Maximum |
| 4919F, 4926, 4936, 4936F, 4941, 4941F, 4947F, 4956, 4956F, 4979F | Ceramic | -35°C | 110°C |
| | Aluminum, Galvanized Steel, Stainless Steel, Enameled Steel, Nickel Coated ABS, Glass (with or without Silane Coating) PVC, Glass/Epoxy, PBT, Polycarbonate, Acrylic/Polyurethane Paint, Polyester Paint | -35°C | 90°C |
| 4991 | ABS | -35°C | 75°C |
| | Polycarbonate, Aluminum, Acrylic/ Polyurethane Paint, Polyester Paint | -35° | 90°C |
| 5915, 5915P, 5915WF, 5925, 5925P, 5925WF, 5930, 5030P, 5930WF, 5952, 5952P, 5952WF, 5962, 5962P, 5962WF | Polycarbonate, Primer 94 Coated Polycarbonate, Aluminum, Acrylic/ Polyurethane Paint, Galvanized Steel, Polyester Paint, Epoxy Paint, Silane Coated Glass, Uncoated Glass, Stainless Steel, Enameled Steel, Glass Epoxy, Polybutylene Terephthalate, Nylon, Polyphenelene Ether (PPE), Acrylic | -35°C | 90°C |
| | Rigid PVC, ABS | -35°C | 75°C |
| 5952, 5952P, 5952WF | Cellulose Acetate Butyrate | -35°C | 90°C |
| RP16 | Aluminum, Silane Coated Glass | -35°C | 90°C |
| | PVC, ABS | -35°C | 75°C |
| RP16, RP25, RP32, RP45, RP62 | Galvanized Steel, Enameled Steel, Nylon, Polycarbonate, Glass Epoxy, Phenolic, PPE/PS Blend, PBT, Epoxy Paint, Polyester Paint, Adhesion Promoter 111 Coated Epoxy Paint, Promoter 111 Coated Polyester Paint, Acrylic Urethane Paint, Epoxy/ Polyester Paint | -35°C | 90°C |
| | Stainless Steel, Glass, Acrylic | -35°C | 90°C |
| RP62 | PVC, ABS | -35°C | 75°C |

A current list can be found at www.ul.com (select certifications, search file MH17478)

Solvent and Fuel Resistance



Test Method

- Tape between stainless steel and aluminum foil
- 72 hours dwell at room temperature
- Solvent immersion for 72 hours
- Test within 45 minutes after removing from solvent
- 90° peel angle
- 12 in/min rate of peel
- Peel adhesion compared to control

Note: Continuous submersion in chemical solutions is not recommended. The above information is presented to show that occasional chemical contact should not be detrimental to tape performance in most applications in ordinary use.

Burn Characteristics 3M™ VHB™ Tape 5958FR


- Meets FAR 25.853 (a) 12 second vertical burn, Appendix F, Part I (a)(ii)
- Meets NBS Smoking Density (ASTM F814/E662)
- Meets Toxicity (Draeger Tube ABD0031, AITM 3.0005)

Design and Tape Selection Considerations

- **Choose the right tape for the substrate:** Adhesives must flow onto the substrate surfaces in order to achieve intimate contact area and allow the molecular force of attraction to develop. The degree of flow of the adhesive on the substrate is largely determined by the surface energy of the substrate.



This illustration demonstrates the effect of surface energy on adhesive interfacial contact. High surface energy materials draw the adhesive closer for high bond strength.



NOTES: There are a wide variety of formulations, surfaces finishes and surface treatments available on substrate materials which can affect adhesion. This chart is intended to provide only a rough estimate of the adhesion levels which can be expected on some common materials relative to a reference surface such as aluminum. Foam type can affect and/or limit maximum adhesive strength.

- **Use the right tape thickness:** The necessary thickness of tape depends on the rigidity of substrates and their flatness irregularity. While the 3M™ VHB™ Tapes will conform to a certain amount of irregularity, they will not flow to fill gaps between the materials. For bonding rigid materials with normal flatness, consider use of tapes with thickness of 45 mils (1.1 mm) or greater. As the substrate flexibility increases thinner tapes can be considered.
- **Use the right amount of tape:** Because 3M™ VHB™ Tapes are viscoelastic by nature their strength and stiffness is a function of the rate at which they are stressed. They behave stronger with relatively faster rate of stress load (dynamic stresses) and will tend to show creep behavior with stress load acting over a long period of time (static stresses). As a general rule, for **static loads**, approximately four square inches of tape should be used for each pound (57 cm² of tape per kg) of weight to be supported in order to prevent excessive creep. For **dynamic loads**, the dynamic performance characteristics provided on page 4 should be useful, factoring in the appropriate safety factors.
- **Allow for thermal expansion/contraction:** 3M™ VHB™ Tapes can perform well in applications where two bonded surfaces may expand and contract differentially. Assuming good adhesion to the substrates, the tapes can typically tolerate differential movement in the shear plane up to 3 times their thickness.
- **Bond Flexibility:** While an advantage for many applications where allowing differential movement is a benefit, the tape bonds are typically more flexible than alternative bonding methods. Suitable design modifications or periodic use of rigid fasteners or adhesives may be needed if additional stiffness is required.
- **Severe Cold Temperature:** Applications which require performance at severe cold temperatures must be thoroughly evaluated by the user if the intended use will subject the tape product to high impact stresses. A technical bulletin “3M™ VHB™ Tape Cold Temperature Performance” (70-0707-3991-0) is available for additional information.

Application Techniques

► **Clean:** Most substrates are best prepared by cleaning with a 50:50 mixture of isopropyl alcohol (IPA*) and water prior to applying 3M™ VHB™ Tapes.

Exceptions to the general procedure that may require additional surface preparation include:

- **Heavy Oils:** A degreaser or solvent-based cleaner may be required to remove heavy oil or grease from a surface and should be followed by cleaning with IPA/water.
- **Abrasion:** Abrading a surface, followed by cleaning with IPA/water, can remove heavy dirt or oxidation and can increase surface area to improve adhesion.
- **Adhesion Promoters:** Priming a surface can significantly improve initial and ultimate adhesion to many materials such as plastics and paints.
- **Porous surfaces:** Most porous and fibered materials such as wood, particleboard, concrete, etc. need to be sealed to provide a unified surface.
- **Unique Materials:** Special surface preparation may be needed for glass and glass-like materials, copper and copper containing metals, and plastics or rubber that contain components that migrate (e.g. plasticizers).

Refer to 3M Technical Bulletin “Surface Preparation for 3M™ VHB™ Tape Applications” for additional details and suggestions. (70-0704-8701-5)

***Note:** These cleaner solutions contain greater than 250 g/l of volatile organic compounds (VOC). Please consult your local Air Quality Regulations to be sure the cleaner is compliant. When using solvents, be sure to follow the manufacturer’s precautions and directions for use when handling such materials.

► **Pressure:** Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact and helps improve bond strength. Typically, good surface contact can be attained by applying enough pressure to insure that the tape experiences approximately 15 psi (100 kPa) pressure. Either roller or platen pressure can be used. Note that rigid surfaces may require 2 or 3 times that much pressure to make the tape experience 15 psi.

► **Temperature:** Ideal application temperature range is 70°F to 100°F (21°C to 38°C). Pressure sensitive adhesives use viscous flow to achieve substrate contact area. Minimum suggested application temperatures:


- 50°F (10°C): 3M™ VHB™ Tapes 5952 and RP families.
- 60°F (15°C): 3M™ VHB™ Tape 4941 family.

Note: Initial tape application to surfaces at temperatures below these suggested minimums is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

To obtain good performance with all 3M™ VHB™ Tapes, it is important to ensure that the surfaces are dry and free of condensed moisture.

► **Time:** After application, the bond strength will increase as the adhesive flows onto the surface (also referred to as “wet out”). At room temperature approximately 50% of ultimate bond strength will be achieved after 20 minutes, 90% after 24 hours and 100% after 72 hours. This flow is faster at higher temperatures and slower at lower temperatures. Ultimate bond strength can be achieved more quickly (and in some cases bond strength can be increased) by exposure of the bond to elevated temperatures (e.g. 150°F [66°C] for 1 hour). This can provide better adhesive wetout onto the substrates. Abrasion of the surfaces or the use of primers/ adhesion promoters can also have the effect of increasing bond strength and achieving ultimate bond strength more quickly.

Bond Typical Build vs. Time



Technical Information

The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer

3M warrants for 24 months from the date of manufacture that 3M™ VHB™ Tape will be free of defects in material and manufacture. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. This warranty does not cover damage resulting from the use or inability to use 3M™ VHB™ Tape due to misuse, workmanship in application, or application or storage not in accordance with 3M recommended procedures (except to the extent 3M approves and issues a specific application warranty, for which the customer must apply, receive 3M approval, and meet all applicable warranty and process requirements, the additional details, terms, and conditions of which are available from 3M). If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

ISO 9001

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

**Industrial Adhesives and Tapes Division**

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-362-3550 • 877-369-2923 (Fax)
www.3M.com/vhb

3M and VHB are trademarks of 3M Company.
Printed in U.S.A.
©3M 2018 70070938637 (10/18)

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [Adhesive Tapes](#) category:

Click to view products by [3M](#) manufacturer:

Other Similar products are found below :

[PF24.0W](#) [4718](#) [4516-1/4x36](#) [56-YELLOW-34"X72YD](#) [00-021200-13972-7](#) [021200-64630](#) [60 TAPE \(1"\)](#) [62-GRAY-12"X36YD](#) [62-GRAY-1"X36YD](#) [69-1"X36YD](#) [764-1"x36yd-Red](#) [764-1"x36yd-White](#) [PG ASSY](#) [926-1/4X18YD](#) [967454-1](#) [1194-14"X36YD](#) [1181 19MM X 16,5 METERS](#) [1182-7.7X10](#) [1245-34"X18YD](#) [1267](#) [130C-1X15FT](#) [130-1x10FT](#) [1345-3/8x18yrd](#) [1380-2"X8"](#) [E39-RS1-CA](#) [1900-48mm](#) [22-1/2X36YD](#) [2229-P-2-1/2x3-3/4](#) [88-SUPER-34X44FT](#) [890103N001](#) [2670](#) [SJ3527N-Black-1.5"x50yd](#) [EVK-TA-TM047NBH01](#) [AD-UCUSB-DCAUD-SPL](#) [20-1"X60YDS](#) [2020-18mmx55m](#) [H150](#) [3900-Blue](#) [3939-24mmx55m](#) [396-1"x36yd](#) [4016-34"x36yd](#) [4462W-12"x72yd](#) [44-TAN-14"X90YD](#) [4504-34x18](#) [471-Trans-1"x36yd-Bulk](#) [5414 34X36](#) [C-22](#) [35-Gray-1/2](#) [371-Tan-48mmx50m](#) [4008-12"X36YD](#)