


# TECHNICAL DATA SHEET **GTI 3000**

Base material Polyolefin

Colour Clear, Black, Red, Yellow,

Blue, White, Green/Yellow striped

Environmental RoHS compliant



## **Typical Properties**

Physical	Value	Unit	Requirement	Test Method	
Shrink ratio	3:1				
Tensile strength	25	N/mm <sup>2</sup>	> 10	IEC 60684-2-19.1	
Elongation at break	540	%	> 250	IEC 60684-2-19.2	
Longitudinal change	-5 - 0	%	- 10 <> + 5	IEC 60684-2-9	
Concentricity supplied (total wall)	80	%	> 65	IEC 60684-2-3	
Concentricity fully recovered (outer wall)	90	%	> 85	IEC 60684-2-3	
Secant Modulus	80	N/mm <sup>2</sup>	50 <> 175	IEC 60684-2-19.4	
Relative Density	0.92	g/cm³	-	IEC 60684-2-4	

Thermal	Value	Unit	Requirement	Test Method
Continuous Operating Temperature	-55 <> 135	å		
Shrink Temperature	135 <> 280	°C		
Heat Shock			4 hrs @ 200 °C	IEC 60684-2-6
Tensile strength	25	N/mm <sup>2</sup>	> 10	IEC 60684-2-19
Elongation at break	540	%	> 200	IEC 60684-2-19
Low Temperature Flexibility	Pass		4hr @ -55 °C	IEC 60684-2-14
			No cracking after bending	
Copper Corrosion	Pass	No corrosion		IEC 60684-2-33
Flammability	Not self extinguishing		method C (30s, 75mm)	IEC 60684-2-26

Electrical	Value	Unit Requirement		Test Method	
Volume resistivity	10 <sup>14</sup>	Ω.m	> 10 <sup>12</sup> @ room temp.	IEC 60684-2-23	
Breakdown Voltage	34	kV.mm	> 21	IEC 60684-2-21	

Chemical	Value	Unit	Requirement	Test Method
Selected fluids according to table 5 of IEC 60684-3-212 @ 23 °C, 24 hrs	pass	N/mm <sup>2</sup> / %	Tensile/ elongation > 7 / > 200	IEC 60684-2-36

#### Important note to the purchaser.

Technical Information provided consists of typical product data and should not be used for specification purposes. Unless otherwise specified in the test method, all tests are performed at room temperature.

All statements, technical information and recommendations contained herein are based on tests 3M believes to be reliable, but their accuracy and completeness are not guaranteed. The user shall be responsible for determining the suitability of the products for his particular application. To discuss your application requirements please contact your representative



# **TECHNICAL DATA SHEET GTI 3000**

#### **Documentation**

#### **Product Guide - Table 1**

Part Number	Expanded ID (min.)	Recovered ID (max.)	Recovered Wall Thickness (nominal)
	[mm]	[mm]	` [mm] <sup>′</sup>
1.5	1.5	0.5	0.45
3.0	3.0	1.0	0.55
6.0	6.0	2.0	0.65
9.0	9.0	3.0	0.75
12.0	12.0	4.0	0.75
18.0	18.0	6.0	0.75
24.0	24.0	8.0	1.00
39.0	39.0	13.0	1.15

### **Storage Conditions**

Temperature:

min. -50  $^{\circ}$ C max. +50  $^{\circ}$ C

Moisture: max. 75 %

Important note to the purchaser.

Technical Information provided consists of typical product data and should not be used for specification purposes. Unless otherwise specified in the test method, all tests are performed at room temperature.

All statements, technical information and recommendations contained herein are based on tests 3M believes to be reliable, but their accuracy and completeness are not guaranteed. The user shall be responsible for determining the suitability of the products for his particular application. To discuss your application requirements please contact your representative

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Heat Shrink Tubing and Sleeves category:

Click to view products by 3M manufacturer:

Other Similar products are found below:

770-006S102 5685710001 CR8248-000 CR9960-000 603312-4 607381P039 611112-000 617867N001 6500750004 CZ1420-000 D-306-38
770-007A303 770-010Y106W1 770-010Y706W1 7771210001 MFP-1/4"-Clear MFP-3/64"-Clear 790-3012 MFT-MT2000-NO.14-0-SP
MHHT-4-15K2-G-104 MIL-LT-1-1/2-4-SP MIL-LT-1-1/2-9-STK MIL-LT-1/2-2-STK MIL-LT-3/0-SP MIL-LT-3/32-0-SP MIL-LT-3/32-6-SP MIL-LT-3/4-6-SP MIL-LT-3/8-0-SP 8159270001 839602-000 8423-6 FP301-116-6"-Black FP301-1/2-48"-Black FP301-12-48"-Black FP301-1/4-48"-Black FP301-1/4-48"-White-Hdr FP301-1-6"-Clear FP301-18-48"-Black-Hdr FP301-1/8-6"-Black FP301-18-6"-Black FP301-316-48"-Black FP301-316-6"-Clear FP301-332-6"-Black 912229N002 120-126-16BL 121-001-09 121-018-32 121-018-40
121-123-1-1-32BTC 121-123-1-1-40BTC