3M™ EMI Tin-Plated Copper Foil Shielding Tape 1183 with Electrically Conductive Acrylic Adhesive

Data Sheet

Product Description	3M™ EMI Tin-Plated Copper Foil Shielding Tape 1183 is a 2.66-mil (0.068 mm) thick tape composed of a 1.4-mil (0.036 mm) tin-plated flat copper foil backing coated on one side with a non-corrosive, electrically conductive acrylic pressure-sensitive adhesive supplied on a removeable liner.
	 Commonly used for EMI/RFI shielding applications in the electronics industry and for static charge draining, seaming shielded rooms, cable wrapping and surface contact to non-solderable materials
	 Can be die-cut, is solderable and offers a multitude of uses in electrical design and test laboratories for prototyping, design and troubleshooting
	 Adhesive requires no moisture, solvents, heat or other manner of preparation to affect application
	Flame Retardant per UL-510A Standard

Physical Properties	Value Imperial (Metric)	Electrical Properties	Value Imperial (Metric)
Color - Visual	Matte Tin	Electrical Resistance ⁴ - Maximum	0.005 Ω/in ²
Adhesive	Electrically Conductive Acry	lic Shielding Effectiveness ³ - Average 300 kHz – 2.5 GHz	68 dB
Backing	Tin Pated Copper Foil - Fla	t	
Flame Retardant ²	Pass		
Mechanical Propertie	s Value Imperial (Metric)		
Backing Thickness - Nom	nal 1.4 mil (0.036 mm)		
Total Thickness ¹	2.66 +/- 0.14 mils (0.068 +/- 0.004 mm)		
Adhesion to Steel ¹ - Minir	25 oz/in (2.7 N/cm)		
Breaking Strength ¹ - Mini	num 18 lb/in (32 N/cm)		
 ASTM D4935 Test N Test Method: MIL-S a. Silver coated gl 	TD-202 Method 307 maintained at 5 psi (3. ss beads embedded in acrylic adhesive pro	perature 73°F (23°C) unless otherwise stated 4 N/cm ²) measured over a 1 in ² surface area ovide the electrical path between application substra	-
 ASTM D4935 Test N Test Method: MIL-S 	Method - properties measured at room temp TD-202 Method 307 maintained at 5 psi (3. Iss beads embedded in acrylic adhesive pro Many factors determine the true	perature 73°F (23°C) unless otherwise stated 4 N/cm ²) measured over a 1 in ² surface area ovide the electrical path between application substra e shielding effectiveness of a shielding ta , intimacy of contact, smoothness of app	pe, including type and
 ASTM D4935 Test M Test Method: MIL-S a. Silver coated gl 	Aethod - properties measured at room temp TD-202 Method 307 maintained at 5 psi (3. ass beads embedded in acrylic adhesive pro Many factors determine the true thickness of foil, adhesive type, frequency of the EMI signal, etc • UL Component Recognized:	perature 73°F (23°C) unless otherwise stated 4 N/cm ²) measured over a 1 in ² surface area ovide the electrical path between application substra e shielding effectiveness of a shielding ta , intimacy of contact, smoothness of app	pe, including type and ication surface, e No. E17385
 ASTM D4935 Test M Test Method: MIL-S a. Silver coated gl Shielding Effectiveness Agency Approvals &	Aethod - properties measured at room temp TD-202 Method 307 maintained at 5 psi (3. ass beads embedded in acrylic adhesive pro Many factors determine the true thickness of foil, adhesive type, frequency of the EMI signal, etc • UL Component Recognized: • For Regulatory information in This product has a 5-year shelf	berature 73°F (23°C) unless otherwise stated 4 N/cm ²) measured over a 1 in ² surface area ovide the electrical path between application substra- e shielding effectiveness of a shielding ta intimacy of contact, smoothness of appl c.	pe, including type and ication surface, e No. E17385 w.3M.com/regs red in humidity-
 ASTM D4935 Test M Test Method: MIL-S a. Silver coated gl Shielding Effectiveness Agency Approvals & Self Certifications 	 Method - properties measured at room temp TD-202 Method 307 maintained at 5 psi (3. ass beads embedded in acrylic adhesive pro- Many factors determine the true thickness of foil, adhesive type, frequency of the EMI signal, etc UL Component Recognized: For Regulatory information in This product has a 5-year shelf controlled storage (50°F/10°C 	berature 73°F (23°C) unless otherwise stated 4 N/cm ²) measured over a 1 in ² surface area ovide the electrical path between application substra- e shielding effectiveness of a shielding ta intimacy of contact, smoothness of application UL510A Standard, Category OARC2, Fincluding RoHS, REACH, please visit www life (from date of manufacture) when sto	pe, including type and ication surface, e No. E17385 w.3M.com/regs red in humidity- /).

Properties

3M[™] EMI Tin-Plated Copper Foil Shielding Tape 1183 with Electrically Conductive Acrylic Adhesive

TECHNICAL STATEMENT

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (*e.g.*, OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product in accordance with all applicable instructions and with appropriate safety equipment, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement or repair of the 3M product or refund of the purchase price. Warranty claims must be made within one (1) year from the date of 3M's shipment.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by applicable law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit <u>www.3M.com</u>

3M is a trademarks of 3M Company.



Electrical Markets Division 13011 McCallen Pass, Bldg. C Austin, TX 78753 Phone: 800.676.8381 www.3M.com/oem

Please Recycle. Printed in USA. © 3M 2021. All Rights Reserved. 78-8124-4704-9 Rev D

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Adhesive Tapes category:

Click to view products by 3M manufacturer:

Other Similar products are found below :

56-YELLOW-34"X72YD 021200-64630 62-GRAY-12"X36YD 764-1"x36yd-Red 764-1"x36yd-White 130C-1X15FT BDN11-3CB/A01 1900-48mm 22-1/2X36YD 88-SUPER-34X44FT 890103N001 2670 9485PC 1" EVK-TA-TM047NBH01 20-1"X60YDS 2020-18mmx55m H150 363 3900-Blue 396-1"x36yd 4016-34"x36yd 4462-SN100 4462W-12"x72yd 4504-34x18 5414 34X36 4008-12"X36YD 4104-34"x18yd 4466 1" 4466W-1/2"x36yd 4492B-1"x72yd 4496W-12"x36yd 4508-1"x36yd 4516-3/8x36 4726 1/2"X36YD 054007-43154 054007-43152 5414 1X36 56 TAPE (1/2") 56-YELLOW-58"X72YD 60-1/2"x36yd 62-Gray-34x36yd 687-758 764-1"x36yd-Yellow 766-3"x36yd-YellowBlack EVK-TA-TM070RBH10 88-SUPER-3/4X66FT 177-982-9-P-1-.150 3900-SILVER 4718-12"x36yd 926-14"x18yd