# **3M**

# **Extreme Sealing Tape**


4411N • 4411G • 4411B • 4412N • 4412G

Technical Data September, 2014

## Product Description

3M<sup>TM</sup> Extreme Sealing Tape is a family of single coated, pressure sensitive adhesive tapes designed for difficult sealing applications. The backing on this tape is an ionomer film that is very tough yet flexible and abrasion resistant. The very soft and thick acrylic adhesive has excellent sealing properties and good outdoor durability. This single coated tape is designed to seal over an existing joint, seam, or penetration. The adhesive is designed to adhere well to the ionomer film so that overlapping tape joints can be made while maintaining a strong seal.

#### Construction



Comptunction		Thickr	ness, mil	s (mm)	Description		
Construction	4411N	4411G	4411B	4412N	4412G	Description	
Release Liner	2 (0.05)					matte, translucent polyester film	
Ionomer Backing	4 (0.1)					acrylic and ethylene copolymer	
Adhesive	36 76 (0.9) (1.9)				very conformable multi- purpose acrylic		
Total Tape Thickness	40 80 (1.0) (2.0)				without disposable release liner		

4411N • 4411G • 4411B • 4412N • 4412G

Typical Physical Properties and Performance Characteristics Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

	3M™ Extreme Sealing Tape								
	4411N	4411G	4411B	4412N	4412G				
Tape Color	Neutral/ Translucent	Gray	Black	Neutral/ Translucent	Gray				
Thickness, mil (mm)		40 (1.0)	80 (2.0)						
Tape Density, lb/ft³ (g/cm³)	51 (0.82)								
Tape Tensile Strength, lb/in (N/cm) (ASTM D-3759 with D-412 dog bone die C)	13 (23)								
Tape Elongation to Break (ASTM D-3759 with D-412 dog bone die C)	400%								
90 Degree Peel Adhesion, Ib/in (N/cm) Based on ASTM D-3330; stainless steel substrate, 72 hour room temp with 3M™ VHB™ Tape 5925 tape to attach aluminum peel strip backing; 3M™ Adhesion Promoter 111 used on substrates	15 (26)	16 (28)	17 (30)	18 (32)	18 (32)				
Moisture Vapor Transmission Rate g/(m² day) (Tested for 4412N only) (ASTM E96, Procedure E)	Not Tested	Not Tested	Not Tested	10.6	Not Tested				
Max Temperature Tolerance									
Short term (minutes, hours)	300°F (149°C)								
Long term (days, weeks)	200°F (93°C)								
High Pressure Water Resistance	Excellent								
Moisture Resistance	Excellent								
Thermal Shock Resistance	Excellent								
U.V. Resistance:	Samples passed adhesion tests after 2000 hours of accelerated aging. See "3M™ Extreme Sealing Tape - Exterior Durability Report".								

<b>Available Sizes</b>	Standard Widths:	0.75", 1", 2", 2.5", 3", 4" (19mm 25mm, 50mm, 65mm, 75mm, 100mm)					
	Standard Lengths:	36 yards (32.9 meters) for 4411N, 4411G and 4411B 18 yards (16.5 meters) for all versions					
	Core Inside Diameter:	3" (76.2 mm)					
	Slitting Tolerance:	± 1/32" (0.8 mm)					
	Thickness Tolerance:	± 10%					

4411N • 4411G • 4411B • 4412N • 4412G

#### 90 Degree Peel Adhesion Strength

(Based on ASTM D-3330; various substrates, 72 hour room temp with 3M<sup>TM</sup> VHB<sup>TM</sup> 5925 tape to attach aluminum peel strip backing; adhesion promoter or primer used on substrates)

			3M™ Extreme Sealing Tape									
		Surface	4411N		4411G		4411B		4412N		4412G	
		Surface Preparation		N/cm	lb/in	N/cm	lb/in	N/cm	lb/in	N/cm	lb/in	N/cm
	Stainless	AP111	15	26	16	28	17	30	18	32	18	32
	Aluminum	AP111	15	26	15	26	19	33	18	32	18	32
ate	Truck Paint	AP111	14	25	15	26	17	30	19	33	17	30
	Glass	AP115	15	26	15	26	19	33	19	33	16	28
Substrate	PC	P94	16	28	15	26	18	32	18	32	18	32
Su	Acrylic	P94	15	26	15	26	16	28	19	33	17	30
	ABS	P94	16	28	16	28	18	32	19	33	18	32
	PVC	P94	16	28	15	26	19	33	19	33	18	32
	PP	P94	15	26	15	26	16	28	18	32	17	30

#### Notes:

- 1. For metals and paints, 3M<sup>™</sup> Adhesion Promoter 111 was used to increase adhesion to maximum levels.
- For glass, 3M<sup>™</sup> Silane Glass Treatment AP115 was used to increase adhesion to maximum levels and to provide long term durability on glass.
- 3. For plastics, 3M<sup>™</sup> Primer 94 was used to increase adhesion to maximum levels. Note that Primer 94 has high levels of VOC's and may not be available for purchase in all areas.

### Preparing the Surfae

The first step in making a successful seal is to prepare the surface for bonding. At a minimum, this means making sure the bonding surface is clean of all contaminants. For most surfaces, cleaning with a 50:50 mixture of isopropyl alcohol\* (IPA) and water works well. If the substrate is contaminated with heavy oils or grease, a degreaser or strong solvent may be used to remove the oil, but a final wipe of IPA/water should be used.

For many substrates, a simple cleaning will allow 3M<sup>TM</sup> Extreme Sealing Tape to bond. However, adhesion promoters can be used to increase both initial and final bond strength. The following three primers are commonly used with 3M<sup>TM</sup> Extreme Sealing Tapes:

#### **Metals and Paints**

3M<sup>TM</sup> Adhesion Promoter 111 (AP111) increases adhesion on most metals and many hard coatings and paints.

#### **Plastics and Rubbers**

3M<sup>TM</sup> Primer 94 increases adhesion on many plastics and rubbers.

#### **Glass**

3M<sup>TM</sup> Adhesion Promoter 115 (AP115) increases adhesion on glass.

See technical data sheets for adhesion promoter and primer application instructions.

\*Consult manufacturer's directions for use and precautions when using cleaning solvents. This cleaning recommendation may not be compliant with the rules of certain Air Quality Management Districts in California; consult applicable rules before use.


4411N • 4411G • 4411B • 4412N • 4412G

#### **Application Temperature**

Ideal tape application is accomplished when temperature is between 70° and 100°F (21° and 38°C). The tape generally reaches full bond strength after 24 hours but provides a seal immediately. Tape application to surfaces at temperatures below 50°F (10°C) is generally not recommended. Once properly applied, low temperature holding is generally satisfactory.

# Select the Proper Tape Width


In order to provide a seal, the tape must cover all points of water intrusion. To do this robustly, the tape should be wide enough to cover the intrusion points and provide for some variation in workmanship. Choosing a tape width that allows the tape to extend at least 2 cm (3/4 in) beyond the sealing points can help to accomplish this.



#### Applying 3M<sup>TM</sup> Extreme Sealing Tape

3M<sup>TM</sup> Extreme Sealing Tape has a release liner on the backing side of the tape. To avoid overstretching, this liner is usually left on while laying down the tape.

#### **Application Steps**



- Lay tape down so that it covers all areas meant to be sealed.
- Remove release liner (file cleaning brush can help)
- Roll down tape with a soft roller (such as a medium nap paint roller). If there is a step, roll down top and bottom separately.

4411N • 4411G • 4411B • 4412N • 4412G

# Creating an Overlap Joint

It is often required to overlap 3M<sup>TM</sup> Extreme Sealing Tape onto itself. In this case, the ionomer backing of the first piece is one of the substrates to which the second piece of tape is bonding. The tapes should overlap at least 2 cm (3/4 in).

#### **Surface Preparation**

The ionomer does not need to be cleaned prior to bonding unless it has been contaminated with oil, dirt, grease, etc. If the bonding area of the ionomer has been contaminated, IPA/water can be used to clean the surface.


A quick wipe of AP111 on the ionomer is suggested for best performance of the overlapping tape. AP111 will approximately double Extreme Sealing Tape's adhesion to its own ionomer backing.

#### **Pressure**

Firm pressure should be applied to all points of overlap between the two tapes to join the adhesives and create a robust seal.

#### **Additional Sealing**

To increase sealing robustness, a small dab of liquid sealant 3M<sup>TM</sup> 4000UV is suggested at the points of overlapping tape. This step maximizes process robustness by decreasing the chance that an improperly pressurized overlap might leave a gap.



In the above images, the white circles indicate where 3M 4000UV should be applied in the corner and step situations. These two general categories can describe most common configurations. For configurations other than these, the general principle is to use 3M<sup>TM</sup> 4000UV in any place where water (shown as blue arrows) could seep past an improperly joined overlap.

Do not apply 3M<sup>TM</sup> Extreme Sealing Tape over the top of uncured liquid sealants. If using over a liquid sealant, check with sealant's manufacturer to determine when sealant is 100% cured. Certain chemicals produced by the curing process of some liquid sealants may cause detrimental effects to the long term stability of the bond.

4411N • 4411G • 4411B • 4412N • 4412G

Storage	Store in original cartons at 40-100°F (4-38°C) and 0-95% relative humidity. Optimum storage conditions are 72°F (22°C) and 50% relative humidity.
Shelf Life	When stored under proper conditions, product retains its performance and properties for 24 months from date of shipment.
<b>Technical Information</b>	The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.
<b>Product Use</b>	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.
Warranty, Limited Remedy, and Disclaimer	Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.
Limitation of Liability	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.





3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-362-3550 • 877-369-2923 (Fax) www.3M.com/extreme



Recycled Paper 40% pre-consumer 10% post-consumer 3M and VHB are trademarks of 3M Company.
Printed in U.S.A.

©3M 2014 70070940468 (9/14)

### **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Adhesive Tapes category:

Click to view products by 3M manufacturer:

Other Similar products are found below:

56-YELLOW-34"X72YD 021200-64630 62-GRAY-12"X36YD 764-1"x36yd-Red 764-1"x36yd-White 130C-1X15FT BDN11-3CB/A01 1900-48mm 22-1/2X36YD 88-SUPER-34X44FT 890103N001 2670 9485PC 1" EVK-TA-TM047NBH01 20-1"X60YDS 2020-18mmx55m H150 363 3900-Blue 396-1"x36yd 4016-34"x36yd 4462-SN100 4462W-12"x72yd 4504-34x18 5414 34X36 4008-12"X36YD 4104-34"x18yd 4466 1" 4466W-1/2"x36yd 4492B-1"x72yd 4496W-12"x36yd 4508-1"x36yd 4516-3/8x36 4726 1/2"X36YD 054007-43154 054007-43152 5414 1X36 56 TAPE (1/2") 56-YELLOW-58"X72YD 60-1/2"x36yd 62-Gray-34x36yd 687-758 764-1"x36yd-Yellow 766-3"x36yd-YellowBlack EVK-TA-TM070RBH10 88-SUPER-3/4X66FT 177-982-9-P-1-.150 3900-SILVER 4718-12"x36yd 926-14"x18yd