



# Technical Data Sheet

# 3M™ Double Coated Tape GPT-020F

### **Product Description**

3M™ Double Coated Tape GPT-020F is an 8 mil thick, double sided tape utilizing a modified acrylic adhesive with polyester carrier and a BOPP (Bi-axially Oriented Polypropylene) film liner.

#### **Product Features**

- High adhesion to a variety of high and low surface energy substrates
- High initial tack
- High shear and temperature resistance
- Easy handling and converting due to polyester carrier
- Bi-axially Oriented Polypropylene (BOPP) Liner for clean handling and automatic unwinding
- General Purpose Tape (GPT)
- High thermal and humidity resistance

Total Tape Thickness (mil)

Typical Physical Properties		
Property	Values	Additional Information
Adhesive Type	Modified Acrylic	
Adhesive Carrier	PET	
Color	Clear	
Liner	Bi-axially Oriented Polypropy Red 3M Logo	lene film, White with
Liner Thickness	0.1 mm	
Liner Print	3M	
Carrier Thickness	0.012 mm	

EN - Dec, 2020 1/7

7.95 mil

View ^



Test Method: ASTM D3652

Total Tape Thickness (mm)	0.202 mm	View ^	
Test Method: ASTM D3652			
Adhesive Thickness	0.095 mm	View ^	
Test Name: Backside			
Notes: Backside adhesive is on the exterior of the	roll, exposed when liner is removed.		
Adhesive Thickness	3.75 mil	View ^	
Test Name: Backside			
Notes: Backside adhesive is on the exterior of the	roll, exposed when liner is removed.		
Adhesive Thickness	0.095 mm	View ^	
Test Name: Faceside			
Notes: Faceside adhesive is on the interior of the r	oll, exposed when unwound and liner removed.		
Adhesive Thickness	3.75 mil	View ^	
Test Name: Faceside			
Notes: Faceside adhesive is on the interior of the r	roll, exposed when unwound and liner removed.		
Carrier Thickness	0.47 mil		
Liner Thickness	3.9 mil		
Shear Adhesion Failure Test - SAFT	500g >190 °C, 1000G>160 °C		
Shear Adhesion Failure Temperature - SAFT	500g >375 °F, 1000G>320 °F		

# Typical Performance Characteristics

Property	Values	Additional Information
180° Peel Adhesion	12.32 N/cm	View ^

Test Method: ASTM D3330

Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F

Environmental Condition: 50%RH



Substrate: Polycarbonate (PC)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion	113 oz/in	View ^
Test Method: ASTM D3330		
Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Polycarbonate (PC)		
Notes: 12 in/min (300 mm/min)		
180° Peel Adhesion	10.86 N/cm	View ^
Test Method: ASTM D3330		
Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: ABS  Notes: 12 in/min (300 mm/min)		
180° Peel Adhesion	99 oz/in	View ^
Test Method: ASTM D3330		
Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: ABS		
Notes: 12 in/min (300 mm/min)		
180° Peel Adhesion	12.26 N/cm	View ^
Test Method: ASTM D3330		
Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Polypropylene (PP)		
Notes: 12 in/min (300 mm/min)		
180° Peel Adhesion	112 oz/in	View ^
Test Method: ASTM D3330		
Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Polypropylene (PP)		
Notes: 12 in/min (300 mm/min)		
180° Peel Adhesion	11.79 N/cm	View ^



Test Method: ASTM D3330

Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F

Environmental Condition: 50%RH

Substrate: Glass

Notes: 12 in/min (300 mm/min)

Devel Moderno ASTM 03330   Devel Modern From F23	180° Peel Adhesion	108 oz/in	View ^
Doesll Care Time: 72.0 Doesll Time luths: hr Temp C: 23.0 Temp F: 27E Environmental Conditions S0/RH Substrate: Stanios Step Notes: 12 in/min (300 mm/min)  190° Peel Adhesion 103 az/in View ^  Test Method: ASTM D3330 Doesll Care Time: 72.0 Doesl Time this: hr Temp C: 23.0 Doesl Time this: hr Temp C: 23.0 Temp F: 27E Environmental Condition: 50/RH Substrate: Staniolises Sign Notes: 12 in/min (300 mm/min)  Short Term Temporature Resistance 380 \(\frac{1}{2}\) View ^  Test Condition: Short Term (minutes, hour)  Test Condition: Long Term (day, weeks)	Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Glass		
Dwell Time Unite: 12.0 Dwell Time Unite: 15 Temp 0: 250 Temp 19: 726 Euroremental Condition: 50 KRH Suitarrae Stainess State  Notas: 12 in/min (300 mm/min)  IS0* Peel Adhesion 103 oz/in View ^  Test Method: ASTM D3330  Devel Time: 72.0 Dwell Time: 172.0 Dwell Time: 172.0 Dwell Time Units: 15 Temp 0: 250 Temp 19: 726 Temp 19: 726 Temp 19: 727 Temp 0: 250 Temp 19: 727	180° Peel Adhesion	11.3 N/cm	View ^
Test Method: ASTM D3330  Doell Crier Units: hr Temp C: 23C Temp P: 72F Environmental Condition: 50%RH Substrate: Stainless Steel  Notes: 12 in/min (300 mm/min)  Short Term Temperature Resistance 320 °F View ^  Test Condition: Short Term (minutes, hour)  Short Term Temperature Resistance 160 °C View ^  Test Condition: Short Term (minutes, hour)  Long Term Temp C 90 °C View ^  Test Condition: Long Term (day, weeks)  Long Term Temp F 195 °F View ^  Test Condition: Long Term (day, weeks)	Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Stainless Steel		
Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Test Condition: Short Term (minutes, hour)  Short Term Temperature Resistance 320 °F View ^  Test Condition: Short Term (minutes, hour)  Long Term Tempe  180 °C View ^  Test Condition: Long Term (day, weeks)	180° Peel Adhesion	103 oz/in	View ^
Test Condition: Short Term (minutes, hour)  Short Term Temperature Resistance 160 °C View ^  Test Condition: Short Term (minutes, hour)  Long Term Temp C 90 °C View ^  Test Condition: Long Term (day, weeks)  Long Term Temp F 195 °F View ^  Test Condition: Long Term (day, weeks)	Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Stainless Steel		
Short Term Temperature Resistance 160 °C View ^  Test Condition: Short Term (minutes, hour)  Long Term Temp C 90 °C View ^  Test Condition: Long Term (day, weeks)  Long Term Temp F 195 °F View ^  Test Condition: Long Term (day, weeks)	Short Term Temperature Resistance	320 °F	View ^
Test Condition: Short Term (minutes, hour)  Long Term Temp C 90 °C View ^  Test Condition: Long Term (day, weeks)  Long Term Temp F 195 °F View ^  Test Condition: Long Term (day, weeks)	Test Condition: Short Term (minutes, hour)		
Long Term Temp C 90 °C View ^  Test Condition: Long Term (day, weeks)  Long Term Temp F 195 °F View ^  Test Condition: Long Term (day, weeks)	Short Term Temperature Resistance	160 °C	View ^
Test Condition: Long Term (day, weeks)  Long Term Temp F 195 °F View ^  Test Condition: Long Term (day, weeks)	Test Condition: Short Term (minutes, hour)		
Long Term Temp F  195 °F  View ^  Test Condition: Long Term (day, weeks)	Long Term Temp C	90 °C	View ^
Test Condition: Long Term (day, weeks)	Test Condition: Long Term (day, weeks)		
	Long Term Temp F	195 °F	View ^
Static Shear >10,000 min View ^	Test Condition: Long Term (day, weeks)		
	Static Shear	>10,000 min	View ^

4/7



Test Method: ASTM D3654

Test Condition: 1000 g @ Room Temperature

Notes: 1 in<sup>2</sup> sample size

Static Shear >10,000 min View ^

Test Method: ASTM D3654

Test Condition: 500 g @ 70°C (158°F)

Notes: 0.5 in² sample size

UV Resistance Excellent

#### Storage and Shelf Life

It is suggested that products are stored at room temperature conditions of 70°F (21°C) and 50% relative humidity. If stored properly, product retains its performance and properties for 18 months from date of manufacture. Note: The shelf life may be shortened if the original packaging is not properly sealed or stored in an environment with high temperatures or humidity.

#### Certificate of Analysis (COA)

Available upon request.

#### Automotive Disclaimer

Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, including, but not limited to, automotive electric powertrain battery or high voltage applications. This product does not fully adhere to typical automotive design or quality system requirements, such as IATF 16949 or VDA 6.3. This product may not be manufactured in an IATF certified facility and may not meet a Ppk of 1.33 for all properties. The product may not undergo an automotive production part approval process (PPAP). Customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's automotive application and for conducting incoming inspections before use of the product. Failure to do so may result in injury, death, and/or harm to property. No written or verbal statement, report, data or recommendation by 3M related to automotive use of the product shall have any force or effect unless in an agreement signed by the Technical Director of 3M's Automotive Division. Customer assumes all responsibility and risk if customer chooses to use this product in an automotive electric powertrain battery or high voltage application, and 3M will not be liable for any loss or damage arising from or related to the 3M product or customer's use of the product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity or recall costs), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability. In no event shall 3M be liable for any damages in excess of the purchase price paid for the product.

NOTWITHSTANDING ANY OTHER STATEMENT TO THE CONTRARY, 3M MAKES NO REPRESENTATIONS, WARRANTIES OR CONDITIONS WHATSOEVER, EXPRESS OR IMPLIED, REGARDING THE PRODUCT IF USED IN AN AUTOMOTIVE ELECTRIC POWERTRAIN BATTERY OR HIGH VOLTAGE APPLICATION, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY ON PERFORMANCE, LONGEVITY, SUITABILITY, COMPATIBILITY, OR INTEROPERABILITY, OR ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE.

#### Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

#### **Bottom Matter**

3M Industrial Adhesives & Tapes Division Converter Markets 3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-223-7427 651-778-4244 (fax) www.3M.com



#### **Trademarks**

3M is a trademark of 3M Company.

#### Handling/Application Information

Application Examples

- Point of purchase displays (POP)
- Indoor/Outdoor signage and banners
- Bonding and mounting of sales displays and billboards.
- Paper bonding and packaging
- Splicing
- Mounting of plastic parts
- Mounting of furniture and decorative trims
- Fixing of decorative trims and emblems.

#### References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/p/d/b5005163007/

#### ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

#### Precautionary Information

For information please contact your local 3M Office. www.3M.com

#### Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be



selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

Please recycle. © 3M 2016 (3/16)

7/7

#### **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Adhesive Tapes category:

Click to view products by 3M manufacturer:

Other Similar products are found below:

56-YELLOW-34"X72YD 021200-64630 62-GRAY-12"X36YD 764-1"x36yd-Red 764-1"x36yd-White 130C-1X15FT BDN11-3CB/A01 1900-48mm 22-1/2X36YD 88-SUPER-34X44FT 890103N001 2670 9485PC 1" EVK-TA-TM047NBH01 20-1"X60YDS 2020-18mmx55m H150 363 3900-Blue 396-1"x36yd 4016-34"x36yd 4462-SN100 4462W-12"x72yd 4504-34x18 5414 34X36 4008-12"X36YD 4104-34"x18yd 4466 1" 4466W-1/2"x36yd 4492B-1"x72yd 4496W-12"x36yd 4508-1"x36yd 4516-3/8x36 4726 1/2"X36YD 054007-43154 054007-43152 5414 1X36 56 TAPE (1/2") 56-YELLOW-58"X72YD 60-1/2"x36yd 62-Gray-34x36yd 687-758 764-1"x36yd-Yellow 766-3"x36yd-YellowBlack EVK-TA-TM070RBH10 88-SUPER-3/4X66FT 177-982-9-P-1-.150 3900-SILVER 4718-12"x36yd 926-14"x18yd