# **FERROXCUBE**

# DATA SHEET

# E32/16/9 E cores and accessories

Supersedes data of September 2004


2008 Sep 01



#### **CORE SETS**

# **Effective core parameters**

SYMBOL	PARAMETER	VALUE	UNIT
Σ(I/A)	core factor (C1)	0.894	mm <sup>-1</sup>
V <sub>e</sub>	effective volume	6180	mm <sup>3</sup>
l <sub>e</sub>	effective length 74		mm
A <sub>e</sub>	effective area 83		mm <sup>2</sup>
A <sub>min</sub>	minimum area 83		mm <sup>2</sup>
m	mass of core half ≈ 16 g		g



#### Core halves

 $A_L$  measured in combination with a non-gapped core half, clamping force for  $A_L$  measurements 40  $\pm 20$  N, unless stated otherwise.

GRADE	A <sub>L</sub> (nH)	$\mu_{\mathbf{e}}$	TOTAL AIR GAP (μm)	TYPE NUMBER
3C90	100 ±5% <sup>(1)</sup>	≈ 71	≈ 1600	E32/16/9-3C90-E100
	160 ±5% <sup>(1)</sup>	≈ 114	≈ 860	E32/16/9-3C90-E160
	250 ±5%	≈ 177	≈ 480	E32/16/9-3C90-A250
	315 ±5%	≈ 223	≈ 360	E32/16/9-3C90-A315
	400 ±8%	≈ 284	≈ 260	E32/16/9-3C90-A400
	$630 \pm 15\%$	≈ 447	≈ 150	E32/16/9-3C90-A630
	2500 ±25%	≈ 1770	≈ 0	E32/16/9-3C90
3C92 des	1850 ±25%	≈ 1320	≈ 0	E32/16/9-3C92
3C94	2500 ±25%	≈ <b>1770</b>	≈ 0	E32/16/9-3C94
3C96 des	2300 ±25%	≈ 1630	≈ 0	E32/16/9-3C96

E32/16/9

GRADE	A <sub>L</sub> (nH)	$\mu_{\mathbf{e}}$	TOTAL AIR GAP (μm)	TYPE NUMBER
3F3	100 ±5% <sup>(1)</sup>	≈ 71	≈ 1600	E32/16/9-3F3-E100
	160 ±5% <sup>(1)</sup>	≈ 114	≈ 860	E32/16/9-3F3-E160
	250 ±5%	≈ 177	≈ 480	E32/16/9-3F3-A250
	315 ±5%	≈ 223	≈ 360	E32/16/9-3F3-A315
	400 ±8%	≈ 284	≈ 260	E32/16/9-3F3-A400
	630 ±15%	≈ 447	≈ 150	E32/16/9-3F3-A630
	2300 ±25%	≈ 1630	≈ 0	E32/16/9-3F3
3F35 des	1700 ±25%	≈ 1210	≈ 0	E32/16/9-3F35

1.  $A_L$  measured in combination with a equal gapped core half.

# Properties of core sets under power conditions

	B (mT) at	CORE LOSS (W) at				
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; $\hat{B}$ = 200 mT; T = 100 °C	f = 400 kHz; B = 50 mT; T = 100 °C	
3C90	≥330	≤ 0.65	≤ 0.7	_	_	
3C92	≥370	_	≤ 0.55	≤ 3.2	_	
3C94	≥330	_	≤ 0.55	≤ 3.2	_	
3C96	≥340	_	≤ 0.43	≤ 2.5	_	
3F3	≥320	_	≤ 0.75	_	≤ 1.3	
3F35	≥300	_	_	_	_	


# Properties of core sets under power conditions (continued)

	B (mT) at				
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 500 kHz; B = 50 mT; T = 100 °C	f = 500 kHz; B = 100 mT; T = 100 °C	f = 1 MHz; B = 30 mT; T = 100 °C	f = 3 MHz; $\hat{B}$ = 10 mT; T = 100 °C
3C90	≥330	_	_	_	_
3C92	≥370	_	_	_	_
3C94	≥330	_	_	_	_
3C96	≥340	≤ 2.3	_	_	_
3F3	≥320	-	_	_	_
3F35	≥300	≤ 0.83	≤ 6.5	_	_

#### **COIL FORMER**

# General data for 12-pins E32/16/9 coil former

PARAMETER	SPECIFICATION	
Coil former material	polyamide (PA6.6), glass reinforced, flame retardant in accordance with "UL 94V-0"; UL file number E41871(M)	
Pin material	copper-tin alloy (CuSn), tin (Sn) plated	
Maximum operating temperature	130 °C, <i>"IEC 60085"</i> , class B	
Resistance to soldering heat	"IEC 60068-2-20", Part 2, Test Tb, method 1B: 350 °C, 3.5 s	
Solderability	"IEC 60068-2-20", Part 2, Test Ta, method 1: 235 °C, 2 s	



# Winding data and area product for 12-pins E32/16/9 coil former

NUMBER OF SECTIONS	WINDING AREA (mm²)	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm <sup>4</sup> )	TYPE NUMBER
1	97	20.2	60	8050	CPH-E32/16/9-1S-12P

E32/16/9

#### **DATA SHEET STATUS DEFINITIONS**

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

# **DISCLAIMER**

**Life support applications** — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

#### **PRODUCT STATUS DEFINITIONS**

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are <b>not</b> recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Ferrite Cable Cores category:

Click to view products by Ferroxcube manufacturer:

Other Similar products are found below:

2643626102 FX28R0984-0 FX28R0984-2 AB 3X2X3SM 2643164251 2643665709 2661626402 LB 2.8X4.5U 28R1127 28R1260
28R1575 SM28R0760 SM28R1531 2631006302 2643165451 2643178351 28R0760 MS 21X14X4.5 W SM28B1101 SS7X4X3W 4327
030 16141 ASSE017-2 2643103102 2643164151 2943666671 4327 030 12611 2643163851 AB4X2X6SM 432703013631 LB4X2X8U
28B1101 28B0785 SM28R1575 SM28R1260 74270051 2643625902 74278032 2643480009 2673069901 HFB123049-300 HFB143064100 HFB143064-300 HFB170070-000 ETD29/16/10-3C94 ETD29-3F3 ETD39-3C94 RFP1-20-10-A5 RFP1-40-28-M-A5 RFP2-10-10-A5
RFP2-25-12-A5