# **FERROXCUBE**

# DATA SHEET

# **E42/21/15**E cores and accessories

Supersedes data of September 2004


2008 Sep 01



#### **CORE SETS**

#### Effective core parameters

SYMBOL	PARAMETER	VALU E	UNIT
$\Sigma(I/A)$	core factor (C1)	0.548	mm <sup>-1</sup>
V <sub>e</sub>	effective volume	17300	mm <sup>3</sup>
I <sub>e</sub>	effective length	97.0	mm
A <sub>e</sub>	effective area	178	mm <sup>2</sup>
A <sub>min</sub>	minimum area	175	mm <sup>2</sup>
m	mass of core half	≈ 44	g



#### **Core halves**

 $A_L$  measured in combination with a non-gapped core half, clamping force for  $A_L$  measurements 40  $\pm 20$  N, unless stated otherwise.

GRADE	A <sub>L</sub> (nH)	$\mu_{\mathbf{e}}$	TOTAL AIR GAP (μm)	TYPE NUMBER
3C81	100 ±5% <sup>(1)</sup>	≈ 43	≈ 3960	E42/21/15-3C81-E100
	160 ±5% <sup>(1)</sup>	≈ 69	≈ 2060	E42/21/15-3C81-E160
	250 ±5% <sup>(1)</sup>	≈ 108	≈ 1140	E42/21/15-3C81-E250
	315 ±5%	≈ 137	≈ 850	E42/21/15-3C81-A315
	400 ±8%	≈ 173	≈ 630	E42/21/15-3C81-A400
	630 ±15%	≈ 273	≈ 360	E42/21/15-3C81-A630
	5300 ±25%	≈ 2300	≈ 0	E42/21/15-3C81
3C90	100 ±5% <sup>(1)</sup>	≈ 43	≈ 3960	E42/21/15-3C90-E100
	160 ±5% <sup>(1)</sup>	≈ 69	≈ 2060	E42/21/15-3C90-E160
	250 ±5% <sup>(1)</sup>	≈ 108	≈ 1140	E42/21/15-3C90-E250
	315 ±5%	≈ 137	≈ 850	E42/21/15-3C90-A315
	400 ±8%	≈ 173	≈ 630	E42/21/15-3C90-A400
	630 ±15%	≈ 273	≈ 360	E42/21/15-3C90-A630
	3950 ±25%	≈ <b>1710</b>	≈ 0	E42/21/15-3C90
3C91 des	5300 ±25%	≈ 2300	≈ 0	E42/21/15-3C91
3C92 des	3100 ±25%	≈ 1350	≈ 0	E42/21/15-3C92
3C94	4100 ±25%	≈ 1780	≈ 0	E42/21/15-3C94

E42/21/15

GRADE	A <sub>L</sub> (nH)	$\mu_{\mathbf{e}}$	TOTAL AIR GAP (μm)	TYPE NUMBER
3C95 des	5300 ±25%	≈ 2300	≈ 0	E42/21/15-3C95
3F3	100 ±5% <sup>(1)</sup>	≈ 43	≈ 3960	E42/21/15-3F3-E100
	160 ±5% <sup>(1)</sup>	≈ 69	≈ 2060	E42/21/15-3F3-E160
	250 ±5% <sup>(1)</sup>	≈ 108	≈ 1140	E42/21/15-3F3-E250
	315 ±5%	≈ 137	≈ 850	E42/21/15-3F3-A315
	400 ±8%	≈ 173	≈ 630	E42/21/15-3F3-A400
	630 ±15%	≈ 273	≈ 360	E42/21/15-3F3-A630
	3600 ±25%	≈ 1560	≈ 0	E42/21/15-3F3

#### Note

1. Measured in combination with an equal gapped core half, clamping force for  $A_L$  measurements, 40  $\pm 20$  N.

#### Properties of core sets under power conditions

	B (mT) at		С	ORE LOSS (W)	N) at		
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; B = 200 mT; T = 25 °C	f = 100 kHz; B = 200 mT; T = 100 °C	f = 400 kHz; B = 50 mT; T = 100 °C	
3C81	≥320	≤ 3.6	_	_	_	_	
3C90	≥320	≤ 1.9	≤2.2	_	_	_	
3C91	≥320	_	≤ 1.3 <sup>(1)</sup>	_	≤ 7.0 <sup>1)</sup>	_	
3C92	≥370	_	≤ 1.7	_	≤ 8.8	_	
3C94	≥320	_	≤ 1.7	_	≤ 8.8	_	
3C95	≥320	_	_	≤ 10.9	≤ 10.4	_	
3F3	≥320	_	≤ 2.2	_	_	≤ 3.8	


#### Note

1. Measured at 60 °C.

#### **COIL FORMERS**

#### General data for E42/21/15 coil former without pins

PARAMETER	SPECIFICATION
	polybutyleneterephtalate (PBT), glass reinforced, flame retardant in accordance with "UL 94V-0"; UL file number E45329(R)
Maximum operating temperature	155 °C, <i>"IEC 60085"</i> , class F




#### Winding data and area product for E42/21/15 coil former without pins

NUMBER OF SECTIONS	WINDING AREA (mm²)	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm <sup>4</sup> )	TYPE NUMBER
1	178	26.2	93	31700	CP-E42/21/15-1S

#### General data for 10-pins E42/21/15 coil former

PARAMETER	SPECIFICATION
Coil former material	polyamide (PA6.6), glass reinforced, flame retardant in accordance with "UL 94-HB"; UL file number E41613(M)
Pin material	copper-tin alloy (CuSn), tin (Sn) plated
Maximum operating temperature	130 °C, "IEC 60085", class E
Resistance to soldering heat	"IEC 60068-2-20", Part 2, Test Tb, method 1B: 350 °C, 3.5 s
Solderability	"IEC 60068-2-20", Part 2, Test Ta, method 1: 235 °C, 2 s




#### Winding data and area product for 10-pins E42/21/15 coil former

NUMBER OF SECTIONS	WINDING AREA (mm²)	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm <sup>4</sup> )	TYPE NUMBER
1	178	25.5	93	31700	CPH-E42/21/15-1S-10P

#### General data for 10-pins E42/21/15 coil former (A)

PARAMETER	SPECIFICATION
Coil former material	polyamide (PA6.6), glass reinforced, flame retardant in accordance with "UL 94-HB"; UL file number E41938(M)
Pin material	copper-tin alloy (CuSn), tin (Sn) plated
Maximum operating temperature	130 °C, "IEC 60085", class A
Resistance to soldering heat	"IEC 60068-2-20", Part 2, Test Tb, method 1B: 350 °C, 3.5 s
Solderability	"IEC 60068-2-20", Part 2, Test Ta, method 1: 235 °C, 2 s



#### Winding data and area product for 10-pins E42/21/15 coil former

NUMBER OF SECTIONS	MINIMUM WINDING AREA (mm²)	NOMINAL WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm <sup>4</sup> )	TYPE NUMBER
1	180	26.3	87	32000	CPH-E42/15-1S-10PD-A-Z


# E42/21/15


# E cores and accessories

#### **MOUNTING PARTS**

#### General data for mounting parts

ITEM	REMARKS	FIGURE	TYPE NUMBER
Clasp	steel, zinc (Zn) plated	5	CLA-E42/21/15
Spring	steel, zinc (Zn) plated	6	SPR-E42/21/15





E42/21/15

#### **DATA SHEET STATUS DEFINITIONS**

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

#### **DISCLAIMER**

**Life support applications** — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

#### **PRODUCT STATUS DEFINITIONS**

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are <b>not</b> recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Ferrite Cable Cores category:

Click to view products by Ferroxcube manufacturer:

Other Similar products are found below:

2643626102 FX28R0984-0 FX28R0984-2 AB 3X2X3SM 2643164251 2643665709 2661626402 LB 2.8X4.5U 28R1127 28R1260
28R1575 SM28R0760 SM28R1531 2631006302 2643165451 2643178351 28R0760 MS 21X14X4.5 W SM28B1101 SS7X4X3W 4327
030 16141 ASSE017-2 2643103102 2643164151 2943666671 4327 030 12611 2643163851 AB4X2X6SM 432703013631 LB4X2X8U
28B1101 28B0785 SM28R1575 SM28R1260 74270051 2643625902 74278032 2643480009 2673069901 HFB123049-300 HFB143064100 HFB143064-300 HFB170070-000 ETD29/16/10-3C94 ETD29-3F3 ETD39-3C94 RFP1-20-10-A5 RFP1-40-28-M-A5 RFP2-10-10-A5
RFP2-25-12-A5