# **FERROXCUBE**

# DATA SHEET

# E65/32/27 E cores and accessories

Supersedes data of September 2004

2008 Sep 01




# E65/32/27

# E cores and accessories

#### **CORE SETS**

#### **Effective core parameters**

SYMBOL	PARAMETER	VALUE	UNIT
Σ(I/A)	core factor (C1)	0.274	mm <sup>-1</sup>
V <sub>e</sub>	effective volume	79000	mm <sup>3</sup>
l <sub>e</sub>	effective length	147	mm
A <sub>e</sub>	effective area	540	mm <sup>2</sup>
A <sub>min</sub>	minimum area	530	mm <sup>2</sup>
m	mass of core half	≈205	g



#### **Core halves**

 $A_L$  measured in combination with a non-gapped core half, clamping force for  $A_L$  measurements 60  $\pm 20$  N, unless stated otherwise.

GRADE	A <sub>L</sub> (nH)	μ <sub>e</sub>	TOTAL AIR GAP (μm)	TYPE NUMBER
3C90	100 ±5% <sup>(1)</sup>	≈ 22	≈ 14380	E65/32/27-3C90-E100
	160 ±5% <sup>(1)</sup>	≈ 35	≈ 7560	E65/32/27-3C90-E160
	250 ±5% <sup>(1)</sup>	≈ 54	≈ 4100	E65/32/27-3C90-E250
	315 ±5% <sup>(1)</sup>	≈ 68	≈ 3020	E65/32/27-3C90-E315
	400 ±8% <sup>(1)</sup>	≈ 87	≈ 2200	E65/32/27-3C90-E400
	630 ±10% <sup>(1)</sup>	≈ 136	≈ 1240	E65/32/27-3C90-E630
	8600 ±25%	≈ 1860	≈ 0	E65/32/27-3C90
3C92 des	6000 ±25%	≈ 1310	≈ 0	E65/32/27-3C92
3C94	8600 ±25%	≈ 1860	≈ 0	E65/32/27-3C94
3C95 des	10600 ±25%	≈ 2300	≈ 0	E65/32/27-3C95
3F3	100 ±5% <sup>(1)</sup>	≈ 22	≈ 14380	E65/32/27-3F3-E100
	160 ±5% <sup>(1)</sup>	≈ 35	≈ 7560	E65/32/27-3F3-E160
	250 ±5% <sup>(1)</sup>	≈ 54	≈ 4100	E65/32/27-3F3-E250
	315 ±5% <sup>(1)</sup>	≈ 68	≈ 3020	E65/32/27-3F3-E315
	400 ±8% <sup>(1)</sup>	≈ 87	≈ 2200	E65/32/27-3F3-E400
	630 ±10% <sup>(1)</sup>	≈ 136	≈ 1240	E65/32/27-3F3-E630
	7300 ±25%	≈ 1580	≈ 0	E65/32/27-3F3

#### Note

1. Measured in combination with an equal gapped core half.

2008 Sep 01

E65/32/27

# Core halves of high permeability grades

Clamping force for  $A_L$  measurements, 60  $\pm 20\ N.$ 

GRADE	A <sub>L</sub> (nH)	μ <sub>e</sub>	AIR GAP (μm)	TYPE NUMBER
3C11	16700 ±25%	≈ 3620	≈ 0	E65/32/27-3C11


# Properties of core sets under power conditions

B (mT) at		CORE LOSS (W) at					
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; B = 200 mT; T = 25 °C	f = 100 kHz; B = 200 mT; T = 100 °C	f = 400 kHz; B = 50 mT; T = 100 °C	
3C90	≥320	≤ 9.1	≤ 12	_	_	_	
3C92	≥370	_	≤ 8.5	_	≤ 47	_	
3C94	≥320	_	≤ 8.5	_	≤ 47	_	
3C95	≥320	_	_	≤ 49.8	≤ 47.4	_	
3F3	≥320	_	≤ 10.5	_	_	≤ 21	

#### **COIL FORMER**

#### General data for E65/32/27 coil former without pins

PARAMETER	SPECIFICATION
Coil former material	polyethylene terephtalate (PET), glass reinforced, flame retardant in accordance with "UL 94V-0"; UL file number E107536
Maximum operating temperature	130 °C, <i>"IEC 60085"</i> , class B




# Winding data and area product for E65/32/27 coil former without pins (E)


NUMBER OF SECTIONS	MINIMUM WINDING AREA (mm²)	NOMINAL WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm <sup>4</sup> )	TYPE NUMBER
1	394	39.2	150	213000	CP-E65-1S-T

#### **MOUNTING PARTS**

#### General data for mounting parts

ITEM	REMARKS	FIGURE	TYPE NUMBER
Clasp	steel, zinc (Zn) plated	3	CLA-E65/32/27
Spring	steel, zinc (Zn) plated	4	SPR-E65/32/27





E65/32/27

#### **DATA SHEET STATUS DEFINITIONS**

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

#### **DISCLAIMER**

**Life support applications** — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

#### **PRODUCT STATUS DEFINITIONS**

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are <b>not</b> recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Ferrite Cable Cores category:

Click to view products by Ferroxcube manufacturer:

Other Similar products are found below:

2643626102 FX28R0984-0 FX28R0984-2 AB 3X2X3SM 2643164251 2643665709 2661626402 LB 2.8X4.5U 28R1127 28R1260
28R1575 SM28R0760 SM28R1531 2631006302 2643165451 2643178351 28R0760 MS 21X14X4.5 W SM28B1101 SS7X4X3W 4327
030 16141 ASSE017-2 2643103102 2643164151 2943666671 4327 030 12611 2643163851 AB4X2X6SM 432703013631 LB4X2X8U
28B1101 28B0785 SM28R1575 SM28R1260 74270051 2643625902 74278032 2643480009 2673069901 HFB123049-300 HFB143064100 HFB143064-300 HFB170070-000 ETD29/16/10-3C94 ETD29-3F3 ETD39-3C94 RFP1-20-10-A5 RFP1-40-28-M-A5 RFP2-10-10-A5
RFP2-25-12-A5