Scotch[™] 88T All Weather Vinyl Plastic Telephone Tape





Specifically Designed to Meet the Telephone Industry Needs

Scotch[™] Brand 88T is specifically designed, formulated and made to meet the needs of the telephone industry. In fact, it's the only tape that meets the industry's full requirements for a vinyl plastic tape for general insulating, wrapping and splicing applications. That means you can use a tape that's perfectly balanced in physical and electrical properties while it offers the ultimate in holding, protecting and insulating. Even its "feel" has been designed with the craftsperson's job in mind.

- All-weather conformability and protection—easy to work with and great protection no matter what the weather.
- Total insulation compatibility works with any insulation or combination as well as cable non-reenterable encapsulating compounds.
- Flame retardant—safe.
- Excellent abrasion and puncture resistance—88T was made to be worked with and to work after it's on the job.
- High tensile and mechanical strength—durability during and after application.
- Good elongation for conformability—performance for even the most irregular splices.

- Non-corrosive—use 88T anywhere.
- High dielectric strength.
- Great resistance to weathering, salt water, alkalies and acid.

It's the only tape you need...

You won't need to carry or store any other vinyl tape than Scotch Brand 88T Tape because you can use it inside or outside plant for every general wrapping, terminating, splicing and insulating in any weather application.

Availability

Scotch Brand 88T Tape is available in the following roll sizes: ³/₄ in. × 36 ft. (19 mm × 11 m) ³/₄ in. × 60 ft. (19 mm × 18 m)

1 in. × 36 ft. (25 mm × 11 m) 1½ in. × 44 ft. (38 mm × 13,5 m)

Typical Properties Physical Properties

	Value	Test Method
Backing	Polyvinyl chloride (PVC)	
Color	Black	
Thickness (mils)	8.5	ASTM D-1000-71
Adhesion to steel (oz./in.) a. Room temp. b. 0°F	20 16	ASTM D-1000-71 ASTM D-1000-71
Adhesion to backing (oz./in.) a. Room temp. b. 0°F	20 16	ASTM D-1000-71 ASTM D-1000-71
Tensile Strength (lbs./in.) a. Room temp. b. 0°F	20 30	ASTM D-1000-71 ASTM D-1000-71
Accelerated Aging	110%	MIL-1-7798A
Elongation (% at break) a. Room temp. b. 0°F	250% 100%	3M 3M
Flammability	1 sec.	Underwriters' Laboratories, Inc.
Resistance to penetration at elevated temp.*	55°C	ASTM D-1000-71
Application temperature range:	From - 10°F to + 125°F	
Temperature range: (after application)	-40°F to +176°F	
Transfer of adhesive	None	

Electrical Properties

	Value	Test Method
Dielectric breakdown (volts/mil)	1100 VPM	ASTM D-1000-71
a. After standard conditioning b. After water immersion	1100 VPM 90% of standard condition	ASTM D-1000-71 ASTM D-1000-71
Direct method of electrolytic corrosion	1.0 ratio	ЗМ
Insulation resistance	1 × 10 ⁶ megohms	ASTM D-1000-71

Chemical Properties

	Value
Resistance to water	Excellent
Resistance to acids	Excellent
Resistance to alkalies	Excellent
Resistance to aging	Excellent
Sunlight & weathering	Not affected
Corrosive effects on electrical conductors	None

*Also specified in MIL-1-7798A. (Values listed are typical and are not to be taken as minimum or maximum.)

Important Notice To Purchaser:

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties, expressed or implied: Seller's and manufacturer's only obligation shall

80-6104-1201-9(48.5)R2

3M TelComm Products Division

PO Box 2963, Austin, TX 78769-2963 512/834 1800 TELEX 29-7023 be to replace such quantity of the product proved to be defective. Neither seller or manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for his

© 1988 Minnesota Mining and Manufacturing Company

intended use, and user assumes all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacturer.

Litho in U.S.A.



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Adhesive Tapes category:

Click to view products by 3M manufacturer:

Other Similar products are found below :

PF24.0W 4718 4516-1/4x36 56-YELLOW-34"X72YD 00-021200-13972-7 021200-64630 60 TAPE (1") 62-GRAY-12"X36YD 62-GRAY-1"X36YD 69-1"X36YD 764-1"x36yd-Red 764-1"x36yd-White PG ASSY 926-1/4X18YD 967454-1 1194-14"X36YD 1181 19MM X 16,5 METERS 1182-7.7X10 1245-34"X18YD 1267 130C-1X15FT 130-1x10FT 1345-3/8x18yrd 1380-2"X8" E39-RS1-CA 1900-48mm 22-1/2X36YD 2229-P-2-1/2x3-3/4 88-SUPER-34X44FT 890103N001 2670 SJ3527N-Black-1.5"x50yd EVK-TA-TM047NBH01 AD-UCUSB-DCAUD-SPL 20-1"X60YDS 2020-18mmx55m H150 3900-Blue 3939-24mmx55m 396-1"x36yd 4016-34"x36yd 4462W-12"x72yd 44-TAN-14"X90YD 4504-34x18 471-Trans-1"x36yd-Bulk 5414 34X36 C-22 35-Gray-1/2 371-Tan-48mmx50m 4008-12"X36YD