FERROXCUBE

DATA SHEET

ETD59/31/22 ETD cores and accessories

Supersedes data of September 2004

2008 Sep 01




ETD cores and accessories

ETD59/31/22

CORE SETS

Effective core parameters

| SYMBOL | PARAMETER | VALUE | UNIT |
|------------------|-------------------|-------|------------------|
| Σ(I/A) | core factor (C1) | 0.378 | mm ⁻¹ |
| V _e | effective volume | 51500 | mm ³ |
| l _e | effective length | 139 | mm |
| A _e | effective area | 368 | mm ² |
| A _{min} | minimum area | 360 | mm ² |
| m | mass of core half | ≈130 | g |



Core halves

Clamping force for A_L measurements, 70 ± 20 N. Gapped cores are available on request.

| GRADE | A _L (nH) | $\mu_{\mathbf{e}}$ | AIR GAP (μm) | TYPE NUMBER |
|----------|------------------------|--------------------|-----------------|------------------|
| 3C90 | 6000 ±25% | ≈ 1800 | ≈ 0 | ETD59/31/22-3C90 |
| 3C94 | 6000 ±25% | ≈ 1800 | ≈ 0 | ETD59/31/22-3C94 |
| 3C95 des | 7340 ±25% | ≈ 2205 | ≈ 0 | ETD59/31/22-3C95 |
| 3F3 | 5600 ±25% | ≈ 1680 | ≈ 0 | ETD59/31/22-3F3 |

Properties of core sets under power conditions


| | B (mT) at | CORE LOSS (W) at | | | | | |
|-------|---|--|---|--|---|--|--|
| GRADE | H = 250 A/m; f = 25 kHz; T = 100 °C | f = 25 kHz; \hat{B} = 200 mT; T = 100 °C | f = 100 kHz; B = 100 mT; T = 100 °C | f = 100 kHz; B = 200 mT; T = 25 °C | f = 100 kHz; B = 200 mT; T = 100 °C | f = 400 kHz; B = 50 mT; T = 100 °C | |
| 3C90 | ≥330 | ≤ 6.2 | ≤ 7.3 | _ | _ | _ | |
| 3C94 | ≥330 | _ | ≤ 5.2 | _ | ≤ 31 | _ | |
| 3C95 | ≥330 | _ | _ | ≤ 32.4 | ≤ 30.9 | _ | |
| 3F3 | ≥320 | _ | ≤ 6.7 | _ | _ | ≤ 12.8 | |

2008 Sep 01 2

COIL FORMER

General data 24-pins ETD59/31/22 coil former

| PARAMETER | SPECIFICATION |
|-------------------------------|---|
| Coil former material | polybutyleneterephtalate (PBT), glass-reinforced, flame retardant in accordance with "UL 94V-0"; UL file number E45329(M) |
| Pin material | copper-tin alloy (CuSn), tin (Sn) plated |
| Maximum operating temperature | 155 °C, <i>"IEC 60085"</i> , class F |
| Resistance to soldering heat | "IEC 60068-2-20", Part 2, Test Tb, method 1B, 350 °C, 3.5 s |
| Solderability | "IEC 60068-2-20", Part 2, Test Ta, method 1 |



Winding data and area product for 24-pins ETD59/31/22 coil former

| NUMBER OF SECTIONS | WINDING AREA (mm²) | MINIMUM WINDING WIDTH (mm) | AVERAGE LENGTH OF TURN (mm) | AREA PRODUCT Ae x Aw (mm ⁴) | TYPE NUMBER |
|-----------------------|--------------------------|-------------------------------------|--------------------------------------|--|------------------|
| 1 | 366 | 41.2 | 106 | 135000 | CPH-ETD59-1S-24P |

2008 Sep 01 3


ETD cores and accessories

ETD59/31/22

MOUNTING PARTS

General data

| ITEM | REMARKS | FIGURE | TYPE NUMBER |
|---------------|---------------------------|--------|-------------|
| Mounting clip | material: stainless steel | | CLI-ETD59 |



ETD cores and accessories

ETD59/31/22

DATA SHEET STATUS DEFINITIONS

| DATA SHEET STATUS | PRODUCT STATUS | DEFINITIONS |
|---------------------------|-------------------|--|
| Preliminary specification | Development | This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product. |
| Product specification | Production | This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product. |

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

| STATUS | INDICATION | DEFINITION |
|-----------|------------|--|
| Prototype | prot | These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change. |
| Design-in | des | These products are recommended for new designs. |
| Preferred | | These products are recommended for use in current designs and are available via our sales channels. |
| Support | sup | These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability. |

2008 Sep 01 5

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Ferrite Cable Cores category:

Click to view products by Ferroxcube manufacturer:

Other Similar products are found below:

2643626102 FX28R0984-0 FX28R0984-2 AB 3X2X3SM 2643164251 2643665709 2661626402 LB 2.8X4.5U 28R1127 28R1260
28R1575 SM28R0760 SM28R1531 2631006302 2643165451 2643178351 28R0760 MS 21X14X4.5 W SM28B1101 SS7X4X3W 4327
030 16141 ASSE017-2 2643103102 2643164151 2943666671 4327 030 12611 2643163851 AB4X2X6SM 432703013631 LB4X2X8U
28B1101 28B0785 SM28R1575 SM28R1260 74270051 2643625902 74278032 2643480009 2673069901 HFB123049-300 HFB143064100 HFB143064-300 HFB170070-000 ETD29/16/10-3C94 ETD29-3F3 ETD39-3C94 RFP1-20-10-A5 RFP1-40-28-M-A5 RFP2-10-10-A5
RFP2-25-12-A5