



# **SPECIFICATION**

(Reference sheet)

• Supplier : Samsung electro-mechanics • Samsung P/N : CL10B154KA8NNNC

• Product : Multi-layer Ceramic Capacitor • Description : CAP, 150 nF, 25V, ±10%, X7R, 0603

### A. Samsung Part Number

<u>CL</u> <u>10</u> <u>B</u> <u>154</u> <u>K</u> <u>A</u> <u>8</u> <u>N</u> <u>N</u> <u>N</u> <u>C</u> ① ② ③ ④ ⑤ ⑥ ⑦ ⑧ ⑨ ⑩ ⑪

1	Series	Samsung Multi-layer Ceramic Capacitor			
2	Size	0603 (inch code)	L: 1.6 ± 0.1 mm	W: 0.8 ± 0.1 m	m
3	Dielectric	X7R	8 Inner electrode	Ni	
4	Capacitance	<b>150</b> nF	Termination	Cu	
(5)	Capacitance	±10 %	Plating	Sn 100% (P	b Free)
	tolerance		<b>9</b> Product	Normal	
6	Rated Voltage	25 V	Special	Reserved for future use	
7	Thickness	$0.8 \pm 0.1$ mm	① Packaging	Cardboard Type, 7" reel	

#### **B. Samsung Reliability Test and Judgement condition**

	Performance	Test condition			
Capacitance	Within specified tolerance	1kHz±10% 1.0±0.2Vrms			
Tan δ (DF)	0.1 max.				
Insulation	10,000Mohm or 100Mohm⋅ <i>μ</i> F	Rated Voltage 60~120 sec.			
Resistance	Whichever is Smaller				
Appearance	No abnormal exterior appearance	Microscope (×10)			
Withstanding	No dielectric breakdown or	250% of the rated voltage			
Voltage mechanical breakdown					
Temperature X7R					
Characteristics	(From -55℃ to 125℃, Capacitance change should be within ±15%)				
Adhesive Strength	No peeling shall be occur on the	500g·F, for 10±1 sec.			
of Termination	terminal electrode				
Bending Strength	Capacitance change : within ±12.5%	Bending to the limit (1mm)			
		with 1.0mm/sec.			
Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder			
	is to be soldered newly	245±5℃, 3±0.3sec.			
		(preheating : 80~120 ℃ for 10~30sec.)			
Resistance to	Capacitance change: within ±7.5%	Solder pot : 270±5°C, 10±1sec.			
Soldering heat	Tan δ, IR : initial spec.	, ,			

	Performance	Test condition
Vibration Test	Capacitance change : within ±5%	Amplitude : 1.5mm
	Tan δ, IR : initial spec.	From 10Hz to 55Hz (return : 1min.)
		2hours × 3 direction (x, y, z)
Moisture	Capacitance change : within ±12.5%	With rated voltage
Resistance	Tan δ: 0.125 max	40±2℃, 90~95%RH, 500+12/-0hrs
	IR : 12.5MΩ·μF or Over	
High Temperature	Capacitance change : within ±12.5%	With 150% of the rated voltage
Resistance	Tan δ: 0.125 max	Max. operating temperature
	IR : 25MΩ·μF or Over	
		1000+48/-0hrs
Temperature	Capacitance change : within ±7.5%	1 cycle condition
Cycling	Tan δ, IR : initial spec.	Min. operating temperature → 25 °C
		→ Max. operating temperature → 25°C
		5 cycle test

#### C. Recommended Soldering method:

Reflow ( Reflow Peak Temperature : 260+0/-5°C, 10sec. Max )



A Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.

## **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Multilayer Ceramic Capacitors MLCC - SMD/SMT category:

Click to view products by Samsung manufacturer:

Other Similar products are found below:

M39014/01-1467 M39014/02-1218V M39014/02-1225V M39014/02-1262V M39014/02-1301 M39014/22-0631 1210J5000102JCT 1210J2K00102KXT 1210J5000103KXT 1210J5000223KXT D55342E07B379BR-TR D55342E07B523DR-T/R 1812J1K00103KXT 1812J1K00473KXT 1812J2K00680JCT 1812J4K00102MXT 1812J5000102JCT 1812J5000103JCT 1812J5000682JCT NIN-FB391JTRF NIN-FC2R7JTRF NPIS27H102MTRF C1206C101J1GAC C1608C0G1E472JT000N C2012C0G2A472J 2220J2K00101JCT KHC201E225M76N0T00 LRC-LRF1206LF-01R025FTR1K 1812J1K00222JCT 1812J2K00102KXT 1812J2K00222KXT 1812J2K00472KXT 2-1622820-7-CUT-TAPE 2220J3K00102KXT 2225J2500824KXT CCR07CG103KM CGA2B2C0G1H010C CGA2B2C0G1H040C CGA2B2C0G1H050C CGA2B2C0G1H060D CGA2B2C0G1H070D CGA2B2C0G1H151J CGA2B2C0G1H1R5C CGA2B2C0G1H2R2C CGA2B2C0G1H3R3C CGA2B2C0G1H680J CGA2B2C0G1H6R8D CGA2B2X8R1H221K CGA2B2X8R1H472K CGA3E1X7R1C474K