

Grounding & Cleaning

If the material is used on top of an already properly grounded surface, grounding hardware may not be necessary. Where no properly grounded surface is available, grounding hardware is required to provide a path-to-ground. Rtg compliance verification measurements must be made as outlined in ESD TR53 with a surface resistance meter.

2-Layer

See Tech Bulletin TB-7000 for Reztore™ Surface & Mat Cleaner Application Instructions.

RoHS 3, REACH, and Conflict Minerals Statement See the Desco Industries RoHS 3, REACH, and Conflict Minerals Statement:

http://www.descoindustries.com/ROHS.aspx

See the Desco Limited Warranty:

http://desco.descoindustries.com/Limited-Warranty.aspx

See the Desco Disclaimer:

http://desco.descoindustries.com/Disclaimer.aspx

Specifications and procedures subject to change without notice.

DESCO

STATFREE T2™ DISSIPATIVE RUBBER



Specifications

Standard Document Meets Requirements of:

ANSI/FSD S20 20 Worksurface

Electrical Properties Typical Values Test Procedures/Method

Color Dissipative Layer

Rtt Resistance: 1×10^6 to $< 1 \times 10^9$ ohms ANSI/ESD S4.1 and ESD TR53 Rta Resistance: 1×10^6 to $< 1 \times 10^9$ ohms ANSI/ESD S4.1 and ESD TR53

More Conductive Black Laver

Rtt Resistance: $< 1 \times 10^{6} \text{ ohms}$ ANSI/ESD S4.1 and ESD TR53

Physical Properties

Construction: Dual-layer rubber material

Thickness: 0.060" (1.5mm)

Color·* Blue (Top), Dark Blue (Top), Dark Grey (Top), Green (Top), Black (Bottom)

Texture:* Slight embossed

Weiaht: 0.43 lbs./sq. ft. (0.2a/cm2)

65 ± 5 Shore "A", per ASTM-D2240 Hardness:

Other Properties

Heat Resistance Does not melt or burn when coming into contact with hot solder and soldering irons. Chemical Resistance: Resistance to degradation by inorganic acids, organic acids, reducing agents, aliphatic

hydrocarbons, mineral oil, aldehydes, and amines.

Tolerances:

Width + 0.250"

Length ± 0.250" every 1 linear foot of running material.

Thickness ±10%

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to condition for at least 4 hours before cutting to size. Always using care trim with a sharp knife or razor blade.

*Color and texture may vary between lots and mills.

For product listings, Click Here



United States of America

**Tray liners have 3/4" radius corners and do not include grounding hardware.

STATFREE T2™ DISSIPATIVE, RUBBER, 2-LAYER, 0.060" (1.5mm)

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407

PHONE (781) 821-8370

MATERIAL STATFREE T2™ **DRAWING PM-104**

DATE: May 2017