

## Introducing

Raychem RT-780 Heat-Shrink Tubing (Orange color)

for Indicating High Power Circuits in Vehicles and Equipment



# RT-780 Orange Tubing



### **KEY FEATURES**

Provided or supplied in an orange color to easily identify high power circuits

Tubing has been hardened to withstand the damaging effect of NBC contamination and decontamination

Tubing meets all of the flammability and fluid resistance demands of current military ground vehicles

Temperature rating -55°C to +175°C

### **DESCRIPTION**

A special version of our 780 tubing has been created for indicating high power circuits in electrical propulsion systems. This orange color tubing meets all requirements of RT-780 Type I product and is compatible with RT-780 Type 2 molded parts and RT-1014 adhesive.

Product is provided in similar spool quantities as RT-780 standard tubing material.

### **APPLICATIONS**

Indication for high amperage circuits and high power voltage circuits

High voltage electrical propulsion system in auxillary and commercial service vehicles

### **TEMPERATURE RATING**

System 780  $-55^{\circ}$ C to  $+175^{\circ}$ C

#### STANDARDS & SPECS

Tested to TE RT-780 specification additionally to SCX-115112 or SCX-15111 for survivability in standard military vehicle fluids at elevated temperatures.

	Wire	Tubing	<b>Molded Parts</b>	Adhesive
System 780	SPEC 55	RT-780 Type 1	RT-780 Type II	RT-1014
System 30	SPEC 55	RT-780 Type 1	-50 Shapes	RT-1014

### **KEY COMPONENTS**

Description	System 780	System 30
Heat-shrinkable tubing	RT-780-x/x-3	RT-780-x/x-3
Molded part - boot (black)	-780	-50
Molded part - transition (black)	-780	-50
Adhesive	S1255-04 or S1264	S1255-04
Wire - primary	SPEC 55	SPEC 55
Marker sleeve	NBC-SCE	HT-SCE
Marker protection sleeve	RT-375	RT-375
Cable	Thermorad 780	Thermorad HT



### **PRODUCT DIMENSIONS**

	As Su	pplied			R	ecovered Di	imensions			
	Inside D	iameter	Inside D	iameter			Wall Thi	ckness		
	Minii	mum	Maxi	mum	Minin	num	Maxin	num	Nom	inal
Size	in.	mm	in.	mm	in.	mm	in.	mm	in.	mm
3/8	0.375	9.50	0.187	4.74	0.018	0.46	0.024	0.61	0.020	0.51
1/2	0.500	12.70	0.250	6.35	0.020	0.51	0.026	0.66	0.022	0.56
5/8	0.625	15.90	0.312	7.93	0.023	0.58	0.030	0.76	0.026	0.66
3/4	0.750	19.05	0.375	9.50	0.029	0.74	0.036	0.91	0.032	0.81
1	1.000	25.40	0.500	12.70	0.034	0.86	0.041	1.04	0.037	0.99
1-1/4	1.250	31.75	0.625	15.87	0.037	0.94	0.044	1.12	0.040	1.01
1-1/2	1.500	38.10	0.750	19.05	0.041	1.04	0.048	1.22	0.045	1.14
2	2.000	50.80	1.000	25.40	0.044	1.12	0.052	1.32	0.048	1.22

### **PHYSICAL**

Property	Unit	RT-780 Type I	Test	
	O.III	Tubing	Method	
Dimensions	Inches (mm)	In accordance with	RT-780	
		Table 1		
Tensile Strength	Psi (MPa)	3000 (20.7) minimum	ASTM D 412	
Ultimate Elongation	Percent	300 minimum	ASTM D 412	
Secant Modulus (expanded), 2%	Psi (MPa)	50,000 (345) maximum	ASTM 882	
Specific Gravity	_	2.0 maximum	ASTM D 792	
Low Temperature Flexibility	_	No cracking	RT-780	
4 hours at -55±3°C (-65±5°F)				
Heat Shock	_	No dripping, flowing	RT-780	
4 hours at 275±5°C (527±9°F)		or cracking		
Heat Resistance			RT-780	
336 hours at 200±3°C (392±5°F)				
Followed by tests for:				
Tensile Strength	Psi (MPa)	2000 (13.8) minimum	_	
Ultimate Elongation	Percent	250 minimum	_	

### **ELECTRICAL**

Property	Unit	RT-780 Type I	Test	
Troporty	Oiiit	Tubing	Method	
Dielectric Strength	Volts/mil	200 (7.9) minimum	ASTM D 149	
(kV/mm)				
Volume Resistivity	Ohm-cm	1 x 10 <sup>11</sup> minimum	ASTM D 257	

### **NUCLEAR**

Property	Unit	RT-780 Type I	Test	
	Omit	Tubing	Method	
Radiation Resistance -10 Mrads gamma			RT-780	
Followed by tests for:				_
Tensile Strength	Psi (MPa)	2000 (13.8) minimum		
Ultimate Elongation	Percent	150 minimum		

### **CHEMICAL**

Copper Mirror Corrosion
16 hours at 175±3°C (347±5°F)
Water Absorption 24 hours at 23±3°C (73±5°F)         Percent         0.5 maximum         ASTM D 570           Flammability         1) 25% max. flag burn 2) No flaming or glowing longer than 30 seconds         ASTM D 2671           Average Burn Time Average extent of burning         Seconds Inches         ASTM D 635-98           Fluid Resistance 24 hours at 23±3°C (73±5°F) a) JP-8 Jet Fuel (MIL-DTL-83133)         RT-780           Followed by tests for: Tensile Strength Ultimate Elongation         Psi (MPa) Percent         2000 (13.8) minimum Percent           24 hours at 50±3°C (122±5°F) a) Bore Cleaner (MIL-PRF-372 b) Diesel Fuel DF-2 (A-A-52557A) c) Anti-loing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)         Psi (MPa) Percent         2000 (13.8) minimum Percent           Followed by tests for: Tensile Strength         Psi (MPa) Percent         250 minimum
24 hours at 23±3°C (73±5°F)
Average Burn Time
- 2) No burning of cotton 3) No faming or glowing longer than 30 seconds  Average Burn Time Seconds - ASTM D 635-98  Average extent of burning Inches  Fluid Resistance RT-780  24 hours at 23-3°C (73±5°F) a) JP-8 Jet Fuel (MIL-DTL-83133)  Followed by tests for: Tensile Strength Percent Percent Percent Percent Percent S maximum  Weight Increase Percent S maximum  24 hours at 50±3°C (122±5°F) a) Bore Cleaner (MIL-PRF-372 b) Diesel Fuel DF-2 (A-A-52557A) c) Anti-lcing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-23699) g) Followed by tests for: Tensile Strength Psi (MPa) 2000 (13.8) minimum  Followed by tests for: Tensile Strength Psi (MPa) 2000 (13.8) minimum  Ultimate Elongation Percent 250 minimum
Average Burn Time
Average Burn Time
Note
Fluid Resistance 24 hours at 23±3°C (73±5°F) a) JP-8 Jet Fuel (MIL-DTL-83133)  Followed by tests for: Tensile Strength Ultimate Elongation Weight Increase 24 hours at 50±3°C (122±5°F) a) Bore Cleaner (MIL-PRF-372 b) Diesel Fuel DF-2 (A-A-52557A) c) Anti-lcing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent Psi (MPa) 2000 (13.8) minimum Ultimate Elongation Percent 250 minimum  Percent 250 minimum  RT-780  RT-780
a) JP-8 Jet Fuel (MIL-DTL-83133)  Followed by tests for:  Tensile Strength Ultimate Elongation Weight Increase Percent 250 minimum  24 hours at 50±3°C (122±5°F) a) Bore Cleaner (MIL-PRF-372 b) Diesel Fuel DF-2 (A-A-52557A) c) Anti-Icing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-2104) f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Psi (MPa) 2000 (13.8) minimum Ultimate Elongation Percent 250 minimum
Followed by tests for:  Tensile Strength Ultimate Elongation Percent Smaximum  24 hours at 50±3°C (122±5°F) a) Bore Cleaner (MIL-PRF-372 b) Diesel Fuel DF-2 (A-A-52557A) c) Anti-Icing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-2104) f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent Psi (MPa) Percent
Tensile Strength Ultimate Elongation Percent Ultimate Elongation Percent  250 minimum Percent  3 maximum  24 hours at 50±3°C (122±5°F) a) Bore Cleaner (MIL-PRF-372 b) Diesel Fuel DF-2 (A-A-52557A) c) Anti-Icing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-2104) f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent  250 minimum  2000 (13.8) minimum Percent  250 minimum
Ultimate Elongation  Weight Increase  24 hours at 50±3°C (122±5°F)  a) Bore Cleaner (MIL-PRF-372  b) Diesel Fuel DF-2 (A-A-52557A)  c) Anti-Icing Fluid (SAE-AMS-1424)  d) Salt-5% solution (ASTM D 632)  e) Lubricating Oil (MIL-PRF-2104)  f) Lubricating Oil (MIL-PRF-23699)  g) Arctic Lube (MIL-PRF-46167)  h) Cleaning Compound (A-A-59133)  i) Electrolyte (P/N 10873919)  Followed by tests for:  Tensile Strength  Ultimate Elongation  Percent  250 minimum  250 minimum  Percent  250 minimum
Weight Increase Percent 3 maximum  24 hours at 50±3°C (122±5°F) a) Bore Cleaner (MIL-PRF-372 b) Diesel Fuel DF-2 (A-A-52557A) c) Anti-Icing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-2104) f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent  250 minimum
24 hours at 50±3°C (122±5°F) a) Bore Cleaner (MIL-PRF-372 b) Diesel Fuel DF-2 (A-A-52557A) c) Anti-Icing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-2104) f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent  250 minimum  Percent
a) Bore Cleaner (MIL-PRF-372 b) Diesel Fuel DF-2 (A-A-52557A) c) Anti-Icing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-2104) f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent  250 minimum
b) Diesel Fuel DF-2 (A-A-52557A) c) Anti-Icing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-2104) f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation  Percent  Psi (MPa) 2000 (13.8) minimum Percent
c) Anti-Icing Fluid (SAE-AMS-1424) d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-2104) f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent  Tensile Strength Percent Psi (MPa) Percent Psi minimum Percent
d) Salt-5% solution (ASTM D 632) e) Lubricating Oil (MIL-PRF-2104) f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent 250 minimum
e) Lubricating Oil (MIL-PRF-2104) f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent 250 minimum
f) Lubricating Oil (MIL-PRF-23699) g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for:  Tensile Strength Ultimate Elongation Percent 250 minimum
g) Arctic Lube (MIL-PRF-46167) h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent 250 minimum
h) Cleaning Compound (A-A-59133) i) Electrolyte (P/N 10873919)  Followed by tests for:  Tensile Strength  Ultimate Elongation  Percent  250 minimum
i) Electrolyte (P/N 10873919)  Followed by tests for: Tensile Strength Ultimate Elongation Percent 250 minimum Percent
Followed by tests for: Tensile Strength Ultimate Elongation Psi (MPa) 2000 (13.8) minimum Percent 250 minimum
Tensile Strength
Ultimate Elongation Percent 250 minimum
•
Weight Increase Percent 3 maximum
24 hours at 71±3°C (160±5°F)
Hydraulic, synthetic
(MIL-PRF-46170)
Followed by tests for:
Tensile Strength Psi (MPa) 2000 (13.8) minimum
Ultimate Elongation Percent 250 minimum
Weight Increase Percent 3 maximum
4 hours at 23±3°C (73±5°F) RT-780
a) Decontaminating Agent, DS-2 (MIL-D-50030)
b) Decontaminating Agent, STB
(MIL-DTL-12468)
5% Solution
Followed by tests for:
Tensile Strength Psi (MPa) 2000 (13.8) minimum
Ultimate Elongation Percent 250 minimum
Weight Increase Percent 3 maximum

### **ORDERING INFORMATION**


TE Connectivity offers a complete system of Raychem brand and other TE brand components that may be used for rugged military grade or NBC contamination survivable applications/requirements.

Examples of these components include Tinel-Lock backshells, CRES-Lock band adapters, molded parts, adhesives, heat-shrinkable tubing, over-braids, interconnection soldering devices, wires, cables, connectors, contacts, etc.

Part numbers, product sizes, additional characteristics of products can be found in Specification Control Drawings and Raychem RT or RW specifications. Contact a TE representative or visit www.te.com\ADM for more detailed information.

### **PART NUMBERING\***

#### **TUBING**



#### FOR MORE INFORMATION

#### **Technical Support**

www.te.com/ADM Internet: USA: +1 (800) 522-6752 Canada: +1 (905) 470-4425 +52 (0) 55-1106-0814 Mexico: +52 (0) 55-1106-0814 C. America: +55 (0) 11-2103-6000 South America: Germany: +49 (0) 6251-133-1999 +44 (0) 8706-080208 Great Britain: +33 (0) 1-3420-8686 France: +31(0) 73-6246-999 Netherlands: +86 (0) 400-820-6015 China:

Follow us on Twitter for all the latest product news @TEConnectivity, and on Facebook, TEConnectivity.

#### www.te.com/ADM

© 2012 Tyco Electronics Corporation. All Rights Reserved.

5-1773457-2 ADM/RRD 2.5M 01/2012

CRES-Lock, Raychem, SPEC 55, Thermorad, Tinel-Lock, TE Connectivity and the TE connectivity (logo) are trademarks of the TE Connectivity Ltd. family of companies.

Other products, logos, and company names mentioned herein may be trademarks of their respective owners.

While TE has made every reasonable effort to ensure the accuracy of the information herein, nothing herein constitutes any guarantee that such information is error-free, or any other representation, warranty or guarantee that the information is accurate, correct, reliable current. The TE entity issuing this publication reserves the right to make any adjustments to the information contained herein at any time without notice. All implied warranties regarding the information contained herein, including, but not limited to, any implied warranties of merchantability or fitness for a particular purpose are expressly disclaimed. The dimensions herein are for reference purposes only and are subject to change without notice. Specifications are subject to change without notice. Consult TE for the latest dimensions and design specifications.

