

SPECIFICATION CONTROL DRAWING


55PC2222

TITLE TWO CONDUCTOR CABLE, FLAT BRAID SHIELDED, JACKETED, 600 VOLT

Date 2-12-96

Revision C

This specification sheet forms a part of the latest issue of Raychem Specification 55PC.



CONSTRUCTION DETAILS

PART NUMBER	CONDUCTOR SIZE (AWG)	SHIELD STRAND THICKNESS (± .0004)	JACKET THICKNESS (in.)		DIAMETER (in.)			WEIGHT (lbs/1000 ft.)	
			LOWER SPEC LIMIT	TARGET WALL	LOWER SPEC LIMIT	TARGET VALUE	UPPER SPEC LIMIT	TARGET VALUE	UPPER SPEC LIMIT
55PC2222-26-*	26	.0015	.0060	.0075	.087	.092	.097	5.88	6.38
55PC2222-24-*	24	.0015	.0060	.0075	.096	.101	.105	7.49	8.01
55PC2222-22-*	22	.0015	.0060	.0075	.108	.113	.118	9.84	10.48
55PC2222-20-*	20	.0015	.0060	.0080	.126	.131	.136	13.63	14.30
55PC2222-18-*	18	.0015	.0060	.0080	.144	.150	.155	18.85	19.72
55PC2222-16-*	16	.0015	.0060	.0080	.159	.165	.170	23.08	24.07
55PC2222-14-*	14	.0015	.0065	.0085	.190	.196	.201	33.59	34.76
55PC2222-12-*	12	.0015	.0070	.0090	.228	.235	.241	49.25	50.80
55PC2222-10-*	10	.0015	.0075	.0095	.276	.284	.291	74.61	76.79

CABLE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C
 Maximum continuous conductor temperature
 VOLTAGE RATING: 600 volts (rms)
 DIELECTRIC WITHSTAND: 1500 volts (rms), 60 Hz
 CROSSLINK VERIFICATION: 300 ± 3°C for 1 hour
 JACKET COLOR: White preferred
 JACKET ELONGATION AND TENSILE STRENGTH:
 Elongation, 50% (minimum)
 Tensile Strength, 5000 lbf/in² (minimum)
 JACKET FLAWS:
 Spark Test, 1000 volts (rms), 60 Hz, 100% test
 Impulse Dielectric Test, 6.0 kV (peak), 100 % test

SHIELD COVERAGE: 85% (minimum)
 VOLTAGE WITHSTAND TEST (POST ENVIRONMENTAL):
 1000 volts (rms), 60 Hz, 1 minute

PART NUMBER:
 The "*" in the part numbers above shall be replaced by a color code designator with a slash separating the component wire colors and a dash separating the component wire colors from the jacket color.
 Example: AWG 24, red and blue component wires; white jacket: 55PC2222-24-2/6-9

COLOR AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-881.

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HERIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.

Raychem

Raychem Corporation
 300 Constitution Drive, Menlo Park, California 94025
 1-800-2 Raychem Fax: 1-415-361-8297