Specification No.	Q/WAPL503562-1011
Edition No.	1.0

Polymer Lithium-ion Battery

Product Specification

Model: <u>503562 1200mAh</u>

Hunan Sounddon New Energy Co., Ltd Address:No.98, Fuzhou Road, Jinhua Demonstration Area, Xiangtan City, Hunan Province, China.

http://www.soundnewenergy.com

Tel: (86) 731 - 5856 7126 Fax: (86) 731 - 5823 6346

E-mail:linda.ding@soundnewenergy.com

Prepared by: Sunping

Checked by: Zhu Qi

Approve by: Jin Gang

All 10 pages

Polymer Lithium-ion battery	Doc. No.	Q/WAPL503562-1011
1 ory mer Entirum-ion battery	Edition No.	1.0
Product Specification		2/10

1, Scope

This product specification describes polymer lithium-ion battery. Please using the test methods that recommend in this specification. If you have any opinions or advices about the test items and methods, please contact us. Please read the cautions recommended in the specifications first, take the credibility measure of the cell's using.

If the cells should be using at the environment that not preferred in this document, please connect with our first and get our authorization. For the reason of stable performance and better safety, battery pack with more than 2 cells connected in serial way should be charged with a balance charger.

It is claimed that we should have no any responsibility with the contingency and loss due to the cells' wrong usage (not preferred in the product specification).

2, Product Type, Model and Dimension

2.1 Type: Polymer lithium-ion battery

2.2 Model: 503562(Cell adding Ni Tabs)

2.3 Cell Dimension(Max, Thickness × Width × Length, mm³): 5.0 × 35 × 62

Pack Dimension(Max, ThicknessWidth×Length, mm³): 5.2*35.5*62.5(with pcm)

3. Specification

Item		Specifications	Remark
Nominal Ca	pacity	<u>1200</u> mAh	0.2C ₅ A discharge, 25°C
Nominal V	oltage	3.75V	Average Voltage at 0.2C ₅ A discharge
Standard Cha	rge Current	$0.2~\mathrm{C_5A}$	Working temperature: $0\sim40^{\circ}$ C
Max Charge	Current	$1C_5A$	Working temperature: 0~40°C
Charge cut-of	f Voltage	4.2V	CC/CV
Standard Discharge Current		$0.5C_5A$	Working temperature: 25°C
Discharge cut-off Voltage		2.75V	
Cell Voltage		3.7-3.9V	When leave factory
Impedance		≤50 m Ω	AC 1KHz after 50% charge,25℃
Weight		Approx:22g	
Storage	≤1month	-10~45℃	
temperature	≤3month	0~30℃	Best 20±5℃ for long-time
	≤6month	20±5℃	storage
Storage hui	nidity	$65\pm20\%$ RH	

4. General Performance

Definition of Standard charging method: At 20 ± 5 °C, charging the cell initially with constant current $0.2C_5A$ till voltage 4.2V, then with constant voltage 4.2 till current declines to $0.05C_5A$.

Polymer Lithium-ion battery	Doc. No.	Q/WAPL503562-1011
1 orymer Entirum-ion battery	Edition No.	1.0
Product Specification		3/10

Item Test Methods Perform		Performance
	After standard charging, laying the battery 0.5h,	then
0.2C Capacity	discharging at 0.24A to voltage 2.75V, recording	the ≥300min
	discharging time.	
	After standard charging, laying the battery 0.5h,	then
1C Capacity	discharging at 1C ₅ A to voltage 2.75V, recording the discharging	≥54min
	time.	
	Constant current 0.5C ₅ A charge to 4.2V, then constant voltage	
Cyala Lifa	charge to current declines to QA5C stay 5min constant	≥400times
Cycle Life	current 0.5C ₅ A discharge to 2.75V, stay 5min. Repeat above	=400times
	steps till continuously discharging time less than 36min.	
Capability of 20±5°C, After standard charging, laying the battery 28days,		
keeping	discharging at 0.26 to voltage2.75V, recording	the ≥240min
electricity	discharging time.	
	0.2C Capacity 1C Capacity Cycle Life Capability of keeping	After standard charging, laying the battery 0.5h, discharging at 0.2\(\Omega\) to voltage 2.75V, recording discharging time. After standard charging, laying the battery 0.5h, discharging at 1C5A to voltage 2.75V, recording the discharging time. Constant current 0.5C5A charge to 4.2V, then constant voltage charge to current declines to 0.45C stay 5min constant current 0.5C5A discharge to 2.75V, stay 5min. Repeat above steps till continuously discharging time less than 36min. Capability of keeping discharging at 0.2\(\Omega\) to voltage 2.75V, recording the battery 28days, discharging at 0.2\(\Omega\) to voltage 2.75V, recording

5. Environment Performance

	Item	Test Methods	Performance
5.1	High temperature	After standard charging, laying the battery 4h at 60° C, then discharging at $0.2C_5$ A to voltage 2.75V, recording the discharging time.	≥270min
5.2	Low temperature	After standard charging, laying the battery 4h at -10° C, then discharging at $0.2C_5$ A to voltage 2.75V, recording the discharging time.	≥210min
5.3	Constant humidity and temperature	After standard charging, laying the battery 48h at $40\pm$ 2° C, RH 93 \pm 2%. Recording 0.2C ₅ A discharging time	No distortion No electrolytes leakage ≥270 min
5.4	Temperature shock	After standard charging, battery stored at -20°C for 2 hours, then stored at 50°C for 2 hours. Repeat 10 times.	No electrolytes leakage

6. Mechanical Performance

Polymer Lithium-ion battery	Doc. No.	Q/WAPL-503562-1011
	Edition No.	1.0
Product Specification		4/10

	Item	Test Methods Performance	
6.1	Vibration	After standard charging, put battery on the vibration table. 30 min experiment from X,Y ,Z axis. Scan oct/min; Frequency 10-30Hz, Swing 0.38mm; Frequency appearance.	
6.2	Collision	After vibration test, batteries were laying on the vibration table about X, Y, Z axis. Max frequency acceleration: electrical performance and 100m/s^2 ; collision times per minutes: $40 \sim 80$; frequency appearance.	
6.3	Drop	Random drop the battery from 10m height onto concrete one times.	No explosion or fire

7. Safety Test

Test conditions: The following tests must be measured at flowing air and safety protection conditions. All batteries must standard charge and lay 24h.

	Item	Test Methods Performance	
7.1	Over charge	At 20±5°C, charging batteries with constant current 3C ₅ A to voltage5V, then with constant voltage5V till current decline to 0. Stop test till batteries' temperature 10°C lower than max temperature.	
7.2	Over discharge	At $20\pm$ 5 °C , discharge battery with 0.20°C No explosion or fire continuously 12.5h.	
7.3	Short-circuit	At $20\pm5^{\circ}$ C, connect batteries' anode and cathode by wire which impedance less than 50 m $_{\Omega}$, keep 6h.	
7.4	Extrusion	At 20 ± 5 °C, put the battery in two parallel steal broad, add pressure 13kN. No explosion or fire	

		Put the battery in the oven. The temperature of the oven	
7.5	Thermal shock	is to be raised at $5\pm1^{\circ}$ C per minute to a temperature of 130	No explosion or fire
		$\pm 2^{\circ}$ C and remains 60 minutes.	

8. Cautions

8.1 Cautions of batteries' operation

Polymer Lithium-ion batteryDoc. No.Q/WAPL503562-1011Edition No.1.0Product Specification5/10

The batteries must be careful of proceed the operation for its soft package.

8.1.1 Aluminum packing materials

The aluminum packing material was easily damaged by the sharp edge part, such as nickel-tabs.

- (1) forbid to use the sharp part touching the battery;
- (2) should cleaning working condition, avoiding the sharp edge part existence;
- (3) forbid to pierce the battery with nail and other sharp items;
- (4) the battery was forbidden with metal, such as necklace, hairpin etc in transportation and storage.

8.1.2 Sealed edge

Sealing edge is very easily damaged and don't bend it.

The Al interlayer of package has good electric performance. It's forbidden to connect with exterior component for preventing short-circuits.



Fig.1. Exterior schematic of polymer lithium-ion cells

8.1.3 Folding edge

The folding edge is formed in batteries' processes and passed all hermetic tests, don't open or deform it. The Al interlayer of package has good electric performance. It's forbidden to connect with exterior component for preventing short-circuits.

Polymer Lithium-ion battery

Product Specification

Doc. No.	Q/WAPL503562-0811
Edition No.	1.0
	6/10



Fig.2. Single folding edge schematic of PL cells schematic of PL cells

Fig.3. Reverse folding edge

8.1.4 Tabs

- (1) The batteries' tabs are not so stubborn especially for aluminum tabs. Don't bend tabs.
- (2) The tab-tapes are used to isolate The anode /cathode tabs from Aluminum packing materials to prevent short-circuit, so prohibit manicuring of the tab-tapes.

8.1.5 Mechanical shock

- (1) Don't fall, hit, bent the batteries' body.
- (2) Don't knock on by sinker or trample the batteries.
- (3) Don't sling the batteries.

8.1.6 Short-circuit

Short-circuit is strictly prohibited. It should damage batteries badly.

- (1) Don't connect the anode and cathode of the batteries to avoid short-circuit.
- (2) Prohibit short-circuit of the anode (or cathode) and aluminum layer of Aluminum packing materials.

8.2 Standard Test Environment for polymer lithium-ion batteries

Environment temperature: $20 \pm 5^{\circ}$ C Humidity: 45-85%

8.3 Cautions of charge & discharge

8.3.1 charge

Charging current should be lower than values that recommend below. Higher current and voltage charging may cause damage to cell electrical, mechanical, safety performance and could lead heat generation or leakage.

- (2) Batteries charger should charging with constant current and constant voltage mode;
 - (2) Charging current should be lower than (or equal to)1ÇA;

Polymer Lithium-ion battery Product Specification

Doc. No.	Q/WAPL503562-1011
Edition No.	1.0
	7/10

- (3) Temperature $0 \sim 40^{\circ}$ C is preferred when charging;
- (4) Charging voltage must be lower than 4.25V.

8.3.2 discharge

- (1) Discharging current must be lower than (or equal to)2GA;
- (2) Temperature $0 \sim 60^{\circ}$ C is preferred when discharging;
- (3) Discharging voltage must not be lower than 2.75V.

8.3.3 over-discharge

It should be noted that the cell would be at an over-discharge state by its self-discharge. In order to prevent over-discharge, the cell shall be charged periodically to keeping voltage between 3.7-3.9V. Over-discharge may cause loss of cell performance. It should be noted that the cell would not discharge till voltage lower than 2.75V.

8.4 Storage of polymer lithium-ion batteries

The environment of long-time storage:

Temperature: $20 \pm 5 \degree \text{C}$; Humidity: 45-85%;

Batteries were $40\sim60\%$ charged.

In case of over-discharge, batteries should be charged for one time every 3 months while storing. Batteries should be discharged and charged after being stored more than a year in order to activate it and restore energy. Please charge the battery with constant current $0.5C_5A$ for 1 hour so that it has some storage of charge for properly using.

Charge and discharge afresh to active and renew battery energy after storage above 1 year.

8.5. Transportation of polymer lithium-ion batteries

The batteries should transportation with $10\sim50\%$ charged states.

8.6. Others

Please note cautions below to prevent cells' leakage, heat generation and explosion.

Prohibition of disassembly cells;

Prohibition of cells immersion into liquid such as water or seawater;

Prohibition of dumping cells into fire;

Prohibition of using damaged cells. The cells with a smell of electrolyte or leakage must be placed away from fire to avoid firing.

In case of electrolyte leakage contact with skin, eye, physicians shall flush the electrolyte immediately with fresh water and medical advise is to be sought.

9. Notice of Designing Battery Pack

9.1 Pack design

Polymer Lithium-ion battery Product Specification

Doc. No.	Q/WAPL503562-1011			
Edition No.	1.0			
	8/10			

Battery pack should have sufficient strength and battery should be protected from mechanical shock. No sharp edge components should be inside the pack contains the battery.

9.2 PCM design

The overcharge threshold voltage should not be exceeding 3.95V.

The over-discharge threshold voltage should not be lower than 2.3V.

The PCM should have short protection function built inside.

9 3 Tab connection

Ultrasonic welding or spot welding is recommended to connect battery with PCM or other parts.

If apply manual solder method to connect tab with PCM, the notice below is very important to ensure battery performance.

- (1) The electric iron should be temperature controlled and ESD safe;
- (2) Soldering temperature should not exceed 350°C;
- (3) Soldering time should not be longer than 3s, keep battery tab cold down before next soldering;
 - (4) Soldering times should not exceed 5 times;
- $^{(5)}$ Directly heat cell body is strictly prohibited, battery may be damaged by heat above approx. $100\,^{\circ}\!\text{C}.$

9.4 Cell fixing

The battery should be fixed to the battery pack by its large surface area. No cell movement in the battery pack should be allowed.

9.5 Cells replacement

The cell replacement should be done by professional people.

Prohibit short-circuit between cells' Al package and exterior component.

Polymer Lithium-ion battery Product Specification

Doc. No.	Q/WAPL503562-1011
Edition No.	1.0
	9/10


Here is no insulated between


Sealed edge & protect component




Fig.4. Schematic of wrong assembly


10. Schematic of Battery:






□Cell adding wire







☐ Cell adding wire

Parameter: ✓

Sign	Item	Max (mm)	Remak	Sign	Item	Max (mm)	Remak
A	Length	62.2		L	Space between Tabs		
В	Width	35.5		Е	PP membrane Length	2.0	
Н	Thickness	5.2		b	Tab Width	3	
	Wire Standard	/			Plug Standard	,	/

1	Material	Specification
1	Battery cell	LP503562-1200mAh
2	Protection Board	IC: S-8261AAJMD, MOSFET 8814
3	Red wire (+)	UL 26AWG
4	Black wire (-)	UL 26AWG
5	Connectors	JST-PHR-2

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Adafruit Accessories category:

Click to view products by Adafruit manufacturer:

Other Similar products are found below:

3209 3561 3560 3562 2503 3011 3048 2973 2868 2958 2836 2968 3610 3568 3551 2858 3353 3584 3484 2865 3556 3559 3262 3348 2499 2878 2963 3219 3005 2882 PGM1202 02-LDR1 02-LDR12 02-LDR13 02-LDR14 02-LDR15 02-LDR2 02-LDR3 02-LDR4 2194 862 460 905 02-LDR20 02-LDR21 02-LDR22 02-LDR23 1008 1020 1031