TECHNICAL DATA SHEET



SN63/PB37 SOLDER ALLOY

FEATURES

- Liquidus 183°C (361°F)
- High Purity
- Low Dross
- Complies with IPC J-STD-006 Current Rev

DESCRIPTION

Sn63/Pb37 ElectropureTM is alloyed in a proprietary method resulting in a low drossing, high wetting solder. The Electropure process reduces suspended oxides in the solder, thus reducing drossing, improving flow, and reducing bridging during soldering. Applications include wave and selective soldering and plating where Sn63/Pb37 Electropure is primarily used as a coating for corrosion protection, and as a base for soldering.

AVAILABILITY

Sn63/Pb37 Electropure is available in 1.1 kg (2.5 lb) bars, 3 kg AIM Safety Bar and Solid Wire. Sn63/Pb37 Electropure is also available in AIM flux cored wire solder and solder paste.

TYPICAL ALLOY COMPOSITION

Typical Alloy Composition		
Sn: 63.0	Pb: 37.0	

TYPICAL MELTING TEMPERATURE

183°C (361°F) Eutectic



HANDLING & STORAGE

Parameter	Time	Temperature
Shelf Life	7 years	Room Temperature

Solid wire and bar solder products have a shelf life of 7 years under proper storage conditions. For other product categories, refer to those product specific TDS's. Consult the SDS for specific handling procedures.

FLUX COMPATIBILITY

Sn63/Pb37 Electropure bar solder is compatible with all RMA, no clean and water soluble electronic grade fluxes.

CLEANING

Refer to data sheets provided by the flux manufacturer.

SAFETY

Use with adequate ventilation and proper personal protective equipment. Refer to the accompanying Safety Data Sheet for any specific emergency information. Do not dispose of any hazardous materials in non-approved containers.

Document Rev # NF5 Page 1 of 1

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Solder category:

Click to view products by AIM manufacturer:

Other Similar products are found below:

600YSY 701-2758 707-0425 707-1746 707-1748 707-1811 707-1813 707-1831 707-1840 707-1850 707-1852 13-217-3-01 P10695 SN63WRAP3-.022-1-LB 24-6040-0007 DAC-061 599Z 701-2089 707-0285 707-0366 707-0441-26 707-1774 707-1810 24-6337-9727 601Y 24-9574-7619 24-4060-2437 14-6040-0125 04-0595-0000 V5S35[42G]217 V8B45[60G]138 V5B45[42G]138 V3B45[20G]138 XGS20[20G]158 631960 S2626-O-T 8055 5760140 TRWR-204 1152 EC2002M-1 WPT17 WS6016 760-2028 ART.AGT-030 54068 8S005 4900-18G 648107 811008