ASMT-TWBM / ASMT-TBBM / ASMT-TGBM

Surface Mount LED Indicator



Reliability Data Sheet

Description

The following cumulative test results have been obtained from testing performed at Avago Technologies in accordance with the latest revision of MIL-STD-883 and JEDEC.

Avago tests parts at the absolute maximum rated conditions recommended for the device. The actual performance you obtain from Avago parts depends on the electrical and environmental characteristics of your application but will probably be better than the performance outlined in Table 1.

Failure Rate Prediction

The junction temperature of the device determines the failure rate of semiconductor devices. The relationship between ambient temperature and actual junction temperature is given by the following:

$$T_J(^{\circ}C) = T_A(^{\circ}C) + \theta_{JA} P_{AVG}$$

Where;

 T_A = ambient temperature in (°C)

 θ_{JA} = thermal resistance of junction-to ambient in °C/watt

P_{AVG} = average power dissipated in watts

The estimated MTTF and failure rate at temperatures lower than the actual stress temperature can be determined by using an Arrhenius model for temperature acceleration. Results of such calculations are shown in the table below using activation energy of 0.43eV (reference MIL-HDBK-217).

Table 1. Life Tests
Demonstrated Performance

Colors	Stress Test Conditions	Total Device Hours	Units Tested	Units Failed	Point Typical Performance	
					MTBF (60% Confidence)	Failure Rate (%/1K Hrs)
Green	$T_A = 55$ °C, $I_F = 20 \text{ mA}$	56,000	56	0	61,100	1.64
Blue / Ice Blue / Cool White	$T_A = 55^{\circ}C$, $I_F = 18 \text{ mA}$	56,000	56	0	71,700	1.39

Reliability Prediction

Table 2a. Green (I_F = 20mA)

Ambient Temperature (°C)	Junction Temperature (°C)	Point Typical Performance in Time ^[1-5] (60% Confidence)		Performance (90% Confide	
		MTTF	Failure Rate (%/1K Hours)	MTTF	Failure Rate (%/1K Hours)
100	125	38500	2.60	15300	6.54
95	125	39200	2.55	15600	6.41
90	124	40000	2.50	15900	6.29
85	123	40700	2.46	16200	6.17
80	123	41500	2.41	16500	6.06
75	122	42300	2.36	16800	5.95
70	122	43100	2.32	17200	5.81
65	121	43900	2.28	17500	5.71
60	116	51700	1.93	20600	4.85
55	111	61100	1.64	24300	4.12
50	106	72500	1.38	28900	3.46
45	101	86500	1.16	34400	2.91
40	96	103600	0.97	41200	2.43
35	91	124700	0.80	49600	2.02
30	86	151000	0.66	60100	1.66
25	81	183700	0.54	73100	1.37

Table 2b. Blue / Ice Blue / Cool White ($I_F = 18mA$)

Ambient Temperature (°C)	Junction Temperature (°C)	Point Typical Performance in Time [1 - 5] (60% Confidence)		Performance in Time [1 - 5] (90% Confidence)	
		MTTF	Failure Rate (%/1K Hours)	MTTF	Failure Rate (%/1K Hours)
100	108	63800	1.57	25400	3.94
95	108	64600	1.55	25700	3.89
90	107	65400	1.53	26000	3.85
85	107	66300	1.51	26400	3.79
80	107	67100	1.49	26700	3.75
75	106	68000	1.47	27100	3.69
70	106	68900	1.45	27400	3.65
65	106	69800	1.43	27800	3.60
60	105	70700	1.41	28200	3.55
55	105	71700	1.39	28500	3.51
50	104	72600	1.38	28900	3.46
45	99	86700	1.15	34500	2.90
40	94	104100	0.96	41400	2.42
35	89	125600	0.80	50000	2.00
30	84	152200	0.66	60600	1.65
25	79	185600	0.54	73900	1.35

Notes:

- 1. The 60% or 90% confidence MTTF represents the minimum level of reliability performance which is expected from 60% or 90% of all samples. The confidence level is established based on the chi-square distribution.

 2. Failure rate (FIT) is 1/MTTF x 10⁵, assuming the failures are exponentially distributed
- 3. A failure is any LED that is open, shorted or fails to emit light.
- 4. Calculated from data generated at 55°C biased at 20mA (Green) 18mA (Blue/Ice Blue/Cool White).
- 5. Junction temperature is calculated based on $\theta_{JA} = 850^{\circ}\text{C/W}$

Example of Failure Rate Calculation

Assume a device operating 8 hours/day, 5 days/week. The utilization factor, given 168 hours/week is: (8 hours/day) x (5 days/week) / (168 hours/week) = 0.24

The point failure rate per year (8760 hours) at 25°C ambient temperature is (60% confidence level): $(0.54\%/1\text{K hours}) \times 0.24 \times (8760 \text{ hours/year}) = 1.13\% \text{ per year}$

Similarly, 90% confidence level failure rate per year at 25°C: $(1.35\%/1 \text{K hours}) \times 0.24 \times (8760 \text{ hours/year}) = 2.84\% \text{ per year}.$

Table 3. Environmental Tests

Test Name	Reference	Test Conditions	Units Tested	Units Failed
Temperature Cycle	Avago Req.	-40/100°C 15 min dwell, 5 min transfer, 1000 cycles	468	0
Resistance to Soldering Heat	JESD 22-B106	260°C for 10 seconds, 2x	30	0
Temperature Humidity Power Cycle	Avago Req.	25/65°C, 95%RH Dwell time: $3 6 3$ hrs $I_F = 15$ mA, 5 mins on/off for 100cyc		0
Power Temperature Cycle	ver Temperature Cycle Avago Req. $-40/85^{\circ}$ C, Dwell time: 15 15 15 Min $I_F = 8$ mA, 5 mins on/off for 1000cyc		231	0
Unbiased AutoClave	nbiased AutoClave JESD22-A102 T _A = 121°C, 100%RH, Vapor Pressure = 205kPa for 96 hours		231	0
Temperature Humidity Storage Life			168	0
Temperature Humidity Operating Life			84	0
High Temperature Operating Life	JESD22-A108 $T_A = 85^{\circ}\text{C}$, $I_F = 8 \text{ mA for 1000 hours}$		84	0
Room Temperature Operating Life	JESD22-A108	$T_A = 25$ °C, $I_F = 20$ mA for 1000 hours	84	0



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Standard LEDs - SMD category:

Click to view products by Broadcom manufacturer:

Other Similar products are found below:

LTST-C19GD2WT LTST-N683GBEW LTW-170ZDC LTW-M140SZS40 598-8110-100F 598-8170-100F 598-8610-202F 67
22VRVGC/TR8 AAAF5060QBFSEEZGS HLMP-6305-L0011 ALMD-LB36-SV002 APT1608QGW 15-21UYC/S530-A3/TR8

EASV1803BA0 LS A676-P2S1-1 SML310BATT86 SML-512VWT86A SML-LX0606SISUGC/A SML-LXL1307SRC-TR SML
LXR851SIUPGUBC LT1ED53A FAT801-S AM27ZGC03 APB3025SGNC APFA3010SURKCGKQBDC APHK1608VGCA

APT2012QGW CLX6D-FKB-CN1R1H1BB7D3D3 LTST-C250KGKT LTW-020ZDCG LTW-21TS5 LTW-220DS5 JANTXM19500/521-02

UYGT801-S LO T67F-V1AB-24-1 YGFR411-H SML-LX0402IC-TR CMDA20AYAA7D1S CMDA16AYDR7A1X 339
1SURSYGW/S530-A2 598-8040-100F 598-8070-100F 598-8140-100F 598-8610-200F EAPL3527GA5 67-11/BHC-M1N2B8Y/2A0 SML
LXL1209SYC/ATR EASV3020YGA0 EAST16086YA5 CMD91-21VRC/TR7