CHEMTRONICS Technical Data Sheet

TDS # CWik

Chem-Wik® Rosin

PRODUCT DESCRIPTION

Chem-Wik® Rosin is especially designed for today's heat sensitive electronic components. The lighter mass, pure copper braid construction allows for better thermal conductivity, even at low temperatures. Chem-Wik® Rosin responds as much as 50% faster than conventional desoldering braids. This design minimizes overheating and requires less "contact" pressure for greater operator control. All sizes are coated with a Type "R" organic flux system.

- Requires little or no post solder cleaning
- No corrosive residues
- Optimized weave design for faster wicking and heat transfer
- Halide free
- Minimal risk of heat damage to components and circuit boards

TYPICAL APPLICATIONS

Chem-Wik[®] Rosin desoldering braid safely removes solder from:

- Thru-hole Components
- Surface Mount Device Pads
- BGA Pads
- Micro Circuits
- Terminals
- Lugs and Posts
- Identification Script

TYPICAL PRODUCT DATA AND PHYSICAL PROPERTIES

Chem-Wik [®] Rosin			
Flux Type:	Grade WW, Type "R"		
Clean-up Required	: No		
Military Specifications : MIL-F-14256F			
Shelf Life – 2 years from manufacturer date			

	Size	Size		
Part #	Inches	Metric		
2-5L	.030"	.76mm		
5-5L	.050"	1.27mm		
7-5L	.075"	1.91mm		
10-5L	.100"	2.54mm		

STATIC DISSIPATIVE PACKAGING

Static Dissipative packaging is available on all 5 foot bobbins. The static dissipative bobbins qualify as electrostatic discharge protective per DOD Standard 1686 and DOD Handbook 263. Meets the static delay rate provision of MIL-B-81705C.

USAGE INSTRUCTIONS

For industrial use only.

Read MSDS carefully prior to use.

- 1) Choose a Chem-Wik® desoldering braid width equal to or slightly larger than the pad or connection.
- 2) Choose a solder iron tip equal to or slightly smaller than the pad or connection.
- 3) Set temperature of iron between 600-750°F
- 4) Place wick on solder joint and place tip of hot iron on top of wick

- 5) As solder becomes molten, the color of the wick will change from copper to silver.
- 6) Remove wick and iron from solder joint simultaneously once color change has stopped.
- 7) The component lead is now clean and free from solder.
- 8) Clip and discard the used portion of the wick.

AVAILABILITY

	Color	5 ft.	25 ft.	50 ft.	100 ft.	500 ft.
Width	Code	Bobbin	Spool	Spool	Spool	Spool
.030"	White	2-5L	2-25L	2-50L	2-100L	2-500L
.050"	Yellow	5-5L	5-25L	5-50L	5-100L	5-500L
.075"	Green	7-5L	7-25L	7-50L	7-100L	7-500L
.100"	Blue	10-5L	10-25L	10-50L	10-100L	10-500L

Chem-Wik®Rosin is designed to meet or exceed the following standards:

MIL-F-14256F, Type R

MIL-STD-2000A

MIL-B-81705C

NASA NHB5300.4(3A)

NASA SP-5002

NASA NPC200-4

IPC SF-818

DOD Handbook 263

DOD Standard 1686

BELLCORE TR-NWT-00078

TECHNICAL & APPLICATION ASSISTANCE

Chemtronics provides a technical hotline to answer your technical and application related questions. The toll free number is:

1-800-TECH-401.

NOTE:

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly.

CHEMTRONICS does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

CHEMTRONICS 8125 COBB CENTER DRIVE KENNESAW, GA 30152 1-770-424-4888 REV. D (08/13)

;	DISTR	RIBUTI	ED BY:		

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Solder Removal category:

Click to view products by Chemtronics manufacturer:

Other Similar products are found below:

532505-2 DS03-910-5 DP-CC STDC-102 T0054463299N T0054465499N T0058741815N T0052921799N T0054465299N T0054463199N T0051320399N 0ICV2000AC T0054466699N T0051317799N CLMU-A CLMU-PA T0053500699 T0053503699 0320705 0320800 0320903 0321200 0321300 0321400 0321500 0ICV2000AI 3280 51314400 51512599 C560-002 C560-003 C560-004 C560-005 WE51314000 DP-100 51315000 51315100 0IC2000AXT 0AS196 0LS197 0VACX 10-5L 80-5-10 S6169 SA21A MX-DCF1F 0119107 SP-108K CL6210 STDC-705L