

Technical Data Sheet

Rev. G (9/18) Page 1 of 2

Soder-Wick® Rosin Flux Desoldering Braid

Product Description

Soder-Wick® offers the state of the art in desoldering technology. Soder-Wick® is designed for today's heat sensitive electronic components using lighter mass, pure copper braid construction that allows for better thermal conductivity, even at low temperatures. Soder-Wick® responds faster than conventional desoldering braids thereby minimizing overheating and preventing PCB damage.

Soder-Wick Rosin has the fastest desoldering action in the industry. Flux residues must be cleaned after the rework process.

Typical Applications

Soder-Wick® desoldering braid safely removes solder from:

- Thru-hole Components
- SMT Pads and BGA Pads
- Micro Circuits
- Terminals
- Lugs and Posts
- Identification Script

Static Dissipative Packaging

Soder-Wick is packaged on Static Dissipative bobbins in 5 and 10-foot lengths to minimize the risk of damage associated with static electricity. The static dissipative bobbins qualify as electrostatic discharge protective per MIL-STD-1686C and MIL-HDBK-263B, and meet the static delay rate provision of MIL-B-81705C.





Typical Product Data and Physical Properties

Flux Tuno.	Docin Crada WW Type "D"
Flux Type:	Rosin Grade WW, Type "R"
	Patented No Clean
	High Temperature No Clean
Specifications:	ANSI/IPC J STD-004
	MIL-F-14256 F
Shelf Life:	2 years
RoHS Compliant	Yes

Part #	Size Inches	Color	Size Metric		
1	.030"	White/Gray	0.8mm		
2	.060"	Yellow	1.5mm		
3	.080"	Green	2.0mm		
4	.110″	Blue	2.8mm		
5	.145"	Brown	3.7mm		
6	.210	Red	5.3mm		

Rev. G (9/18) Page 2 of 2

Soder-Wick® Rosin Flux Desoldering Braid

Usage Instructions

For industrial use only. Read SDS carefully prior to use.

- Choose a Soder-Wick® braid width equal to or slightly larger than the pad or connection.
- 2) Choose a solder iron tip equal to or slightly larger than the pad or connection.
- 3) Set temperature of iron between 600-750°F.
- Place wick on solder joint and place tip of hot iron on top of wick.
- As solder becomes molten, the color of the wick will change from copper to silver.
- 6) Remove wick and iron from joint simultaneously once color change has stopped.
- The component lead / pad is now clean and free from solder.
- 8) Clip and discard used portion of the wick
- If needed, clean PCB with CircuitWorks Flux Remover Pen and remove soils with a ControlWipes absorbent wipe.

Availability

VacuPak™Packaging	Part #	Size	
The VacuPak™ Can contains	SW18015	1	
ten five-foot bobbins in a	SW18025	2	
vacuum sealed can. This package provides the highest	SW18035	3	
level of cleanliness and freshness. Great for tool kit	SW18045	4	
storage.	SW18055	5	

Soder-Wick Is Designed To Meet or Exceed the Following:

- MIL-F-14256F, Type R
- NASA-STD-8739.3
- DOD-STD-883E, Method 2022
- ANSI/IPC J STD-004, Type ROL0
- BELLCORE TR-NWT-000078
- ANSI/IPC J SF-818

HELPFUL HINTS:

Water Soluble Users: Use Soder-Wick Unfluxed 70 or 75 Series to dip in water soluble flux and then desolder normally.

Ball Grid Array: Use #6 red Soder-Wick with a large tipped iron to remove solder from a number of BGA pads all at once.

Technical and Application Assistance

Chemtronics provides a technical hotline to answer your technical and application related questions.

The toll free number is: 1-800-TECH-401.

Note:

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. CHEMTRONICS does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

Chemtronics®, Soder-Wick® and CircuitWorks® are registered trademarks of Chemtronics. All rights reserved. Vacu-Pak™ and ControlWipes™ are trademarks of Chemtronics. All rights reserved.

Part #	Size	Length	Part #	Size	Length	Part #	Size	Length	Part #	Size	Length	Part #	Size	Length
80-1-5	1	5′	80-1-10	1	10′	50-1-25	1	25′						
80-2-5	2	5′	80-2-10	2	10′	50-2-25	2	25′	50-2-100	2	100′	50-2-500	2	500′
80-3-5	3	5′	80-3-10	3	10′	50-3-25	3	25′	50-3-100	3	100′			
80-4-5	4	5′	80-4-10	4	10′	50-4-25	4	25′	50-4-100	4	100′			
80-5-5	5	5′	80-5-10	5	10′	50-5-25	5	25′						
80-6-5	6	5′				50-6-25	6	25′						



X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Solder Removal category:

Click to view products by Chemtronics manufacturer:

Other Similar products are found below:

532505-2 DS03-910-5 DP-CC STDC-102 T0054463299N T0054465499N T0058741815N T0052921799N T0054465299N T0054463199N T0051320399N 0ICV2000AC T0054466699N T0051317799N CLMU-A CLMU-PA T0053500699 T0053503699 0320705 0320800 0320903 0321200 0321300 0321400 0321500 0ICV2000AI 3280 51314400 51512599 C560-002 C560-003 C560-004 C560-005 WE51314000 DP-100 51315000 51315100 0IC2000AXT 0AS196 0LS197 0VACX 10-5L 80-5-10 S6169 SA21A MX-DCF1F 0119107 SP-108K CL6210 STDC-705L