


Datasheet revision 1.3 <u>www.chipquik.com</u>

# Conductive Paint 30g Jar - Low Resistance





#### Product Highlights

Low Resistance
Dries at room temperature
RoHS 3 and REACH compliant

### Specifications

Resistance: 1.0 Ohms/Square at 0.004" stencil thickness

Viscosity: 100 mPa·s
Packaging: 30g Jar
Shelf Life: >12 months

Drying Time: Allow 60-120 minutes for paint to dry before using circuit. Resistance will drop from a few

Mega Ohms at 0 minutes to approximately 3 ohms per inch of trace after 120 minutes. If encapsulating or conformal coating on top of conductive paint, allow 7 days (168 hours) for

full drying before covering is applied.

Operating Temperature: -40°C to 120°C (-40°F to 248°F)

# Application

Apply by dot dispensing, line dispensing, stencil and squeegee, or with paint brush.

#### Cleaning

Clean using water or isopropyl alcohol (IPA).

#### Storage and Handling

Store at 3-25°C (37-77°F). Do not freeze.

# Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Chemicals category:

Click to view products by Chip Quik manufacturer:

Other Similar products are found below:

DP-605NS 3045-QT 3125-9S 3748-Q-58"x8" FO-25DT S1009-KIT-A-CS8606 DP100-200ML 1743-2FP 152-KA-NC 826-450G 9729

9223 9945 7000000275 1601 8330-19G 842AR-15ML 841AR-150ML 842AR-P 843WB-15ML 8462-85ML 4354-1L 838AR-P 838AR
15ML 419D-P-BK 419D-P-WH 8MT-450 8MT-25 832HD-25ML 832FX-450ML 834ATH-375ML 832HD-400ML 8617-1P 843AR-340G

843ER-800ML 9310-300ML 847-1P 419D-55ML 8800-375ML 8810-375ML 8820-2.55L 419E-340G 842UR-12ML 419D-1L

CW3300WHITE CW2205 10447 9620-945ML 4140A-945ML FW2170