# **CHIPQUIK®**

## SMD4300AX250T5

Datasheet revision 1.4 www.chipquik.com

### Solder Paste Water-Washable Sn63/Pb37 in Jar 250g T5 Mesh

**Product Highlights** 

Printing speeds up to 100mm/sec

Long stencil life

Wide process window

Clear residue

Low voiding

Excellent wetting compatibility on most board finishes

Print grade

Compatible with enclosed print heads

**Specifications** 

Alloy: Sn63/Pb37

Mesh Size: T5
Micron (µm) Range: 15-25

Flux Type: Synthetic Water-Washable

Flux Classification: REL0

Metal Load: 89.5% Metal by Weight

Melting Point: 183°C (361°F)
Packaging: Jar 250g

Shelf Life: Refrigerated >12 months, Unrefrigerated >6 months \*See notes below:

\*Shelf Life Notes: Chip Quik® solder paste is good past its quoted shelf life, regardless of refrigeration. Before use, visually inspect the solder paste to ensure it is not dried out or clumpy, or check stencil release. If stored in a jar, stir the product thoroughly for 2-3 minutes before inspection and use.

Chip Quik® solder paste is manufactured using Made in USA high quality synthetic flux and precision atomized metal powder. Chip Quik® solder paste is guaranteed for 12 months from date of manufacture, regardless of refrigeration. If you have any issues with our solder paste, please contact Chip Quik® directly for no charge warranty replacement. Please retain original bill of sale, and solder paste in original container as we may request its return for internal R&D testing purposes.

#### **Printer Operation**

Print Speed: 25-100mm/sec

Squeegee Pressure: 70-250g/cm of blade

Under Stencil Wipe: Once every 10-25 prints, or as necessary

#### Stencil Life

>8 hours @ 20-50% RH 22-28°C (72-82°F) >4 hours @ 50-70% RH 22-28°C (72-82°F)

#### **Stencil Cleaning**

Automated stencil cleaning systems for both stencil and misprinted boards. Manual cleaning using isopropyl alcohol (IPA).

#### Storage and Handling


Refrigerate at 3-8°C (37-46°F). Do not freeze. Allow 4 hours for solder paste to reach an operating temperature of 20-25°C (68-77°F) before use.

#### **Transportation**

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.

#### **Recommended Profile**

Reflow profile for Sn63/Pb37 solder assembly, designed as a starting point for process optimization.



#### **Test Results**

Test J-STD-004 or other requirements as stated	Test Requirement	Result
Copper Mirror	IPC-TM-650: 2.3.32	L: No breakthrough
Corrosion	IPC-TM-650: 2.6.15	L: No corrosion
Quantitative Halides	IPC-TM-650: 2.3.28.1	L: <0.5%
Electrochemical Migration	IPC-TM-650: 2.6.14.1	L: <1 decade drop (No-clean)
Surface Insulation Resistance 85°C, 85% RH @ 168 Hours	IPC-TM-650: 2.6.3.7	L: ≥100MΩ (No-clean)
Tack Value	IPC-TM-650: 2.4.44	37g
Viscosity – Malcom @ 10 RPM/25°C (x10³mPa/s)	IPC-TM-650: 2.4.34.4	Print: 200-275, Dispense: 100-140
Visual	IPC-TM-650: 3.4.2.5	Clear and free from precipitation
Conflict Minerals Compliance	Electronic Industry Citizenship Coalition (EICC)	Compliant
REACH Compliance	Articles 33 and 67 of Regulation (EC) No 1907/2006	Contains Lead (Pb) CAS# 7439-92-1 No other SVHC present

#### **Conforms to the following Industry Standards:**

J-STD-004B, Amendment 1 (Solder Fluxes):	Yes
J-STD-005A (Solder Pastes):	Yes
J-STD-006C, Amendments 1 & 2 (Solder Alloys and Fluxed/Non-Fluxed Solders):	Yes
RoHS 2 Directive 2011/65/EU:	No

## **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Solder category:

Click to view products by Chip Quik manufacturer:

Other Similar products are found below:

600YSY 701-2758 707-1746 707-1748 707-1811 707-1813 707-1831 707-1840 707-1850 707-1852 13-217-3-01 P10695 SN63WRAP3.022-1-LB 24-6040-0007 DAC-061 701-2089 707-0285 707-0366 707-0441-26 707-1774 707-1810 24-6337-9727 601Y 24-9574-7619
24-4060-2437 14-6040-0125 04-0595-0000 5901003 631960 SW02-10 S2626-O-T 8055 5760140 TRWR-204 1152 EC2002M-1 WPT17
WS6016 760-2028 8001115 8001073 8001495 41-096-0203N ART.AGT-030 389289 54068 ECO 1 (SNCU1) FLUX B2.1 0,8 MM 250G
ECO3 (SNCU3) FLUX B2.1 0,8 MM 250 G. ECO3 (SNCU3) FLUX B2.1 0,8 MM 1000 G. ECO4 (SNAG3CU0.5) FLUX B2.1 0,8 MM 1000G