

Datasheet revision 1.1

www.chipquik.com

Thermally Stable Solder Paste No-Clean Sn63/Pb37 T4 (15g Syringe)

Product Highlights

. ...

Revolutionary Formula: No Refrigeration Required!

Printing speeds up to 125mm/sec Long stencil life Wide process window Clear residue Low voiding Excellent wetting compatibility on most board finishes Dispense grade Compatible with enclosed print heads REACH Compliant

Specifications		
Alloy:	Sn63/Pb37	
Mesh Size:	Τ4	
Micron (µm) Range:	20-38	
Flux Type:	Synthetic No-Clean	
Flux Classification:	ROL0	
Metal Load:	88% Metal by Weight	
Melting Point:	183°C (361°F)	
Packaging:	5cc/15g Syringe	
Shelf Life:	Refrigerated >12 months, Unrefrigerated >12 months	*See notes below:

<u>*Shelf Life Notes:</u> Chip Quik® solder paste is good past its quoted shelf life, regardless of refrigeration. Before use, visually inspect the solder paste to ensure it is not dried out or clumpy, or check stencil release. If stored in a jar, stir the product thoroughly for 2-3 minutes before inspection and use.

Chip Quik® solder paste is manufactured using Made in USA high quality synthetic flux and precision atomized metal powder. Chip Quik® solder paste is guaranteed for 12 months from date of manufacture, regardless of refrigeration. If you have any issues with our solder paste, please contact Chip Quik® directly for no charge warranty replacement. Please retain original bill of sale, and solder paste in original container as we may request its return for internal R&D testing purposes.

Printer Operation

Print Speed: 25-125mm/sec Squeegee Pressure: 70-250g/cm of blade Under Stencil Wipe: Once every 10-25 prints, or as necessary

Stencil Life

>12 hours @ 20-50% RH 22-28°C (72-82°F) >4 hours @ 50-70% RH 22-28°C (72-82°F)

Stencil Cleaning


Automated stencil cleaning systems for both stencil and misprinted boards. Manual cleaning using isopropyl alcohol (IPA).

Storage and Handling

Store at room temperature 20-25°C (68-77°F). Do not freeze. Chip Quik Thermally Stable solder paste should be stored at its operating temperature (room temperature) of 20-25°C (68-77°F), therefore no warming time is required before use.

Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.



Test Results

Test J-STD-004 or other requirements as stated	Test Requirement	Result
Copper Mirror	IPC-TM-650: 2.3.32	L: No breakthrough
Corrosion	IPC-TM-650: 2.6.15	L: No corrosion
Quantitative Halides	IPC-TM-650: 2.3.28.1	L: <0.5%
Electrochemical Migration	IPC-TM-650: 2.6.14.1	L: <1 decade drop (No-clean)
Surface Insulation Resistance 85°C, 85% RH @ 168 Hours	IPC-TM-650: 2.6.3.7	L: ≥100MΩ (No-clean)
Tack Value	IPC-TM-650: 2.4.44	33g
Viscosity – Malcom @ 10 RPM/25°C (x10³mPa/s)	IPC-TM-650: 2.4.34.4	Print: 140-195, Dispense: 115-160
Visual	IPC-TM-650: 3.4.2.5	Clear and free from precipitation
Conflict Minerals Compliance	Electronic Industry Citizenship Coalition (EICC)	Compliant
REACH Compliance	Articles 33 and 67 of Regulation (EC) No 1907/2006	Contains Lead (Pb) CAS# 7439-92-1 No other SVHC present

Conforms to the following Industry Standards:	
J-STD-004B, Amendment 1 (Solder Fluxes):	Yes
J-STD-005A (Solder Pastes):	Yes
J-STD-006C, Amendments 1 & 2 (Solder Alloys and Fluxed/Non-Fluxed Solders):	
RoHS 2 Directive 2011/65/EU:	No

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Solder category:

Click to view products by Chip Quik manufacturer:

Other Similar products are found below :

 600YSY
 701-2758
 707-1746
 707-1811
 707-1813
 707-1831
 707-1850
 707-1852
 13-217-3-01
 P10695
 SN63WRAP3

 .022-1-LB
 24-6040-0007
 DAC-061
 701-2089
 707-0285
 707-0366
 707-0441-26
 707-1774
 707-1810
 24-6337-9727
 601Y
 24-9574-7619

 24-4060-2437
 14-6040-0125
 04-0595-0000
 5901003
 631960
 SW02-10
 S2626-O-T
 8055
 5760140
 TRWR-204
 1152
 EC2002M-1
 WPT17

 WS6016
 760-2028
 8001115
 8001073
 8001495
 41-096-0202N
 41-096-0203N
 ART.AGT-030
 389289
 54068
 ECO 1 (SNCU1) FLUX B2.1

 0,8 MM 250G
 ECO3 (SNCU3) FLUX B2.1
 0,8 MM 250 G.
 ECO3 (SNCU3) FLUX B2.1
 0,8 MM 1000 G.