

Datasheet revision 1.0 www.chipquik.com

Thermally Stable Solder Paste WS (Water-Soluble) Sn63/Pb37 T4 (35g syringe)

Low voiding

Dispense grade

Compatible with most board finishes

Compatible with enclosed print heads

Product Highlights

Revolutionary Formula: No Refrigeration Required!

Printing speeds up to 100mm/sec

Long stencil life

Wide process window

Excellent Wetting with Moderate Activity (REM0) Flux Water-Soluble Easily cleaned with water (60°C+)

Specifications

Alloy: Sn63/Pb37


Mesh Size: T4
Micron (µm) Range: 20-38

Flux Type: Synthetic Water-Soluble

Flux Classification: REM0 (Residue must be water-washed at 60°C+ after reflow)

Metal Load: 87% Metal by Weight Melting Point: 183°C (361°F)
Packaging: 35g/10cc Syringe

Shelf Life: Refrigerated >6 months, Unrefrigerated >6 months *See notes below:



Chip Quik® solder paste is manufactured using Made in USA high quality synthetic flux and precision atomized metal powder. Chip Quik® solder paste is guaranteed for 12 months from date of manufacture, regardless of refrigeration. If you have any issues with our solder paste, please contact Chip Quik® directly for no charge warranty replacement. Please retain original bill of sale, and solder paste in original container as we may request its return for internal R&D testing purposes.

Printer Operation

Print Speed: 25-100mm/sec

Squeegee Pressure: 70-250g/cm of blade

Under Stencil Wipe: Once every 10-25 prints, or as necessary

Stencil Life

>8 hours @ 20-50% RH 22-28°C (72-82°F) >4 hours @ 50-70% RH 22-28°C (72-82°F)

Stencil Cleaning

Automated stencil cleaning systems for both stencil and misprinted boards. Manual cleaning using isopropyl alcohol (IPA).

Storage and Handling


Store at 3-25°C (37-77°F). Do not freeze. Refrigeration is not required, but will extend shelf life. Allow 4 hours for solder paste to reach an operating temperature of 20-25°C (68-77°F) before use.

Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.



Reflow profile for Sn63/Pb37 solder assembly, designed as a starting point for process optimization.



Test Results

100111004110		
Test J-STD-004 or other requirements as stated	Test Requirement	Result
Copper Mirror	IPC-TM-650: 2.3.32	L: No breakthrough
Corrosion	IPC-TM-650: 2.6.15	L: No corrosion
Quantitative Halides	IPC-TM-650: 2.3.28.1	L: <0.05%
Electrochemical Migration	IPC-TM-650: 2.6.14.1	L: <1 decade drop
Surface Insulation Resistance 85°C, 85% RH @ 168 Hours	IPC-TM-650: 2.6.3.7	L: ≥100MΩ
Tack Value	IPC-TM-650: 2.4.44	37g
Viscosity – Malcom @ 10 RPM/25°C (x10³mPa/s)	IPC-TM-650: 2.4.34.4	Print: 200-275, Dispense: 100-140
Visual	IPC-TM-650: 3.4.2.5	Clear and free from precipitation
Conflict Minerals Compliance	Electronic Industry Citizenship Coalition (EICC)	Compliant
REACH Compliance	Articles 33 and 67 of Regulation (EC) No 1907/2006	Contains Lead (Pb) CAS# 7439-92-1 No other SVHC present

Conforms to the following Industry Standards: LSTD 004B, Amendment 1 (Solder Fluxes):

J-STD-004B, Amendment 1 (Solder Fluxes):	Yes
J-STD-005A (Solder Pastes):	Yes
J-STD-006C, Amendments 1 & 2 (Solder Alloys and Fluxed/Non-Fluxed Solders):	Yes
RoHS 3 Directive (EU) 2015/863:	No
RoHS 3 Directive (EU) 2015/863:	No

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Solder category:

Click to view products by Chip Quik manufacturer:

Other Similar products are found below:

701-2758 707-1811 91362-6 13-217-3-01 P10695 SN63WRAP3-.022-1-LB 599Z 707-0441-26 707-1810 601Y 24-9574-7619 24-4060-2437 T0051387299 5760140 1152 EC2002M-1 760-2028 389289 570027 811035 811036 811018 ALPHA VACULOY SNCX PLUS 07 1 KG 15704 15808 0008752 0401-08-000460 04-6040-0050 H560103-BULK H560106-BULK H562159-BULK 5601365 BON-102F BON-102K BON-102S BR-102F 560006BA 560048 560069W-LF 5601034 5601053 5601056 5601058 5601129 5601157 5601161 5601166 5601167 5601170 8001092