

Product Code: AN10 AN20 AN60 AN210 AN220 AN260

PRODUCT DESCRIPTION

Polyimide film with copper foil on one or both sides, bonded together with a proprietary C-staged modified acrylic adhesive.

Copper-Clad Product

Copper oz/ft ² (g/m ²) 1 (305)	Adhesive Mil (µm) 1 (25)	Kapton Mil (µm) 1 (25)	IPC Cert.1 Yes
--	---------------------------------------	-------------------------------------	-----------------------------

Copper-Clad Laminate Properties vs IPC Specifications

Property	IPC Spec	Typical Clad Value
Peel Strength, min., lb/in (kg/cm)		
As received	8 (1.4)	10 (1.8)
After solder	7 (1.3)	9 (1.6)
Dimensional Stability, max., percent	0.15	0.10
Dielectric Constant, max. (at 1 MHz)	4.0	3.6
Dissipation Factor, max. (at 1 MHz)	0.03	0.02
Volume Resistivity, min., megohm-cm (ambient)	10 ⁷	10 ⁹
Surface Resistivity, min., megohm-cm (ambient)	10 ⁶	10 ⁸

Copyright CIF 2003

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. CIF - cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.



The Professional Tools

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [cif manufacturer](#):

Other Similar products are found below :

[AJB58](#) [V900130](#) [AL441](#) [DU68.10](#) [AAC20](#) [AD20](#) [V900131](#) [V900132](#) [AN10](#) [DU64.10](#) [V900121](#) [ABC16](#) [AAC16](#) [DU80](#) [DU67](#) [AEB16](#)
[AB15](#) [AR224](#) [DW101010](#) [AEB20](#) [AGP20](#) [AJP20](#) [AA20](#) [DU77](#) [AJP58](#) [DU71](#) [AGP30](#) [AA15](#) [ABB16](#) [DU66](#) [AGB30](#) [DU65.10](#) [ADB16](#)
[AR234](#) [AL435](#) [DU69](#) [AAT10](#) [DU85](#) [ADB20](#) [AE20](#) [AAB16](#) [AR45](#) [AB16](#) [AD16](#) [AJB22](#) [AJP22](#) [AGB10](#) [AR412](#) [AR21](#) [AJP16](#)