

DOC NO.: DEC-SA-WI003

REV.: B/4

DATE: 2021/08/13

瓷片電容器規格承認書 APPROVAL SPECIFICATION FOR DISC CERAMIC CAPACITORS

客戶 CUSTOMER		立創	
客戶料號 CUSTOMER P/N			
客戶規格描述 CUST. SPEC			
規格描述 DESCRIPTION	500V/682/M/F	5.08/直脚/L18/酚醛(黄)/Y5V/8C/ZNR
產品編碼 PART NUMBER	C	CC2H682MC1FDF48C31	00
日期 DATE	2023年12月9日	文件編號 DOC. NO.	DEC-SA-WI003

批準 APPROVED BY おことを表する おいています。 まいています。 まいています。 まいています。 まいています。 まれています。 まれています。 まれています。 まれています。 まれていまする。まれています。 まれていまする。まれていまする。まれています。 まれていまする。まれています。 まれていまする。まれていまする		德爾創承認欄 APPROVED BY DERSONIC		承認欄 Y CUSTOMER
		CHECKBY		
	彭少雄		胡明康	

東莞市德爾創電子有限公司 DONGGUAN DERSONIC ELECTRONIC CO., LTD.

ZNRC®

廣東省東莞市寮步鎮松湖智谷產業園F2棟15樓

15/F, Blk F2, Songshan Lake Intelligent Valley Industrial Park, Liaobu Town, Dongguan City, PRC

TEL: +86-769-8155 5686 FAX: +86-769-8155 5989

E-mail: sales@dersonic.com / quality@dersonic.com

Website: http://www.dersonic.com



編號DOC NO.:	DEC-SA-WI003
版本REV.:	B/4
日期DATE:	2023年12月9日
百碼PAGF.	1 / 10

目 錄 CONTENTS

1. 規格表 DATA SHEET	2
2. 總則 GENERAL	3
3. 適用標準 APPLICABLE STANDARD	3
4. 產品結構 STRUCTURE	3
5. 產品編碼 PART NUMBER	4
6. 測量和試驗 MEASUREMENT AND TEST	5
7. 包裝和儲存 PACKAGING AND STORAGE	7
8. 測量和使用注意事項 MEASURING AND APPLICATION NOTICE	8
9. 編帶尺寸規格 TAPING SPECIFICATIONS	10




請確保我們的產品安裝到您的產品上前,已根據您的需求進行了評估。 Please make sure that your product has been evaluated in view of your specifications with our product being mounted to your product. 請您在使用我們的產品時,不要偏離此標準。

You are requested not to use our product deviating from this specification.



編號DOC NO.:	DEC-SA-WI003
版本REV.:	B/4
日期DATE:	2023年12月9日
直碼PAGF:	2 / 10

規格表 DATA SHEET



產品編碼 Part number	CC2H682MC1FDF48C3100	
規格描述 Description	500V/682/M/F5.08/直脚/L18/酚醛(黄)/Y5V/8C/ZNR	
客戶料號 Customer P/N		
介質類別 Dielectric class	Class 2	
額定電壓 Rated voltage	500VDC	
電容量 Capacitance	6800 pF ±20% @ 1kHz 1V 25°C	
損耗角正切 Tangent of loss angle	0.025 max @ 1kHz 1V 25°C	
耐電壓 Testing voltage	1.3 KV (Charge/discharge 50mA max), 3s, PASS	
絕緣電阻 Insulation resistance	6GΩ min @ 500V 60s, ≤RH70%	
温度特性	Y5V	
Temperature characteristics	ΔC/C: +22/-82% @ -30°C~85°C	
D (Diameter)	$8.5 \text{ mm} \pm 0.7 \text{mm}$	
T (Thickness)	2.6 mm±0.7mm	
F (Lead spacing)	5.08 mm±0.8mm	
L (Lead length)	18.0 mm±5.0mm	
ød (Lead diameter)	0.5 mm±0.10mm	
C (Coating rundown on lead) 1.5 mm max		
標誌 Marking	ZNR 682 500V	
	Part number 規格描述 Description 客戶料號 Customer P/N 介質類別 Dielectric class 額定電壓 Rated voltage 電容量 Capacitance 損耗角正切 Tangent of loss angle 耐電壓 Testing voltage 絕緣電阻 Insulation resistance 温度特性 Temperature characteristics D (Diameter) T (Thickness) F (Lead spacing) L (Lead length) ød (Lead diameter) C (Coating rundown on lead)	



編號DOC NO.:	DEC-SA-WI003
版本REV.:	B/4
日期DATE:	2023年12月9日
頁碼PAGE:	3 / 10

2. 總則

GENERAL

1) 本規格書適用於額定電壓不超過直流&kV或最大標稱電容量爲0.22uF的電子設備用瓷片電容器。

This specification applies to the disc ceramic capacitors for electronic equipment with a rated voltage not exceeding DC 8kV or 0.22uF of maximum nominal capacitance.

2) 溫度補償型(1類瓷)電容器是專門設計並用在低損耗、電容量穩定性高或要求溫度系數有明確規定的諧振電路中的一種電容器,例如,在電路中作溫度補償之用。

Temperature compensation (Class 1) ceramic capacitor specially designed and suited for resonant circuit application where low losses and high stability of capacitance are essential or where a precisely defined temperature coefficient is required, for example for compensating temperature effects in the circuit.

該類陶瓷介質是由標稱溫度系數(alpha)來確定,如NPO、N750、SL等等。

The ceramic dielectric is defined by its rated temperature coefficient (alpha), such as NPO, N750, SL, etc. •

3) 高介電常數型(2類瓷)電容器是是適用於作旁路、耦合或用在對損耗和電容量穩定性要求不高的電路中的具有高介電常數的一種電容器。

High dielectric (Class 2) ceramic capacitor which has a dielectric with a high permittivity and is suitable for by-pass and coupling applications or for frequency discriminating circuits where low losses and high stability of capacitance are not of major importance.

該類陶瓷介質是以在類別溫度範圍内電容量非線性變化來表征,如Y5P、Y5U、Y5V等等。

The ceramic dielectric is characterized by the non-linear change of capacitance over the category temperature range, such as Y5P, Y5U and Y5V etc.

4) 可適用於自動化生產線

Cost-saving automatic insertion available

5) 符合RoHS 2.0、REACH標準,無鹵。 Comply with RoHS 2.0 & REACH, halogen-free available

3. 適用標準

APPLICABLE STANDARD

本產品符合下列標準,且本規格書的相關內容引用以下標準,當雙方對此存在爭議時,可依以下標準進行仲裁。
This product complies with the following standards, and the relevant content of this specification refers to the following standards, when the two sides in dispute, the following criteria for arbitration.

GB/T 2693-2001 電子設備用固定電容器 第1部分 總規範(IDT IEC 60384-1)

Fixed capacitors for use in electronic equipmen — Part 1: Generic specification (IDT IEC 60384-1)

GB/T 5966-2011 電子設備用固定電容器 第8部分 分規範 1類瓷介固定電容器(IDT IEC 60384-8)

Fixed capacitors for use in electronic equipmen — Part 8: Sectional specification: Fixed capacitors of ceramic dielectric,

Class 1 (IDT IEC 60384-8)

GB/T 5968-2011 電子設備用固定電容器 第9部分 分規範 2類瓷介固定電容器(IDT IEC 60384-9)

Fixed capacitors for use in electronic equipmen — Part 9: Sectional specification: Fixed capacitors of ceramic dielectric,


Class 2 (IDT IEC 60384-9)

4. 結構

STRUCTURE

本產品結構如下圖所示,外部包封層爲環氧樹脂(藍色)或酚醛樹脂(土黃色),內部介質爲陶瓷,銀電極,導線爲鍍錫銅包鋼線,電極與導線采用無鉛錫焊接而成,經過激光打標而成。

The structure of this product is shown in the following figure, external coating layer to epoxy resin (blue) or phenolic resin (yellowish), internal dielectric for ceramics, silver electrodes, lead wires for tin-plated copper clad steel wire, electrodes and lead wires using lead-free tin soldering, through laser marking.





編號DOC NO.:	DEC-SA-WI003
版本REV.:	B/4
日期DATE:	2023年12月9日
頁碼PAGE:	4 / 10

5. 產品編碼

PART NUMBER

本公司產品編碼方式,舉例說明如下:

The product part number representation of the company, examples are as follows:

<u>CC</u>	<u>2H</u>	<u>682</u>	<u>M</u>	<u>C1</u>	<u>F</u>	<u>D</u>	<u>F4</u>	<u>8C3</u>	<u>100</u>
系列	額定直流	標稱容量	容量偏差	引線	編帶包裝	包封	温度特性	内部識別碼	標誌
Series	電壓	Nominal capacitance	Cap.	成型方式	或腳長	Coating	Temperature	Inter identification	Marking
	Rated dc		tolerance	Lead format	Taping		characteristics	code	
	voltage				packing or				
					Lead length				

CC: 瓷片電容器 ■ 系列 Series Disc ceramic capacitors

2E: 250V 3A: 1kV 3G: 4kV ■ 額定直流電壓 1C: 16V 1H: 50V Rated dc voltage 1E: 25V 1J: 63V 2H: 500V 3D: 2kV 3H: 5kV 1V: 35V 2A: 100V 2J: 630V 3F: 3kV(3.15kV) 3J: 6.3kV 2D: 200V 3K: 8kV

用3位數表示,單位pF。如下所示: ■ 標稱容量 In 3 digits, unit is pF, as shown in below: Nominal capacitance

682:6800 pF (1 uF = 1 000 nF = 1 000 000 pF)

■ 容量偏差 C: ±0.25pF $J: \pm 5\%$ S: +50%/-20% D: ±0.50pF K: ±10% Z: +80%/-20% Capacitance tolerance M: ±20% P: +100%/-0%

■ 引線成型方式 Lead format

代碼 Code	腳距 Lead spacing
Α	2.54mm
С	5.08mm
D	7.50mm
Е	10.0mm

代碼 Code	1	2	4	5	7
腳型 樣式 Lead style drawing	直腳	外彎腳	内彎腳	平行腳	小單外彎腳 Mini outside kink
	Straight Lead	Outside kink Lead	Inside kink Lead	Vertical kink Lead	Lead

■ 編帶包裝或腳長 Taping packing or

Bulk (Lead length) 4: 3.5mm 9: 6.0mm 5: 3.8mm V: 7.0mm 6: 4.0mm A: 8.0mm B: 10mm

F: 18mm G: 20mm I: 24mm

Taping T: Reel packing 卷盤包裝



■ 包封 Coating

Lead length

D: 酚醛(黃)

7: 4.5mm

8: 5.0mm

Class 3:

E: 環氧(藍) Epoxy (Blue)

3F: Y5V

Phenolic (Yellow)

DL: N3300 ■ 温度特性 Class 1: CH: NP0 UJ: N750 SL: SL R1: X7R Temperature characteristics Class 2: B4: Y5P E4: Y5U F4: Y5V

3E: Y5U

E: 16mm

■ 内部識別碼 Inter identification 内部控制碼,本規格書不作說明。

Inter control code will not be described in this an approval specifications.

code

■ 標誌

見規格表最後一欄

See the last column of the "DATA SHEET" Marking



編號DOC NO.:	DEC-SA-WI003
版本REV.:	B/4
日期DATE:	2023年12月9日
頁碼PAGE:	5 / 10

6. 測量和試驗

No.	項目 Item	標準 Specifications	試驗方法 Testing Method	
1	工作溫度範圍 Operating temp. range	-30°C~85°C		
2	額定電壓 Rated voltage (U _R)	500VDC	額定電壓是指在工作溫度範圍內,可連續施加在電容器上的最大直流電壓或最大交流電壓有效值或脈沖電壓的峰值當交流電壓附加於直流電壓時,Vp-p或Vo-p(以較大者爲準)應維持在額定電壓範圍內。 The rated voltage is defined as the maximum voltage which may be applied continuously to the capacitor within the operating temperature range. When AC voltage is superimposed on DC voltage, Vp-p or Vo-p, whichever is larger, should be maintained within the rated voltage range.	
3	外觀與尺寸 Appearance (APP) and Dimension	外觀形狀沒有明顯的缺點,尺寸在標準範圍内。 No marked defect on appearance form and dimensions are within specified range.	電容必須用目視檢查其明顯的缺點。 The capacitor should be visually inspected for evidence of defect. 尺寸用遊標卡尺測量。 Dimensions should be measured with slide calipers.	
4	標誌 Marking	清晰易於識別。 To be easily legible.	目視檢查。 The capacitor should be visually inspected.	
5	容量 (C _R) Capacitance (C _R)	5.44NF-8.16NF	容量與tanδ在25±1℃下,使用1kHz和1Vrms下測量。	
6	坦托名式切		The capacitance, tan δ should be measured at 25°C \pm 1°C with 1kHz and 1.0V (r.m.s.).	
7	絕緣電阻 Insulation Resistance (IR)	6GΩ min	在兩導線間施加下列電壓進行測量,時間不超過1分鐘。 The insulation resistance should be measured with a test voltages of below at normal temperature and humidity and less than 1 min. of charging. 500V @ RH < 70%	
8	耐電壓 Testing Voltage (TV)	沒有不合格 No failure.	在電容器兩導線間施加下列測試電壓(充/放電流不大於 2mA)1到5s後不被破壞。 The capacitor should not be damaged when test voltages (Charge/Discharge current 2mA) of below are applied between the lead wires for 1 to 5 sec.	
9	導線抗張強度 Terminal Tensile Strength 写l線不應斷開,電容器不應破裂。 Lead wire should not be cut off capacitor should not be broken.		1250VDC 固定住電容器,在引線上逐步施加徑嚮拉力直至10N,並保持 10 ± 1 秒鐘。 Fix the body of the capacitor and apply a tensile weight gradually to each lead wire in the radial direction of the capacitor up to 10N and keep it for 10 ± 1 sec	
10	導線抗折強度 Terminal Bending Strengt	引線不應斷開,電容器不應破裂。 Lead wire should not be cut off capacitor should not be broken.	在引線出口處沿一個方嚮施加5N、90°的彎曲壓力,再恢復至初始狀態。之後,在2至3秒內再以相反方嚮施加一次90°的彎曲壓力。 Each lead wire should be subjected to 5N of weight and bent 90° at the point of egress, in one direction, then returned to its original position and bent 90° in the opposite direction at the rate of one bent in 2 to 3 sec.	
11	可焊性 Solderability of Lead	導線必須有3/4以上的面積均勻附着焊錫 Lead wire should be soldered with uniform coating on the axial direction over 3/4 of the circumferential direction.	引線必須浸入焊料中3±0.5秒鐘,浸入深度離導線根部1.5-2.0mm。 The lead wire of a capacitor should be dipped into molten solder for 3±0.5 sec The depth of immersion is up to about 1.5 to 2.0mm from the root of lead wires 焊錫溫度:無鉛焊(Sn-3Ag-0.5Cu) 245±5°C Temp. of solder: Lead Free Solder (Sn-3Ag-0.5Cu) 245±5°C	



編號DOC NO.:	DEC-SA-WI003
版本REV.:	B/4
日期DATE:	2023年12月9日
頁碼PAGE:	6 / 10

續上表

No. 項目 Item		Item Specifications		試驗方法 Testing Method		
	APP		沒有可見損傷 No marked defect	將導線浸入離導線根部1.5-2.0mm處、錫溫爲260±10℃中3.5±		
	焊錫耐熱性 — Soldering Effect	ΔC/C	±20%	0.5秒。 The lead wires should be immersed in solder of 260±5°C up to 1.5 to 2.0mm		
12		IR	大於初始標準的50% More than 50% initial specified value.	from the root of terminal for 3.5±0.5 sec. 試驗後處理:電容必須存放在室溫下24小時。 ———Post-treatment: Capacitor should be stored for 24h at room condition.		
		TV	如第8項進行試驗,沒有不合格 Per Item 8.	1 OSC-GERGINENT: CAPACITO STICUIO DE STOTEO DO 2411 ACTOURI CONTIGUIO.		
		APP	沒有可見損傷 No marked defect	將電容器導線焊穩和調整振動頻率範圍爲10-55Hz、總振幅爲 ————1.5mm,振動從10Hz到55Hz,然後再回到10Hz,大約一分鐘。		
13	振動 Vibration Resistance	C_R	如第5項進行試驗,沒有不合格 Per Item 5.	The capacitor should be firmly soldered to the supporting lead wire and vibrat at a frequency range of 10 to 55Hz, 1.5mm in total amplitude, with about a 1 minute rate of vibration change from 10Hz to 55Hz and back to 10Hz.		
		tan δ	如第6項進行試驗,沒有不合格 Per Item 6.	總時間六個小時,每兩小時在相互垂直方嚮來回三次。 Apply for a total of 6 hours, 2 hours each in 3 mutually perpendicular direction		
14	温度特性 Temperature characteristics		ΔC/C: +22/-82%	電容器必須按照下列每一步驟進行測量。 The capacitance measurement should be made at each step specified in below Stwp Temperature (±1°C) 1 +20 2 Lower category temperature 3 +20 4 Upper category temperature 5 +20		
	APP		沒有可見損傷 No marked defect	施加下列電壓的電容保持在溫度爲40±2℃、相對濕度爲90- 95%條件下500±12小時。		
		∆ C/C	±30%	Apply a test voltage of below for 500 ± 12 hours at $40\pm2^{\circ}\mathrm{C}$ in 90 to 95% relative humidity.		
15	耐濕負荷 Humidity Loading -	tan δ	小於初始標準的2倍 Less than 200% initial specified value.	1000V		
		IR	大於初始標準的25% More than 25% initial specified value.	試驗後處理:電容必須貯存在室溫條件下24小時。 Post-treatment: Capacitor should be stored for 24 h. at room condition.		
		TV	如第8項進行試驗,沒有不合格 Per Item 8.			
	高溫負荷 High Temperature Load	APP	沒有可見損傷 No marked defect	在上限類別溫度相對溫度不大於50%條件下施加下列電壓 1000+48/-0小時(充/放電流小於5mA)		
		∆ C/C	±30%	Apply a test voltages of below for 1000+48/-0 hours at Upper category temperature with a relative humidity of 50% max. (Charge/discharge current ≤5mA)		
16		tan δ	小於初始標準的2倍 Less than 200% of initial specified value.	1.5KV		
		IR	大於初始標準的50% More than 50% initial specified value.	試驗後處理: 電容器應在室溫下儲存24小時。 Post-treatment: Capacitor shall be stored for 24 h at room condition.		
		TV	如第8項進行試驗,沒有不合格 Per Item 8.			



編號DOC NO.:	DEC-SA-WI003
版本REV.:	B/4
日期DATE:	2023年12月9日
頁碼PAGE:	7 / 10

續上表

Continued on the table

No.	項目 Item		標準 Specifications	試驗方法 Testing Method
		APP	沒有可見損傷 No marked defect	溫度循環試驗按以下條件進行試驗和測量
		∆ C/C	±20%	Temperature cycling shall be measured in the following test. 下限類別溫度:30分鐘
17	溫度循環 Temperature and Immersion Cycle	tan δ	小於初始標準的2倍 Less than 200% of initial specified value.	Lower category temperature: 30min 上限類別溫度: 30分鐘 Upper category temperature: 30min
		IR	大於初始標準的50% More than 50% initial specified value.	循環次數: 5次 Cycle numbers: 5 cycles 試驗後處理: 電容器應在室溫下儲存24小時。
		TV	如第8項進行試驗,沒有不合格 Per Item 8.	Post-treatment: Capacitor shall be stored for 24 h at room condition.

7. 包装和**儲存**

PACKAGING AND STORAGE

7.1. 包裝

PACKAGING

盒裝編帶品,每盒2000pcs(每箱20000pcs)。

Taping of ammo packing, 2000 pcs/box (20 000 pcs/carton)

散包包裝,每包1000pcs(視瓷片大小不等,每箱20000~10000pcs)。

Bulk packing, 1000 pcs/bag (Depending on the disc size, each carton is 20 000 $\sim\!100$ 000 pcs)

7.2. 貯存條件

STORAGE ENVIRONMENT

電容器絕緣包封層不是完美的密封形式,因此,請勿將電容器存放在腐蝕性氣體中,尤其是存在氯氣、硫氣、酸、堿、鹽等場所,同時應防潮。

The insulating coating of capacitors does not form a perfect seal; therefore, do not use or store capacitors in a corrosive atmosphere, especially where chloride gas, sulfide gas, acid, alkali, salt or the like are present. And avoid exposure to moisture.

電容器應存放在溫度及相對濕度分別不超出5~40℃及15~70%範圍的場所。

Store the capacitors where the temperature and relative humidity do not exceed 5 to 40 degrees centigrade and 15 to 70%.

請在6個月內使用電容器。超過6個月,在使用前確認其可焊性和電容量。

Use capacitors within 6 months after delivered. for more than 6 months, confirm the solderability and capacitance before use.



編號DOC NO.:	DEC-SA-WI003
版本REV.:	B/4
日期DATE:	2023年12月9日
頁碼PAGE:	8 / 10

3. 測量和使用注意事項

MEASURING AND APPLICATION NOTICE

8.1. 測量注意事項

Measurement notice

請在以下條件下測量。

Please measure under the following conditions.

8.1.1. 標準大氣條件

Standard atmospheric conditions

除非另有規定,所有試驗和測量應按在IEC 60068-1的5.3中規定的試驗用標準大氣條件下表進行。

Unless otherwise specified, all tests and measurements shall be made under standard atmospheric conditions for testing as given in 5.3 of IEC 60068-1.

温度	相對濕度	氣壓	
Temperature	Relative humidity	Air pressure	
15°C~35°C	25%~75%		

Before the measurements are made, the capacitor shall be stored at the measuring temperature for a time sufficient to allow the entire capacitor to reach this temperature. The period as prescribed for recovery at the end of a test is normally sufficient for this purpose.

在標準大氣條件下進行測量,其測量結果存在爭議時應采用仲裁溫度(見8.1.3)重復測量。

Test and measurement shall be made under standard atmospheric conditions for testing, in the event of a dispute, the measurements shall be repeated using one of the referee temperatures (as given in 8.1.3).

當按某一順序進行試驗時,一個試驗的最後測量可以作爲下一試驗的初始測量。

When tests are conducted in a sequence, the final measurements of one test may be taken as the initial measurements for the succeeding test. 在測量期間,不應使電容器受到氣流、陽光直射或可能引起誤差的其他影響。

During measurements the capacitor shall not be exposed to draughts, direct sunlight or other influences likely to cause error.

8.1.2. 恢復條件

Recovery conditions

除非另有規定,恢復應在試驗用標準大氣條件(見8.1.1)下進行。

Unless otherwise specified recovery shall take place under the standard atmospheric conditions for testing (8.1.1).

如果恢復必須在嚴格控制的條件下進行,應采用IEC 60068-1中5.4.1的控制條件。

If recovery under closely controlled conditions is necessary, the controlled recovery conditions of 5.4.1 of IEC 60068-1 shall be used.

除非有關規範另有規定,恢復時間應爲1h~2h。

Unless otherwise specified in the relevant specification, a duration of $1\,\mathrm{h}$ to $2\,\mathrm{h}$ shall be used.

8.1.3. 仲裁條件

Referee conditions

在仲裁情況下,應選用IEC 60068-1中5.2中規定的仲裁試驗用標準大氣條件。

For referee purposes, one of the standard atmospheric conditions for referee tests taken from 5.2 of IEC 60068-1, as given in table 1 below, shall be selected:

溫度	相對濕度	氣壓	
Temperature	Relative humidity	Air pressure	
25°C±1°C	48%~52%	86kPa∼106kPa	

8.2. 工作電壓

Operating voltage

嚮電容器施加的電壓切勿超過額定電壓。

The voltage applied to the capacitor must not exceed the rated voltage.

電壓	直流電壓	直流+交流電壓	交流電壓	脈沖電壓
Voltage	DC Voltage	DC+AC Voltage	AC Voltage	Pulse Voltage
測量位置 Positional Measurement	Vo-p	Se p	N d d d d d d d d d d d d d d d d d d d	V P-P



編號DOC NO.:	DEC-SA-WI003
版本REV.:	B/4
日期DATE:	2023年12月9日
頁碼PAGE:	9 / 10

在交流電路或紋波電流電路中使用直流額定電壓電容器時,請務必將外加電壓的Vp-p值或包含直流偏置電壓的Vo-p值維持在額定電壓範圍內。

When DC-rated capacitors are to be used in AC or ripple current circuits, be sure to maintain the Vp-p value of the applied voltage or the Vo-p which contains DC bias within the rated voltage range.

若嚮電路施加電壓,開始或停止時可能會因諧振或切換產生暫時的異常電壓。請務必使用額定電壓範圍包含這些異常電壓的電容器。

When the voltage is applied to the circuit, starting or stopping may generate irregular voltage for a transit period because of resonance or switching. Be sure to use a capacitor with a rated voltage range that includes these irregular voltages.

8.3. 過電壓影響

Overvoltage effects

施加到電容器的過電壓可能會導致電容器內部介質層擊穿而引起電路短路。

The overvoltage applied to the capacitor may cause the dielectric layer of the capacitor to break down and cause a short circuit.

擊穿前的可持續時間取決於施加電壓和周圍溫度。

The duration before the breakdown depends on the applied voltage and the ambient temperature.

8.4. 焊錫

Soldering

當在PCB/PWB焊錫這個產品時,不要超過電容器的焊錫耐熱性標準。過度的熱量會使電容器內部焊錫熔化,可能導致熱沖擊而使陶瓷介質出現暗裂。

When soldering this product to a PCB/PWB, do not exceed the solder heat resistance specifications of the capacitor. Subjecting this product to excessive heating could melt the internal junction solder and may result in thermal shocks that can crack the ceramic element.



注意:請不要使用於雙波峰焊錫中,如 果需要使用於雙波峰焊錫,請提前通知 我公司。

Note: please do not use in double wave soldering. If you use double wave soldering, please inform our company in advance.




Fig.: Wave-soldering temperature-time profile to recommend

當使用烙鐵進行手工焊錫時,應該遵照下列條件:

When soldering capacitor with a soldering iron, it should be performed in the following conditions.

焊錫溫度: 320℃最大

Temperature of iron-tip: 320 degrees C. Max.


烙鐵頭: 不超過40W Soldering iron wattage: 40W max. 焊錫時間: 不超過3.0秒 Soldering time: 3.0 sec. Max.




編號DOC NO.:	DEC-SA-WI003
版本REV.:	B/4
日期DATE:	2023年12月9日
頁碼PAGE:	10 / 10

編帶尺寸規格 TAPING SPECIFICATIONS

■ Method 1 : sprocket hole between parts



■ Method 2: sprocket hole between leads



ltem		Symbol	Specification (mm)	Remarks
Lead-wire diameter		Ød	0.5±0.1	
	Pitch of component			
	P0		Cumulative pitch error: 1.0mm/20 pitch	
	Feed hole center to lead			
Hole	e center to component center	P2		
	Lead-to-lead distance	F	5.08±0.8	
	Component alignment	Δh	≤2.0	
Devi	Deviation along tape, Left or right		≤1.3	
	Tape width		18.0+1.0/-0.5	
	Hold-down tape width		≥7.0	
	Hole position	W1	9.0+0.75/-0.5	
	Hole-down tape position	W2	≤3.0	
Height of component from tape	Straight lead	Н	18.0+2/-0	
center	Kinked lead	Н0	16.0±0.5	
Component height		H1	≤32.25	
Feed hole diameter		D0	4.0±0.3	
Total tape thickness		t1	≤0.9	Ground paper: 0.5±0.1mm
Total t	Total thickness, tape and lead wire		≤1.5	
	Length of snipped		≤11.0	

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Ceramic Disc Capacitors category:

Click to view products by Dersonic manufacturer:

Other Similar products are found below:

5AU100JCECA 5AU220JCGCA 5AU560JCJCA HCU180KBCDRTKR 432202101621 101GHR102K W1X223MCVCF0KR CC-100N NCD102K1KVY5FF NCD103M1KVZ5UF NCD331K1KVY5FF AOL-1502-02 DEF2CLH040CN3A F05B1B331KN0B0SHN0 8903D0 90410-10 YV101103Z060HAND5P SL102101J060BAND5P YP202102K080D04A7H ZU501103M090B20C6P ZU102103M100X05B0P YP102271K050B20C6P YP102391K050BAND5P YP501101K040BAND5P ZU102103M100BAND5H YP102681K060B20C6P YP501121K040B20C6P SL102181J070HAND5P YP501471K040B20C6P SL102151J070HAND5P YP501102K050HAND5P ZU501102M050B20C6P YP501472K100B20C6P ZU102103M100B20C0P YV500223Z080HAND5P CC1H220KA1EDCH4B1100 HGK3FE102MG3BW HGK3FF152MA3BW HGK3FE472MG3BW-3085A5 HGK3AB271KG2BW SL500330J040B20C2P SL501510J050B20C6P SL102221J080HAND5P YP500103M100HAND5P SL102101J060HAND5H YP102222K080D20C5B LN202471K080D3EAEH S103Z59Y5VP6TK7R S222Z33Y5VP6TK5R S472Z43Y5VP6TK5R