STATSHIELD® METAL-OUT SERIES

Specifications: Standard Document

ANSI/ESD S11.4

Electrical Properties

ANSI/ESD S541 (ANSI/ESD S20.20)

Meets Requirements of:

ESD Protective Packaging Level 3 Technical Requirements



Test Procedures/Method ANSI/ESD STM11.11

ANSI/ESD STM11.11 ANSI/ESD STM11.31, EIA 541 Modified Incline Plane

Modified Incline Plane

ANSI/EIA-541/Appendix E, 1 kV Discharge

Typical Values

Surface Resistance: Outer Surface 1×10^4 to $< 1 \times 10^8$ ohms 1×10^4 to $< 1 \times 10^{11}$ ohms Inner Surface Discharge Shielding <20 nJ

Charge Generation Teflon: -0.03 nC/sq. in. Quartz: +0.10 nC/sq. in.

Capacitance Probe (to dissipate 1 KV) <30 volts

Physical Properties:

Film Thickness Nominal 3.0 mil (0.07mm) ±10% Width (Inside Dimensions) Nominal -0" / + 0.250" Length (Inside Dimensions) Nominal + 0 125" **Light Transmission** 40% (Tobias) Puncture Resistance >10 lbs Heat Seal >10 lbs/in.

Non-corrosive Pass Silicone Not detected

Marking Adhesion Pass MIL-STD-3010, 1003

ASTM D-1003 MIL-STD-3010, 2065 375°F, 1/2 sec 60 psi MIL-STD-3010. M3005

FTIR

IPC-TM-650 2.4.1

Date & Lot Code

Printed for QC

Traceablility

Soft Fold Bottom

ANSI/ESD S541 Section 6.2 Outside an EPA

"Transportation of sensitive products outside of an EPA shall require packaging that provides:

1. Low charge generation

2. Dissipative or conductive materials for intimate contact

3. A structure that provides electrostatic discharge shielding."

RoHS, REACH and Conflict Minerals Statement

See the Desco Industries RoHS, REACH, and Conflict Minerals Statement: Desco.com/pdf/REACHRoHSConflictMinerals-Desco Bags.pdf

See the Desco Limited Warranty:

Desco.DescoIndustries.com/Limited-Warranty.aspx

Statshield[®] and Statfree[®] are Registered Trademarks of Desco Industries Inc.

For product listing, Click **HERE** See Bag Selection Chart Click HERE



Made in the United States of America

Specifications and procedures subject to change without notice.

STATSHIELD® BAG, SHIELDING, METAL-OUT CONSTRUCTION, ZIPPER, 3.0 MIL (0.07mm)



Statshield® bags are packaged 100 per package in an oversized shielding bag.

Mixed Unsortable Plastic Scrap Mixed unsortable plastic scrap shall contain assorted plastics of multiple grades that are co-extruded, bonded or laminated

together which are unsortable into individual grades

Desco's bags are recyclable

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407

PHONE (781) 821-8370

DRAWING NUMBER 13205

DATE: June 2019

Low Charging Clear Zipper

Opening

STATSHIFI D Static Shielding Bad

(inches)

Side Weld Seals 3/8 in. (±0.10)

Lip 1 in. (±0.125)

Shielding Layer

Polyester Layer Low Charging Static

Low Charging Static

Dissipative Proprietary

Dissipative Proprietary Inner Polyethylene Layer

See Shielding Bag Storage at TB-7057.

High Performance Static Dissipative Abrasion Resistant Coating

Lip

Lenath

(inches)

Weld Seal

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Antistatic Control Products category:

Click to view products by Desco manufacturer:

Other Similar products are found below:

13505 13870 14404 20-053-0017 2229 2231 3039 37061 39792 42470 XON-ASB4X30 XON-ASB4X6 XON-ASB6X30 09813 09857

XON-ASB8X10 XON-ASB6X10 19695 09037 68101 68103 73741 13515 13869 13868 13485 13457 13245 13332 13205 13135 91070

8031 8523 13080 13215 157 ROLL BEIGE 1.0 VERAX1R-300R 17260 66051 12550 19863 09121 73831 13340 13338 04541 19696

16104 SPI-20686