STATSHIELD® METAL-IN BOXED SERIES

Specifications:

Electrical Properties

Standard Document

ANSI/ESD S541 (ANSI/ESD S20.20) ANSI/ESD S11.4

Meets Requirements of:

ESD Protective Packaging Level 3 Technical Requirements

Test Procedures/Method

Surface Resistance: $1 \times 10^4 \text{ to} < 1 \times 10^{11} \text{ ohms}$ Outer Surface ANSI/ESD STM11.11 1×10^4 to $< 1 \times 10^{11}$ ohms Inner Surface ANSI/ESD STM11.11 Discharge Shielding ANSI/ESD STM11.31. EIA 541 Charge Generation Teflon: 0.09 nC/sq. in. Modified Incline Plane Quartz: 0.01 nC/sq. in. Modified Incline Plane

Typical Values


Capacitance Probe (to dissipate 1 KV) <30 volts ANSI/EIA-541/Appendix E, 1kV Discharge

Physical Properties

Film Thickness Nominal 0.0030" (0.0762mm) ±10% MIL-STD-3010, 1003 Width (Inside Dimensions) Nominal -0" / + 0.125" Length (Inside Dimensions) Nominal ± 0.125" Light Transmission >40% (Tobias) **ASTM D-1003** Heat Seal >10 lbs/in 375°F, 1/2 sec 60 psi 4600 PSI, 32 MPa Tensile Strength **ASTM 882**

Puncture Resistance >10 lbs MIL-STD-3010, 2065 Non-corrosive Pass MIL-STD-3010. M3005 Silicone Not detected FTIR

Marking Adhesion Pass IPC-TM-650 2 4 1



DescoIndustries.com Made in America

Overall Width (OW)

STATSHIELD®

Metal In Construction

Discharge Shielding RoHS

Static Shielding Bag

Opening

Length (L)



Date & Lot Code

Printed for QC

Traceablility

Low Charging Static Dissipative Proprietary Inner Polyethylene Layer

Dissipative Proprietary

Outer Polyester Layer Aluminum Shielding Layer

ANSI/ESD S541 Section 6.2 Outside an EPA

"Transportation of sensitive products outside of an EPA shall require packaging that provides:

- 1. Low charge generation
- 2. Dissipative or conductive materials for intimate contact
- 3. A structure that provides electrostatic discharge shielding."

RoHS, REACH and Conflict Minerals Statement

See the Desco Industries RoHS. REACH, and Conflict Minerals Statement: Desco.com/pdf/REACHRoHSConflictMinerals-Desco Bags.pdf

See the Desco Limited Warranty:

Desco.DescoIndustries.com/Limited-Warranty.aspx

Mixed Unsortable Plastic Scrap

Mixed unsortable plastic scrap shall contain assorted plastics of multiple grades that are co-extruded, bonded or laminated together which are unsortable into individual grades

Desco's bags are recyclable

Statshield® bags are packaged 100 per package in an oversized shielding bag. See Shielding Bag Storage at TB-7057.

Statshield® and Statfree® are Registered Trademarks of Desco Industries Inc. See Bag Selection Chart Click HERE.



United States of America

Specifications and procedures subject to change without notice.

STATSHIELD® METAL-IN BOXED, 0.0030" (0.0762mm)



DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407

PHONE (781) 821-8370

DRAWING NUMBER 13330

DATE: April 2018

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Antistatic Control Products category:

Click to view products by Desco manufacturer:

Other Similar products are found below:

13020 13490 13870 13879 13881 13883 13882 14404 2202SP 3039 37061 42470 09060 09857 42516 37059 04563 17252 19691 19695 09037 09826 09813 66070 100816 68101 68103 98132 73741 13868 13485 13457 13245 13468 13420 13332 13205 13135 91070 8031 8523 66085 40931 37081 13080 13215 13806 73749 010-0225 17260